

HINDUSTAN PETROLEUM CORPORATION LIMITED

(A Government of India Enterprise)

QUALITY CONTROL LABORATORY

MAZGAON TERMINAL

LUBE PLANT, HAY BUNDER ROAD, MAZGAON

MUMBAI,400033

LABORATORY TEST REPORT**ENKLO 100 (210 L)(0266241)**

Laboratory Serial No.	PP 1562	Sample Drawn By	QC OFFICER
JDE Serial No	1229686	Date Sample Drawn	17/03/23
Batch No / Lot No	M1-23-C-303	Date Received In Lab	17/03/23
Work Order No	1033050	Date Tested	17/03/23
Tank /Kettle/Location	WHS	Particular of Sample	DRUM
Plant Code/ Name	14546	Mazgaon TML Lubes-(STP 0101)	Sampling Plan
			IS 1447

Test Line Number	Test Description/ Characteristics	Units	Test Method	Specifications		Result Value
				Min	Max	
10	ZINC	%Wt	D6443 EDTA	.026	.070	.031
11	EMULSION CHAR @ 82° / 30MIN	Milliliter	P91 D1401		40-37-3	40-39-1
1	APPERANCE	Visual	VISUAL	B&C	B&C	B&C
8	POUR POINT	°C	P10 D97	-	0	-12
2	ACIDITY TOTAL	mg KOH/g	P2 D664 D974	-	1.50	.71
4	FLASH POINT	°C	P69 D92	210	-	248
3	DENSITY@29.5°C	gm/cc	P16 D1298 D4052 D7042	-	-	.8827
5	FOAMING STABILITY SEQ1	Milliliter	P67 D892	NIL	NIL	NIL
6	FOAMING STABILITY SEQ2	Milliliter	P67 D892	NIL	NIL	NIL
7	FOAMING STABILITY SEQ3	Milliliter	P67 D892	NIL	NIL	NIL
12	KV @ 100°C	cSt	P 25 D 445 D7042	-	-	11.33
9	K V @ 40°C	cSt	P25 D445 D7042	90.00	110.00	103.30
13	RUST TEST	.	P96 D665	P	P	P
14	VISCOSITY INDEX (VI)	.	P56 D2270	90	-	95

Remarks : Sample meets the specification in above tests.

Note:

- 1) The report refers only to the sample tested.
- 2) The test report shall not be reproduced except in full without prior written approval of the Lab Incharge.
- 3) This test report shall not be used in any advertising media or as evidence in the Court of Law without prior written consent of Laboratory.
- 4) Test results reported are valid at the time of testing
- 5) This is a system generated test report and hence does not require signature.

Reviewed and Authorized by:
PARVEEN RUBANA(31989940)