

HINDUSTAN PETROLEUM CORPORATION LIMITED

(A Government of India Enterprise)

QUALITY CONTROL LABORATORY

MAZGAON TERMINAL

LUBE PLANT, HAY BUNDER ROAD, MAZGAON

MUMBAI,400033

LABORATORY TEST REPORT**ENKLO 100 (210 L)(0266241)**

Laboratory Serial No.	FB 1589	Sample Drawn By	BLENDING OFFICER
JDE Serial No	1211026	Date Sample Drawn	06/01/23
Batch No / Lot No	M1-23-D-447	Date Received In Lab	06/01/23
Work Order No	1010818	Date Tested	06/01/23
Tank /Kettle/Location	WHS2	Particular of Sample	DRUM
Plant Code/ Name	14546	Mazgaon TML Lubes-(STP 0101)	Sampling Plan
			IS 1447

Test Line Number	Test Description/ Characteristics	Units	Test Method	Specifications		Result Value
				Min	Max	
11	ZINC	%Wt	D6443 EDTA	.026	.070	.034
1	APPERANCE	Visual	VISUAL	B&C	B&C	B&C
4	EMULSION CHAR @54 °C / 30 MIN	Milliliter	P91 D1401	-	3	0
9	POUR POINT	°C	P10 D97	-	0	-23
2	ACIDITY TOTAL	mg KOH/g	P2 D664 D974	-	1.50	.45
5	FLASH POINT	°C	P69 D92	210	-	242
3	DENSITY@29.5°C	gm/cc	P16 D1298 D4052 D7042	-	-	.8853
6	FOAMING STABILITY SEQ1	Milliliter	P67 D892	NIL	NIL	NIL
7	FOAMING STABILITY SEQ2	Milliliter	P67 D892	NIL	NIL	NIL
8	FOAMING STABILITY SEQ3	Milliliter	P67 D892	NIL	NIL	NIL
10	K V @ 40°C	cSt	P25 D445 D7042	90.00	110.00	105.10
13	RUST TEST	.	P96 D665	P	P	P
12	VISCOSITY INDEX (VI)	.	P56 D2270	90	-	100

Remarks : Sample meets the specification in above tests.

Note:

- 1) The report refers only to the sample tested.
- 2) The test report shall not be reproduced except in full without prior written approval of the Lab Incharge.
- 3) This test report shall not be used in any advertising media or as evidence in the Court of Law without prior written consent of Laboratory.
- 4) Test results reported are valid at the time of testing
- 5) This is a system generated test report and hence does not require signature.

Reviewed and Authorized by:

PAKALE SANTOSH BHIKAJI(38031160)