

HINDUSTAN PETROLEUM CORPORATION LIMITED

(A Government of India Enterprise)

QUALITY CONTROL LABORATORY

MAZGAON TERMINAL

LUBE PLANT, HAY BUNDER ROAD, MAZGAON

MUMBAI,400033

LABORATORY TEST REPORT**HP MILCY POWER 15W 40 (210L)(0818241)**

Laboratory Serial No.	FB 1703	Sample Drawn By	QC OFFICER
JDE Serial No	1216694	Date Sample Drawn	28/01/23
Batch No / Lot No	M1-23-A-481	Date Received In Lab	28/01/23
Work Order No	1017115	Date Tested	28/01/23
Tank /Kettle/Location	WHS	Particular of Sample	DRUM
Plant Code/ Name	14546	Mazgaon TML Lubes-(STP 0101)	Sampling Plan
			IS 1447

Test Line Number	Test Description/ Characteristics	Units	Test Method	Specifications		Result Value
				Min	Max	
6	TBN	mg KOH/g	P86 D2896	9.00	-	11.63
1	APPEARANCE	.	VISUAL	B&C	B&C	B&C
11	CCS @ -20°C	Centi Poise	P108 D5293	-	7000	6842
3	DENSITY@29.5°C	gm/cc	P16 D1298 D4052 D7042	-	-	.8839
4	FLASHPOINT	°C	P69 D92	190	-	226
8	KV @ 100°C	cSt	P25 D445 D7042	14.00	15.20	14.41
7	KV @ 40°C	cSt	P25 D445 D7042	-	-	106.0
5	POUR POINT	°C	P 10 D 97	-	-21	-30
2	SULFATEDASH	%Wt	P 4 D 874	1.190	1.420	1.200
9	VISCOSITY INDEX (VI)	.	P56 D2270	120	-	139
10	ZINC	%Wt	D6443 EDTA	.11	.13	.12
15	CALCIUM	%Wt	ASTMD6443,EDTA	.391	.478	.422
15	SULFATED ASH	%Wt	P 4 D 874 IP 163	1.50	1.83	1.77
15	TBN	mg KOH/g	P86 D2896	11.3	-	11.6
15	ZINC	%Wt	ASTMD6443,EDTA	.112	.137	.118

Remarks : Sample meets the specification in above tests.

Note:

- 1) The report refers only to the sample tested.
- 2) The test report shall not be reproduced except in full without prior written approval of the Lab Incharge.
- 3) This test report shall not be used in any advertising media or as evidence in the Court of Law without prior written consent of Laboratory.
- 4) Test results reported are valid at the time of testing
- 5) This is a system generated test report and hence does not require signature.

Reviewed and Authorized by:

PARVEEN RUBANA(31989940)