

HINDUSTAN PETROLEUM CORPORATION LIMITED

(A Government of India Enterprise)

QUALITY CONTROL LABORATORY

MAZGAON TERMINAL

LUBE PLANT, HAY BUNDER ROAD, MAZGAON

MUMBAI,400033

LABORATORY TEST REPORT**PARTHAN EP 320 (210 L)(0883241)**

Laboratory Serial No.	FB-242	Sample Drawn By	OPERATION OFFICER
JDE Serial No	1244867	Date Sample Drawn	27/05/23
Batch No / Lot No	M1-23-E-972	Date Received In Lab	27/05/23
Work Order No	1054295	Date Tested	28/05/23
Tank /Kettle/Location	WHS	Particular of Sample	DRUM
Plant Code/ Name	14546	Mazgaon TML Lubes-(STP 0101)	Sampling Plan
		IS 1447	

Test Line Number	Test Description/ Characteristics	Units	Test Method	Specifications		Result Value
				Min	Max	
1	APPEARANCE	.	VISUAL	C	C	C
2	ASH	%Wt	IS 1448(P4), ASTMD482	-	.100	.010
3	DENSITY@29.5°C	gm/cc	P16,ASTMD4052, D1298, D7042	-	-	.8669
4	FLASH POINT°C,COC	°C	IS1448(P69),ASTMD92	220	-	228
6	FOAMING TEST SEQ1	Milliliter	IS1448(P67), ASTMD892		100/0	0/0
7	FOAMING TEST SEQ2	Milliliter	IS1448(P67), ASTMD892	-	50/0	10/0
8	FOAMING TEST SEQ3	Milliliter	IS1448(P67), ASTMD892	-	100/0	0/0
9	RUST TEST A/B	.	IS1448(P96),ASTMD665	P	P	P
10	KINEMATIC VISCOSITY @40°C	cSt	IS1448(P25),ASTMD445, D7042	300.0	340.0	323.2
5	EMULSION TEST@82°C/30MIN	Milliliter	IS1448(P91), ASTMD1401	40-40-0	40-40-0	40-40-0
11	PHOSPHORUS	%Wt	IS1448(P101),ASTMD1091, D6443	.0098	.0145	.0099

Remarks : SAMPLE MEETS THE SPECIFICATION IN ALL ABOVE TEST PARAMETERS.

Note:

- 1) The report refers only to the sample tested.
- 2) The test report shall not be reproduced except in full without prior written approval of the Lab Incharge.
- 3) This test report shall not be used in any advertising media or as evidence in the Court of Law without prior written consent of Laboratory.
- 4) Test results reported are valid at the time of testing
- 5) This is a system generated test report and hence does not require signature.

Reviewed and Authorized by:

WARANG CHANDRAKANT PRABHAKAR(30074520)