



HINDUSTAN PETROLEUM CORPORATION LIMITED
(A Government of India Enterprise)
QUALITY CONTROL LABORATORY
MAZGAON LUBE PLANT
HAY BUNDER ROAD, MAZGAON
MUMBAI - 400033, MAHARASHTRA
LABORATORY TEST REPORT



Product	0202266 (HP ENKLO 32 - DRUM 208L)	Test Report Number	4546232400309
Loc/ Customer/ Supplier	4546 (MAZGAON TML LUBES)	Sample Number	40000000887
Process/Purchase/Sales Order	10001481 4900902471 0001	Lab Sr. No	FB 433
Source of the Sample	DRUM	ULR Number	TC-5177230000000309F
Tank No.	WHS2 (Lube Warehouse 2)	Date of Sampling	26.07.2023 12:37:44
Type of the Sample	COMPOSITE	Date of Receipt of Sample	21.07.2023
Number/Quantity of Sample	1*1 L	Date(s) of Sample Testing	21.07.2023 To 21.07.2023
Batch No.	M2-23G0034	Date of Issue of the Report	26.07.2023 18:17:57
Stock Represented	16.000 EA	Sample Drawn By	KUMAR AJAY
Test Required	FB		
Sampling Plan/Method	IS 1447	Seal No.	Wooden Box Seal
Reason for Testing	PRODUCTION - DRUM		Aluminium Box Seal

S.No	Characteristics	UOM	Test Method	Specifications	Result
1	APPEARANCE	-	VISUAL	BRIGHT AND CLEAR	BRIGHT AND CLEAR
2	DENSITY AT 29.5°C	g/cm ³	ASTM D7042	TO REPORT	0.8739
3	EMULSION CHARACTERISTICS AT 54°C/20 MIN	-	ASTM D1401	NOT WORSE THAN 40-37-3 (20)	40-38-2 (20)
4	FLASH POINT, COC	°C	ASTM D92	MIN 190	222
5	FOAM STABILITY SEQUENCE I	mL	ASTM D892	0 - 0	0
6	FOAM STABILITY SEQUENCE II	mL	ASTM D892	0 - 0	0
7	FOAM STABILITY SEQUENCE III	mL	ASTM D892	0 - 0	0
8	FOAMING TENDENCY SEQUENCE I	mL	ASTM D892	MAX 50	10
9	FOAMING TENDENCY SEQUENCE II	mL	ASTM D892	MAX 50	10
10	FOAMING TENDENCY SEQUENCE III	mL	ASTM D892	MAX 50	10
11	KINEMATIC VISCOSITY AT 100°C	cSt	ASTM D7042	TO REPORT	5.143
12	KINEMATIC VISCOSITY AT 40°C	cSt	ASTM D7042	29.00 - 34.00	30.77
13	VISCOSITY INDEX	-	ASTM D2270	MIN 90	93
14	POUR POINT	°C	ASTM D97	MAX -3	-18
15	RUST TEST AT 60°C, 24 HOURS, SSW	-	ASTM D665	PASS	PASS
16	ZINC CONTENT	%Wt	ASTM D6443	0.026 - 0.070	0.036

Remarks : The Sample meets the Specification in the above tested parameters only.

Tested By:
WARANG CHANDRAKANT PRABHAKAR (30074520)

Reviewed and Authorised By:
WARANG CHANDRAKANT PRABHAKAR
(30074520)

Note:
1) The sample is drawn by client and results apply to the sample as received.
2) The test report shall not be reproduced except in full without prior written approval of the Lab In-charge.
3) This test report shall not be used in any advertising media or as evidence in the Court of Law without prior written consent of Laboratory.
4) Test results reported are valid for the sample tested, which was provided at the time of testing.
5) The details of sample submitted is provided by sender / customer. The authenticity / correctness of the submitted data is the responsibility of the sender/customer.
6) This is a system generated test report. Hence, it does not require signature.

