



HINDUSTAN PETROLEUM CORPORATION LIMITED
(A Government of India Enterprise)
QUALITY CONTROL LABORATORY
SILVASA LUBE PLANT
KHANVEL UDVA ROAD, KHERDI
SILVASSA - 396230, DADRA AND NAGAR HAVELI



LABORATORY TEST REPORT

Product	0202241 (HP ENKLO 32 - DRUM 210L (0.9 MM))	Test Report Number	4512232400782
Loc/ Customer/ Supplier	4512 (SILVASA LUBE TML)	Sample Number	40000003094
Process/Purchase/Sales Order	10005526 4902442608 0001	Lab Sr. No	FB-473
Source of the Sample	DRUM	ULR Number	TC-6943230000000782F
Tank No.	WHS (WAREHOUSE)	Date of Sampling	11.09.2023 08:12:05
Type of the Sample	COMPOSITE	Date of Receipt of Sample	08.09.2023
Number/Quantity of Sample	1*1 L	Date(s) of Sample Testing	08.09.2023 To 08.09.2023
Batch No.	SI-23J0575	Date of Issue of the Report	11.09.2023 16:08:12
Stock Represented	23.000 EA	Sample Drawn By	PANDEY PRATHIMESH KUMAR
Test Required	FB		
Sampling Plan/Method	IS 1447	Seal No.	Wooden Box Seal
Reason for Testing	PRODUCTION - DRUM		Aluminium Box Seal

S.No	Characteristics	UOM	Test Method	Specifications	Result
1	APPEARANCE	-	VISUAL	BRIGHT AND CLEAR	BRIGHT AND CLEAR
2	DENSITY AT 29.5°C	g/cm ³	ASTM D7042	TO REPORT	0.8723
3	EMULSION CHARACTERISTICS AT 54°C/20 MIN	-	ASTM D1401	NOT WORSE THAN 40-37-3 (20)	40-39-1 (20)
4	FLASH POINT, COC	°C	ASTM D92	MIN 190	238
5	FOAM STABILITY SEQUENCE I	mL	ASTM D892	0 - 0	0
6	FOAM STABILITY SEQUENCE II	mL	ASTM D892	0 - 0	0
7	FOAM STABILITY SEQUENCE III	mL	ASTM D892	0 - 0	0
8	FOAMING TENDENCY SEQUENCE I	mL	ASTM D892	MAX 50	10
9	FOAMING TENDENCY SEQUENCE II	mL	ASTM D892	MAX 50	20
10	FOAMING TENDENCY SEQUENCE III	mL	ASTM D892	MAX 50	10
11	KINEMATIC VISCOSITY AT 100°C	cSt	ASTM D7042	TO REPORT	5.193
12	KINEMATIC VISCOSITY AT 40°C	cSt	ASTM D7042	29.00 - 34.00	30.75
13	VISCOSITY INDEX	-	ASTM D2270	MIN 90	97
14	POUR POINT	°C	ASTM D97	MAX -3	-6
15	RUST TEST AT 60°C, 24 HOURS, SSW	-	ASTM D665	PASS	PASS
16	ZINC CONTENT	%Wt	ASTM D6443	0.026 - 0.070	0.030

Remarks : The Sample meets the Specification in the above tested parameters only.

Tested By:
GAYEN SAUGATA KUMAR (31960410)

Reviewed and Authorised By:
GAYEN SAUGATA KUMAR (31960410)

Note:
1) The sample is drawn by client and results apply to the sample as received.
2) The test report shall not be reproduced except in full without prior written approval of the Lab In-charge.
3) This test report shall not be used in any advertising media or as evidence in the Court of Law without prior written consent of Laboratory.
4) Test results reported are valid for the sample tested, which was provided at the time of testing.
5) Entire quantity of sample expended during testing.
6) The details of sample submitted is provided by sender / customer. The authenticity / correctness of the submitted data is the responsibility of the sender/customer.
7) This is a system generated test report. Hence, it does not require signature.

