



HINDUSTAN PETROLEUM CORPORATION LIMITED
(A Government of India Enterprise)
QUALITY CONTROL LABORATORY
MAZGAON LUBE PLANT
HAY BUNDER ROAD, MAZGAON
MUMBAI - 400033, MAHARASHTRA



LABORATORY TEST REPORT

Product	0235000 (HP ENKLO 46 - BULK)	Test Report Number	4546232401538
Loc/ Customer/ Supplier	4546 (MAZGAON TML LUBES)	Sample Number	40000002971
Process/Purchase/Sales Order	20001855 4902317963 0001	Lab Sr. No	MB 2483
Source of the Sample	BLENDING KETTLE	ULR Number	TC-5177230000001538F
Tank No.	BULK (BULK DUMMY)	Date of Sampling	07.09.2023 11:07:57
Type of the Sample	COMPOSITE	Date of Receipt of Sample	05.09.2023
Number/Quantity of Sample	1*1 L	Date(s) of Sample Testing	05.09.2023 To 05.09.2023
Batch No.	M2-23J0236	Date of Issue of the Report	07.09.2023 13:24:56
Stock Represented	21.000 KL	Sample Drawn By	ANKITA MEENA
Test Required	MB		
Sampling Plan/Method	IS 1447	Seal No.	Wooden Box Seal
Reason for Testing	PRODUCTION - KETTLE		Aluminium Box Seal

S.No	Characteristics	UOM	Test Method	Specifications	Result
1	APPEARANCE	-	VISUAL	BRIGHT AND CLEAR	BRIGHT AND CLEAR
2	EMULSION CHARACTERISTICS AT 54°C/20 MIN	-	ASTM D1401	NOT WORSE THAN 40-37-3 (20)	40-40-0 (20)
3	VISCOSITY INDEX	-	ASTM D2270	MIN 90	100
4	ZINC CONTENT	%Wt	ASTM D6443	0.026 - 0.070	0.036
5	KINEMATIC VISCOSITY AT 100°C	cSt	ASTM D7042	TO REPORT	6.539
6	KINEMATIC VISCOSITY AT 40°C	cSt	ASTM D7042	42.00 - 50.00	43.55
7	DENSITY AT 29.5°C	g/cm ³	ASTM D7042	TO REPORT	0.8754
8	FOAM STABILITY SEQUENCE I	mL	ASTM D892	0 - 0	0
9	FOAM STABILITY SEQUENCE II	mL	ASTM D892	0 - 0	0
10	FOAM STABILITY SEQUENCE III	mL	ASTM D892	0 - 0	0

Remarks : The Sample meets the Specification in the above tested parameters only.

Tested By:
PAKALE SANTOSH BHIKAJI (38031160)

Reviewed and Authorised By:
PAKALE SANTOSH BHIKAJI (38031160)

Note:
1) The sample is drawn by client and results apply to the sample as received.
2) The test report shall not be reproduced except in full without prior written approval of the Lab In-charge.
3) This test report shall not be used in any advertising media or as evidence in the Court of Law without prior written consent of Laboratory.
4) Test results reported are valid for the sample tested, which was provided at the time of testing.
5) Entire quantity of sample expended during testing.
6) The details of sample submitted is provided by sender / customer. The authenticity / correctness of the submitted data is the responsibility of the sender/customer.
7) This is a system generated test report. Hence, it does not require signature.

