



HINDUSTAN PETROLEUM CORPORATION LIMITED
(A Government of India Enterprise)
QUALITY CONTROL LABORATORY
MAZGAON LUBE PLANT
HAY BUNDER ROAD, MAZGAON
MUMBAI - 400033, MAHARASHTRA
LABORATORY TEST REPORT



Product	0360241 (HP WAYLUBE N 68 - DRUM 210L (0.9 MM))	Test Report Number	4546232400022
Loc/ Customer/ Supplier	4546 (MAZGAON TML LUBES)	Sample Number	40000000143
Process/Purchase/Sales Order	10000088 4900379897 0001	Lab Sr. No	PP-334
Source of the Sample	DRUM	ULR Number	TC-5177230000000022F
Tank No.	WHS1 (Lube Warehouse 1)	Date of Sampling	10.07.2023 15:53:36
Type of the Sample	COMPOSITE	Date of Receipt of Sample	10.07.2023
Number/Quantity of Sample	1*1 L	Date(s) of Sample Testing	10.07.2023 To 10.07.2023
Batch No.	M1-23G0005	Date of Issue of the Report	12.07.2023 09:31:41
Stock Represented	60.000 EA	Sample Drawn By	JAGJEET SINGH
Test Required	FB		
Sampling Plan/Method	IS 1447	Seal No.	Wooden Box Seal
Reason for Testing	PRODUCTION - DRUM		Aluminium Box Seal

S.No	Characteristics	UOM	Test Method	Specifications	Result
1	APPEARANCE	-	VISUAL	CLEAR	CLEAR
2	COPPER STRIP CORROSION FOR 3 H AT 100 °C	-	ASTM D130	NOT WORSE THAN 1B	1A
3	DENSITY AT 29.5°C	g/cm ³	ASTM D7042	TO REPORT	0.879
4	FLASH POINT, COC	COC	ASTM D92	MIN 190	238
5	NEUTRALIZATION NUMBER	mgKOH/g	ASTM D974	MAX 0.25	0.20
6	RUST TEST AT 60°C, 24 HOURS, DW	-	ASTM D665	PASS	PASS
7	SAPONIFICATION VALUE	mgKOH/g	ASTM D94	8.0 - 11.0	9.4
8	KINEMATIC VISCOSITY AT 40°C	cSt	ASTM D7042	62 - 68	62.37
9	VISCOSITY INDEX	-	ASTM D2270	MIN 100	104

Remarks : The Sample meets the Specification in the above tested parameters only.

Tested By:
SARKAR TANMAY KUMAR (31999240)

Reviewed and Authorised By:
SARKAR TANMAY KUMAR (31999240)

Note:
1) The sample is drawn by client and results apply to the sample as received.
2) The test report shall not be reproduced except in full without prior written approval of the Lab In-charge.
3) This test report shall not be used in any advertising media or as evidence in the Court of Law without prior written consent of Laboratory.
4) Test results reported are valid for the sample tested, which was provided at the time of testing.
5) The details of sample submitted is provided by sender / customer. The authenticity / correctness of the submitted data is the responsibility of the sender/customer.
6) This is a system generated test report. Hence, it does not require signature.

