

TEST REPORT : MAK HYDROL HLP 68

Issued to	PLANT MANAGER/CUSTOMER	Date	16-09-2023
Sample Id	439094	Date of Sampling	12-09-2023
Test Report Number	23-58323	Date of Receipt in Lab	12-09-2023
Type of Sample	Final	Date of Testing	16-09-2023
Source of Sample	BT1	Reason for Testing	Batch Formation
Batch Number	B56245234		

Sr.No.	Characteristics	Units	Test Method P of IS 1448/ASTM/ISO	Test Result
1	Appearance	NA	VISUAL	Clear and Bright
2	Crackle Test	NA	SOP-10	Negative
3	Density at 29.5°C	g/ml	ASTM D - 1298	0.8485
4	Emulsion Characteristic at 54°C	MIN	ASTM D - 1401	15.000
5	Foaming charac.- Seq (I) Stability	ML	ASTM D - 892	0
6	Foaming charac.- Seq (I) Tendency	ML	ASTM D - 892	10
7	Foaming charac.- Seq (II) Stability	ML	ASTM D - 892	0
8	Foaming charac.- Seq (II) Tendency	ML	ASTM D - 892	10
9	Kinematic Viscosity at 100°C, cSt	cSt	ASTM D - 445	9.548
10	KV at 40 °C	cSt	ASTM D - 445	67.99
11	Pour Point	°C	ASTM D - 97	-18
12	Viscosity Index	UNI	ASTM D - 2270	120

REMARKS:

1.THE PRODUCT AS REPRESENTED BY THE SAMPLE MEETS THE SPECIFICATION OF MAK HYDROL HLP 68 w.r.t THE ABOVE TESTS CARRIED OUT AS PER INTERNAL SPECIFICATION.

Notes:

- 1.The result relates to the sample tested.
- 2.The certificate shall not be reproduced wholly or in part without prior written consent of the laboratory
- 3.This certificate shall not be used in any advertising media or as evidence in the court of law without written consent of laboratory
NA - Not Applicable
4. Latest version of test methods are used as per latest specification

Authorised Signatory	sharmaganeshraj
Note : This document has been generated electronically and is valid without signature.	