



HINDUSTAN PETROLEUM CORPORATION LIMITED
(A Government of India Enterprise)
QUALITY CONTROL LABORATORY
SILVASA LUBE PLANT
KHANVEL UDVA ROAD, KHERDI
SILVASSA - 396230, DADRA AND NAGAR HAVELI



LABORATORY TEST REPORT

Product	2736241 (HP ENKLO 68 PREMIUM - DRUM 210L (0.9 MM))	Test Report Number	4512232401301
Loc/ Customer/ Supplier	4512 (SILVASA LUBE TML)	Sample Number	40000005699
Process/Purchase/Sales Order	10009434 4904445360 0001	Lab Sr. No	FB-747
Source of the Sample	DRUM	ULR Number	TC-6943230000001301F
Tank No.	WHS (WAREHOUSE)	Date of Sampling	06.11.2023 15:56:45
Type of the Sample	COMPOSITE	Date of Receipt of Sample	04.11.2023
Number/Quantity of Sample	1*1 L	Date(s) of Sample Testing	04.11.2023 To 06.11.2023
Batch No.	SI-23L1150	Date of Issue of the Report	06.11.2023 16:06:07
Stock Represented	100.000 EA	Sample Drawn By	VATSAL PAJVANI
Test Required	FB		
Sampling Plan/Method	IS 1447	Seal No.	Wooden Box Seal
Reason for Testing	PRODUCTION - DRUM		Aluminium Box Seal

S.No	Characteristics	UOM	Test Method	Specifications	Result
1	KINEMATIC VISCOSITY AT 100°C	mm ² /s	ASTM D7042	TO REPORT	8.798
2	KINEMATIC VISCOSITY AT 40°C	mm ² /s	ASTM D7042	62.00 - 72.00	63.38
3	VISCOSITY INDEX	-	ASTM D2270	MIN 90	113
4	ACIDITY, TOTAL	mgKOH/g	ASTM D974	TO REPORT	0.56
5	ACIDITY, INORGANIC	mgKOH/g	ASTM D974	TO REPORT	0
6	APPEARANCE	-	VISUAL	BRIGHT AND CLEAR	BRIGHT AND CLEAR
7	COLOUR (ASTM)	ASTM	ASTM D1500	MAX 2.0	0.5
8	COPPER STRIP CORROSION FOR 3 H AT 100 °C	-	ASTM D130	NOT WORSE THAN 1B	1A
9	DENSITY AT 29.5°C	g/cm ³	ASTM D7042	TO REPORT	0.8513
10	FLASH POINT, COC	°C	ASTM D92	MIN 210	256
11	FOAM STABILITY SEQUENCE I	mL	ASTM D892	TO REPORT	0
12	FOAM STABILITY SEQUENCE II	mL	ASTM D892	TO REPORT	0
13	FOAM STABILITY SEQUENCE III	mL	ASTM D892	TO REPORT	0
14	FOAMING TENDENCY SEQUENCE I	mL	ASTM D892	MAX 150	10
15	FOAMING TENDENCY SEQUENCE II	mL	ASTM D892	MAX 75	10
16	FOAMING TENDENCY SEQUENCE III	mL	ASTM D892	MAX 150	10
17	PHOSPHORUS CONTENT	%Wt	ASTM D6443	MIN 0.027	0.035
18	ZINC CONTENT	%Wt	ASTM D6443	MIN 0.029	0.042
19	POUR POINT	°C	ASTM D97	MAX -12	-30
20	RUST TEST AT 60°C, 4 HOURS, SSW	-	ASTM D665	PASS	PASS

Remarks : The Sample meets the Specification in the above tested parameters only.

Tested By:
GAYEN SAUGATA KUMAR (31960410)

Reviewed and Authorised By:
GAYEN SAUGATA KUMAR (31960410)

Note:
1) The sample is drawn by client and results apply to the sample as received.
2) The test report shall not be reproduced except in full without prior written approval of the Lab In-charge.
3) This test report shall not be used in any advertising media or as evidence in the Court of Law without prior written consent of Laboratory.
4) Test results reported are valid for the sample tested, which was provided at the time of testing.
5) Entire quantity of sample expended during testing.
6) The details of sample submitted is provided by sender / customer. The authenticity / correctness of the submitted data is the responsibility of the sender/customer.
7) This is a system generated test report. Hence, it does not require signature.

