

HINDUSTAN PETROLEUM CORPORATION LIMITED

(A Government of India Enterprise)

QUALITY CONTROL LABORATORY

MAZGAON TERMINAL

LUBE PLANT, HAY BUNDER ROAD, MAZGAON

MUMBAI,400033

LABORATORY TEST REPORT**PARTHAN EP - 460 (210 L)(0707241)**

Laboratory Serial No.	MB 0502	Sample Drawn By	OPNS OFFICER
JDE Serial No	1239033	Date Sample Drawn	28/04/23
Batch No / Lot No	M2-23-D-791	Date Received In Lab	28/04/23
Work Order No	1046454	Date Tested	28/04/23
Tank /Kettle/Location	WHS2	Particular of Sample	DRUM
Plant Code/ Name	14546	Mazgaon TML Lubes-(STP 0101)	Sampling Plan
			IS 1447

Test Line Number	Test Description/ Characteristics	Units	Test Method	Specifications		Result Value
				Min	Max	
1	APPEARANCE	.	VISUAL			B&C
2	ASH	%Wt	IS1448 (P4)	-	.100	.060
3	DENSITY@29.5°C	gm/cc	P16, ASTMD1298, D4052 ,D7042	-	-	.8983
4	FLASH POINT,COC	°C	IS1448(P69), ASTMD 92	230	-	260
5	EMULSION TEST @ 82°/30MIN	Milliliter	IS1448 (P 91),ASTM D1401	40-40-0	-	40-40-0
6	FOAMING TEST SEQ1	Milliliter	IS1448 (P 67), ASTMD 892		100/0	10/0
7	FOAMING TEST SEQ2	Milliliter	IS1448 (P 67), ASTMD 892		50/0	10/0
8	FOAMING TEST SEQ3	Milliliter	IS1448 (P 67), ASTMD 892		100/0	10/0
9	RUST TEST A/B	.	IS1448(P96), ASTM D 665			P
10	KV@40°C	cSt	IS1448(P25), ASTMD445,D7042	440.0	475.0	443.7
11	PHOSPHORUS	%Wt	IS1448(P101),ASTMD1091,D6443	.0098	.0145	.0107

Remarks : SAMPLE MEETS THE SPECIFICATION IN ABOVE TESTS

Note:

- 1) The report refers only to the sample tested.
- 2) The test report shall not be reproduced except in full without prior written approval of the Lab Incharge.
- 3) This test report shall not be used in any advertising media or as evidence in the Court of Law without prior written consent of Laboratory.
- 4) Test results reported are valid at the time of testing
- 5) This is a system generated test report and hence does not require signature.

Reviewed and Authorized by:

AGARWALLA PRIYANKA(31960370)