

Liquid Crystal Measurements Notes

Wedge Cell Measurements

(Mostly Aronzon Thesis)

α

Put the empty wedge cell on the track, shine laser on it. Put a sheet of paper next to the laser. The distance between the reflected dot and the laser is l . The distance between cell and laser is L . Then the angle the top of wedge cell makes is α and satisfies

$$\tan(2\alpha) = \frac{l}{L}. \quad (1)$$

n

Put a card at the far end of the track, shine laser through the empty wedge cell, mark the dot on the card. Fill the wedge cell with sample, shine laser through it, the displacement of the dot is, say Δl . Then we have

$$\tan \delta = \frac{\Delta l}{L}. \quad (2)$$

And

$$n = \frac{\sin(\frac{\alpha+\delta}{2})}{\sin(\frac{\alpha}{2})} \quad (3)$$

Index Determination

Index of Water

As our target solution are mostly water, we should at first try to find the relationship between n_{water} and n_{sample} . We can analytically calculate the n_{water} by solving

$$\frac{n_{water}^2 - 1}{n_{water}^2 + 1} \left(\frac{1}{\bar{\rho}} \right) = a_0 + a_1 \bar{\rho} + a_2 \bar{T} + a_3 \bar{\lambda}^2 \bar{T} + \frac{a_4}{\bar{\lambda}} + \frac{a_5}{\bar{\lambda}^2 - \bar{\lambda}_{UV}^2} + \frac{a_6}{\bar{\lambda}^2 - \bar{\lambda}_{IR}^2} + a_7 \bar{\rho}^2, \quad (4)$$

where $\bar{T} = \frac{T}{T^*}$, $\bar{\rho} = \frac{\rho}{\rho^*}$, and $\bar{\lambda} = \frac{\lambda}{\lambda^*}$. (Type in exactly what these quantities are later)

$n_{iso}, n_{\perp}, n_{\parallel}$

From the property

$$n_{iso} = \frac{n_{\parallel} + 2n_{\perp}}{3} \quad (5)$$

and $n_{\parallel} - n_{\perp} = \Delta n$, we may deduce

$$n_{\parallel} = n_{iso} + \frac{2}{3} \Delta n \quad (6)$$

$$n_{\perp} = n_{\text{iso}} - \frac{1}{3}\Delta n \quad (7)$$

Calculating n at various temperature and wavelength

We have learned that from data given in Nastishi05, typically, $(n_{\text{iso}} - n_{\text{water}} \approx 0.03)$. Therefore, what is left for us to do is to figure out how Δn varies with temperature and wavelength. The wavelength dependence is given in Nastishi05, for 15% and 17%. What we did is just interpolated a line for 16%. This gives Δn for various wavelength at 20°C . The temperature dependence is generally given by the rule

$$\Delta n = \Delta n_0 \left(1 - \frac{T}{T^*}\right)^{\gamma} \quad (8)$$

where Δn_0 , T^* , and γ are fit parameters. We acquired a fit for the function, and get

$$\Delta n_0 = -0.022$$

, $T^* = 31.75^{\circ}\text{C}$, and $\gamma = 0.082$. To account for the difference in transition temperature between our sample and used in the paper, we modified the equation to be (for $\lambda = 633 \text{ nm}$):

$$\Delta n = \Delta n_{20^{\circ}\text{C}} \left(1 - \frac{T - 1.3}{T^*}\right)^{\gamma} \quad (9)$$

to account for difference between transition temperature and plugged in exact value for $\Delta n_0 = \Delta n_{20^{\circ}\text{C}}$ found in Nastishin05.

Then, with the assumption that

$$\frac{\Delta n_{\lambda, 20^{\circ}\text{C}}}{\Delta n_{\lambda, t}} = \frac{\Delta n_{633\text{nm}, 20^{\circ}\text{C}}}{\Delta n_{633\text{nm}, t}} \quad (10)$$

We can use 9 to find $\Delta n_{633\text{nm}, t}$, and with these, we are able to find n_{\perp} and n_{\parallel} for all wavelength and all temperatures.

Measurement Protocol

The detailed description of how to use the microscope.

1. No sample, set on parallel polarizers.
Post Processing \leftarrow Shading Correction \leftarrow Define.
2. Add disred filter, parallel polarizer. Add water sample. Adjust exposure time and power to make desired curve fill up the spectrum.
3. Measure I_{\perp}^w and I_{\parallel}^w . Also put a blocker under the microscope to measure I_{\perp}^0 and I_{\parallel}^0 .
4. Switch to sample. Set sample to desired temperature. Wait 2 minutes after temperature control hovers the desired limit. Be sure to selected the the region that is darkest with crossed polarizer. Measure I_{\perp}^s and I_{\parallel}^s and I_{\perp}^0 and I_{\parallel}^0 .
5. After traversing all temperature, switch back to water and do the same measurement to make sure isotropicity is not violated.
6. At high temperature (isotropic phase for samples), make measurement for sample again.

Empirically, a longer exposure time helps with averaging intensity. The absorption at each temperature is

$$A_{\parallel} = \log_{10} \frac{I_{\parallel}^w - I_{\parallel}^0}{I_{\parallel}^s - I_{\parallel}^0}, \quad (11)$$

and

$$A_{\perp} = \log_{10} \frac{I_{\perp}^w - I_{\perp}^0}{I_{\perp}^s - I_{\perp}^0}, \quad (12)$$

Calculate S

Finally, we may calculate the order parameter

$$S = \frac{n_{\parallel} A_{\parallel} - n_{\perp} A_{\perp}}{n_{\parallel} A_{\parallel} + 2n_{\perp} A_{\perp}} \quad (13)$$