Sealing Solutions

COMPOUND DATA SHEET
FM27/0 Grey

General description
FM27/0 is a styrene butadiene compound. Conventionally cured, free from MBT.

Identification as per Ph.Eur. 3.2.9., method A
A typical ATR-FTIR spectrum of a clean, cut surface of FM27/0 is enclosed on page 2.

Physical properties

Hardness *ISO 7619-1(1sec Indentation)*	**51 ± 5 °Shore A**
Density *ISO 2781*	**1.290 ± 0.025 g/cm³**
Ash content *Internal method. Calc.4h@700°C*	**43.7 ± 2.0 %**
Compression set *ISO 815, (typical value)*	**21 %**
Modulus 100 *Internal method. 100mm/min,ISO 37 Dumb-bell 2, (typical value)*	**2.2 N/mm²**
Modulus 300 *Internal method. 100mm/min,ISO 37 Dumb-bell 2, (typical value)*	**6.0 N/mm²**
Elongation @ Break *Internal method. 200mm/min, ISO 37 Dumb-bell 2, (typical value)*	**360 %**
Tensile Strength *Internal method. 200mm/min, ISO 37 Dumb-bell 2, (typical value)*	**9 N/mm²**
Water Vapor Transmission Rate *Mocon, 38°C,100%RH, 1.2 mm thickness, (typical valu e)*	**3.9 g/m².24h**
Oxygen Transmission Rate *Mocon, 38°C, 50%RH, 100% O2, 1.2 mm thickness, (typ ical value)*	**971 cc/m².24h**

Compound ingredient declarations

Latex FM27/0 may contain natural rubber latex which may cause allergic reactions in latex sensitive individuals.

Nitrosamines FM27/0 is not made with chemicals that are associated with nitrosamine formation as per the ASTM F1313-90 list.

Phthalates FM27/0 is not made using Di(2-EthylHexyl) Phthalate (DEHP) or other phthalates.

BSE/TSE For the raw materials of FM27/0, certification confirming that such products are either of vegetable origin or are manufactured in severe process conditions for inactivation of prions as described in the EMA/410/01-rev.3 and in the European Pharmacopoeia 5.2.8. "Minimizing the risk of transmitting Animal Spongiform Encephalopathy Agents" is available.

MBT FM27/0 is not made with 2-mercapto-benzothiazole (MCBT, also named MBT), or any of its derivatives.

Heavy Metals FM27/0 fulfills the EC Guideline 94/62/EC for heavy metals in packaging materials and the CONEG regulation on reduction of toxics in Packaging Law: "packaging components shall not contain more than 100 ppm of Pb, Cd, Hg, and Cr(VI)".

Biocompatibility
FM27/0 is non-cytotoxic and meets the requirements of the Elution Test as described in General Chapter <87>,"Biological Reactivity Tests, in vitro" of the USP. A typical USP<87> Elution Test certificate is enclosed on page 3.

Chemical properties
FM27/0 meets the chemical requirements for Type I closures specified in Ph.Eur. 3.2.9 and in USP <381>.
Typical results are given in the table below.
A typical UV spectrum is enclosed on page 2.

Characteristic		***Limits***		***FM27/0***
Appearance of solution	*Turbidity*	*Type I: 6 NTU (*)* *Type II: 18 NTU (*)*		***2***
	Color	*Solution S is not more intensely colored than reference*		***Pass***
Acidity or alkalinity (NA : Not applicable)		*0.8 ml 0.01M HCl*	*EP*	***NA***
			USP°	***NA***
		0.3 ml 0.01M NaOH	*EP*	***0.0***
			USP°	***0.0***
UV Absorbance (max 220-360 nm)		*Type I: 0.2* *Type II: 4.0*		***0.1***
Reducing substances		*Type I: 3.0 ml 0.01M* $Na_2S_2O_3$ *Type II: 7.0 ml 0.01M* $Na_2S_2O_3$		***0.9***
Extractable heavy metals		*2 ppm* Pb^{2+}	*EP*	***Pass***
			USP	***Pass***
Extractable zinc		*5.0 ppm* Zn^{2+}		***0.5***
Ammonium		*2 ppm* NH_4^+		***Pass***
Residue on evaporation (only for EP)		*Type I: 2.0 mg* *Type II: 4.0 mg*		***0.2***
Volatile sulphides		*Any black stain on the paper is not more intense than that produced by a control solution*		***Pass***

(*) By definition corresponding with reference suspensions II and III (for Ph.Eur.) or B and C (for USP) respectively
(°) corrected with blank
Note : Chemical testing is performed on non-post-treated standard test plates or products, prepared using representative process conditions.

Note : "FMxxx" refers to the type of compound, the extension "/x" refers to the color of the said compound. Differently colored compounds might be used for testing throughout this document. It is generally accepted that the color is irrelevant for the properties discussed, except Ash content and Density which are different per color.

Team Leader R&D lab	Senior Manager Material Development	Manager Global Quality & Regulatory Affairs
Date : 27 mar 2014	Date : 27 Mar 2014	Date : March 27, 2014

Datwyler Pharma Packaging International NV, Industrieterrein Kolmen 1519, BE-3570 Alken, Belgium
T +32 11 590 811, F +32 11 314 086, pharma@datwyler.com, www.datwyler.com

COMPOUND DATA SHEET
FM27/0 Grey

Typical ATR-FTIR spectrum of a clean, cut surface of FM27/0:



Typical UV spectrum of the Solution S extract of FM27/0, measured as per the USP <381> / Ph.Eur. 3.2.9.:



Datwyler Pharma Packaging International NV, Industrieterrein Kolmen 1519, BE-3570 Alken, Belgium
T +32 11 590 811, F +32 11 314 086, pharma@datwyler.com, www.datwyler.com

COMPOUND DATA SHEET
FM27/0 Grey

USP<87> Elution Test certificate for FM27/0:

TOXIKON
Leaders in Life Science and Technology

TEST RESULT CERTIFICATE

Project Number:	**TE 08211**	**Study Number:**	**08-B0508-N1**
Sponsor:	**Helvoet Pharma Belgium NV**	**Report Date:**	**20/03/2008**
Contact:	*Mrs. Nadia Nouri*		
Address:	Industrieterrein Kolmen 1519 B-3570 Alken Belgium		
		Technical Initiation:	17/03/2008
PO.Number:	PB0800805	Technical Completion:	20/03/2008

Study	**Elution Test - ISO**	Temp/Time	37°C/24 hours
Test Item	P8568A FM27 ISAFNS ½" domed Not treated	Ratio	25 cm²/20 mL
Lot	Ch751915	Vehicle	MEM-Complete

REFERENCE: Based on "ISO 10993-5, 1999: Biological Evaluation of Medical Devices- Part 5:Tests for In Vitro Cytotoxicity." and "USP 30-NF 25, 2007: <87> Biological reactivity test, in vitro." Toxikon Reference: SOP 3.1.2.3, rev. 05

PROCEDURE: The biological reactivity of a mammalian monolayer, L929 mouse fibroblast cell culture, in response to the test item extract was determined. Extracts were prepared at 37±1°C for 24 hours in a humidified atmosphere containing 5±1% carbon dioxide (static). Positive (natural rubber) and negative (silicone) control articles were prepared to verify the proper functioning of the test system. The maintenance medium on the cell cultures is replaced by the extracts of the test item or control article in triplicate and the cultures are subsequently incubated for 48 hours, at 37±1°C, in a humidified atmosphere containing 5±1% carbon dioxide. Biological reactivity was rated on the following scale: Grade 0 (No reactivity); Grade 1 (Slight reactivity), Grade 2 (Mild reactivity), Grade 3 (Moderate reactivity) and Grade 4 (Severe reactivity). The test item is considered non-cytotoxic if none of the cultures exposed to the test item shows greater than mild reactivity (Grade 2).

RESULTS: No reactivity (Grade 0) was exhibited by the cell cultures exposed to the test item at the 48 hours observation. Severe reactivity (Grade 4) was observed for the positive control article. The negative control article showed no signs of reactivity (Grade 0).

CONCLUSION: Based on the evaluation criteria mentioned above, the test item is considered non-cytotoxic.

RECORD STORAGE: All raw data generated in this study will be archived at Toxikon Europe, according to SOP 4.2.8.

AUTHORIZED PERSONNEL

FOR: ir. Peter Cornelis
Study Director

Vanessa Ruymen
Quality Assurance

Toxikon Europe nv - Romeinsestraat 12 - B - 3001 Leuven - Belgium - Tel. 32-16-40 04 84 - Fax 32-16-40 13 04 - www.toxikon.com
Fortis 230-0391575-06 - KBC 431-0597001-33 - BTW/TVA BE 0442.395.719 - H.R. Leuven 80.154

Datwyler Pharma Packaging International NV, Industrieterrein Kolmen 1519, BE-3570 Alken, Belgium
T +32 11 590 811, F +32 11 314 086, pharma@datwyler.com, www.datwyler.com