

Compound Data Sheet

FM457/0
Grey

General description

Bromobutyl compound, unconventionally cured. Latex free and free from MBT.

Extremely low extractables level.

Application range: universal; especially suitable for WFI applications.

Physical properties

	Unit	Method	Target	Range
Hardness	°Shore A	ISO 7619-1 (1 sec. Indentation) Avg of 3 measurements	47	± 5
Density	g/cm ³	ISO 2781	1.265	± 0.025
Ash	%	Internal Method(s): Calc. 4h @ 700° C	41.0	± 2.0
Compression Set	%	ISO 815	30	max.
Tensile Strength	N/mm ²	ISO 37	4	min.

Chemical properties

FM457(**) meets the chemical requirements for Type I Closures specified in General Chapter 3.2.9. of the European Pharmacopoeia and specified in General Chapter <381> of the United States Pharmacopoeia.

Typical USP <381> / EP 3.2.9. data for FM457(**) are presented in the table on page 2.

A typical UV spectrum of the USP <381> / EP 3.2.9. extract of FM457(**) is presented in the figure on page 3.

Biological properties

FM457(**) is non-cytotoxic and meets the requirements of the Elution Test as described in General Chapter <87> of the United States Pharmacopoeia.

A typical USP <87> Elution Test Certificate is enclosed on page 4.

Pyrolysate

An infrared spectrum of the pyrolysate of FM457(**) is enclosed on page 5.

Compound statement


A statement about compound FM457(**) in respect to natural rubber latex, nitrosamines, MCBT, Heavy metals, TSE/BSE and GMO is enclosed on page 6.

(**) Note: FM457 refers to the type of compound, the extension "/0", "/1", ... refers to the colour of the said compound.

Differently coloured compounds might be used for testing throughout this document. It is generally accepted that the colour is irrelevant for the properties discussed in this document.

Prepared by:  R&D Laboratory

Date: 11 Oct 2010

Reviewed by:  Material Development

Date: 12 Oct 2010

Approved by:  Quality Assurance

Date: 14 Oct 2010


Typical USP <381> / EP 3.2.9. chemical properties of FM457()**

Characteristic		Amount tested	Units	Limit	Typical Values	
<i>Appearance of solution</i>	<i>Turbidity</i>	Sol. S	NTU	Type I: ≤ 6.0 (*)		0.1
	<i>Colour</i>	Sol. S		See test procedure		pass
<i>Acidity or alkalinity</i>		Sol. S (20 ml)	ml 0.01M HCl ml 0.01M NaOH	≤ 0.8 ≤ 0.3	<u>Blank</u>	
					0.06	0.06
					EP	0.06
					USP	0.00
<i>Absorbance</i>		Sol. S	A_{\max} 220-360nm	Type I: ≤ 0.2		0.01
<i>Reducing substances</i>		Sol. S (20 ml)	ml 0.002M KMnO ₄	Type I: ≤ 3.0		0.2
<i>Extractable heavy metals</i>		Sol. S	ppm Pb	≤ 2	EP USP	<2 <2
<i>Extractable zinc</i>		Sol. S	ppm Zn	≤ 5.0		<0.01
<i>Ammonium</i>		Sol. S	ppm NH ₄	≤ 2		<2
<i>Residue on evaporation (only for EP)</i>		Sol. S (50 ml)	mg	Type I: ≤ 2.0		0.2
<i>Volatile sulphides</i>		20 cm ²	mg S	≤ 0.02		<0.02

(*) By definition corresponding with reference suspension II.

(**) Note: FM457 refers to the type of compound, the extension "0", "1", ... refers to the colour of the said compound. Differently coloured compounds might be used for testing throughout this document. It is generally accepted that the colour is irrelevant for the properties discussed in this document.

Typical UV-spectrum of USP <381> / EP 3.2.9. extract of FM457()**



(**) Note: FM457 refers to the type of compound, the extension "/0", "/1", ... refers to the colour of the said compound. Differently coloured compounds might be used for testing throughout this document. It is generally accepted that the colour is irrelevant for the properties discussed in this document.

Typical USP <87> Elution Test Certificate of FM457(**)

TOXIKON

► Leaders in Life Science and Technology

TEST RESULT REPORT N°10-B1030-N1



Project Number:	TE 10445	Study Number:	10-B1030-N1
Sponsor:	Helvoet Pharma Belgium NV	Report Date:	20/05/2010
Contact:	Mrs. Nadia Nouri	Date Sample Arrival:	12/05/2010
Address:	Industrieterrein Kolmen 1519	Technical Initiation:	17/05/2010
	3570 Alken, Belgium	Technical Completion:	20/05/2010
PO.Number:	PB1001706		

Study	Elution Test - ISO	Temp/Time	37°C/24 hours
Test Item	V9341 FM457/0 0 kGy Gamma t=24m	Ratio	25cm ² /20mL
Lot	Ch808934	Vehicle	MEM-Complete

REFERENCE: According to "ISO 10993-5, 2009: Biological Evaluation of Medical Devices- Part 5: Tests for In Vitro Cytotoxicity," and "USP 32-NF 27, 2009: <87> Biological reactivity test, in vitro." Toxikon Reference: SOP 3.1.2.3, rev. 08

PROCEDURE: The biological reactivity of a mammalian monolayer, L929 mouse fibroblast cell culture, in response to the test item extract was determined. The samples and control articles were autoclaved prior to the preparation of the extracts. Extracts were prepared at 37±1°C for 24 hours in a humidified atmosphere containing 5±1% carbon dioxide (static). Positive (natural rubber) and negative (silicone) control articles were prepared to verify the proper functioning of the test system. The maintenance medium on the cell cultures is replaced by the extracts of the test item or control article in triplicate and the cultures are subsequently incubated for 48 hours, at 37±1°C, in a humidified atmosphere containing 5±1% carbon dioxide. Biological reactivity was rated on the following scale: Grade 0 (No reactivity); Grade 1 (Slight reactivity), Grade 2 (Mild reactivity), Grade 3 (Moderate reactivity) and Grade 4 (Severe reactivity). The test item is considered non-cytotoxic if none of the cultures exposed to the test item shows greater than mild reactivity (Grade 2).

RESULTS: No reactivity (Grade 0) was exhibited by the cell cultures exposed to the test item at the 48 hours observation. Severe reactivity (Grade 4) was observed for the positive control article. The negative control article showed no signs of reactivity (Grade 0).

OPINION AND INTERPRETATION: Based on the evaluation criteria mentioned above, the test item is considered non-cytotoxic.

RECORD STORAGE: All raw data generated in this study will be archived at Toxikon Europe, according to SOP 4.2.8.

AUTHORIZED PERSONNEL



ir. Peter Cornelis
Study Director




Vanessa Ruymen
Quality Assurance

The test results on the enclosed report are only referring to the tested articles. Partly reproduction of this report can only be allowed after written permission of Toxikon. Toxikon guarantees that all results are acquired by testing according to officially accepted scientific methodology.

Toxikon Europe nv - Researchpark Haasrode 1724 - Romeinsestraat 12, B 3001 Leuven, Belgium - Tel. 32-16-40 04 84 - Fax 32-16-40 13 04
Fortis 230-0391575-06 - KBC 431-0597001-33 - BTW/TVA BE 0442.395.719 - H.R. Leuven 80.154 - www.toxikon.be

(**) Note: FM457 refers to the type of compound, the extension "/0", "/1", ... refers to the colour of the said compound. Differently coloured compounds might be used for testing throughout this document. It is generally accepted that the colour is irrelevant for the properties discussed in this document.

Typical infrared spectrum of a pyrolysate (4000-600 cm⁻¹) of FM457()**



(**) Note: FM457 refers to the type of compound, the extension "/0", "/1", ... refers to the colour of the said compound. Differently coloured compounds might be used for testing throughout this document. It is generally accepted that the colour is irrelevant for the properties discussed in this document.

Compound statement for FM457()**

Natural rubber latex

Compound FM457(**) is free from natural rubber and natural rubber latex.

Nitrosamines

Compound FM457(**) does not use rubber chemicals that are associated with hazardous nitrosamines formation.

MCBT

Compound FM457(**) does not contain 2-mercaptobenzothiazole (MCBT, also named MBT), or any of its derivatives.

Heavy Metals

- Compound FM457(**) fulfils the European Community Guideline 94/62/EC for heavy metals in packaging materials.
- Compound FM457(**) fulfils the CONEG regulation on reduction of toxics in Packaging Law.

Both directives state that packaging components should not contain more than 100 ppm of Lead (Pb), Cadmium (Cd), Mercury (Hg) and Hexavalent Chromium (VI) (Cr). Where the regulated metals are present at levels below the values stated above, they were not intentionally added during the manufacturing process.

TSE/BSE

Compound FM457(**) does not contain material of animal origin and hence is not associated with TSE/BSE risks.

(TSE = Transmissible Spongiform Encephalopathy; BSE = Bovine Spongiform Encephalopathy)

GMO

Compound FM457(**) does not contain ingredients made from GMO's (Genetically Modified Organisms).

(**) Note: FM457 refers to the type of compound, the extension "/0", "/1", ... refers to the colour of the said compound. Differently coloured compounds might be used for testing throughout this document. It is generally accepted that the colour is irrelevant for the properties discussed in this document.