

# GAYATRISHAKTI PAPER & BOARDS LIMITED



## PRODUCT SPECIFICATION SHEET

### **COATED PACKAGING BOARD (GREY BACK)**

#### **APPLICATION / FEATURES**

- 1. Pharmaceutical cartons
- 2. Advertising Pamplets.
- 3. High Value Consumer Packaging.
- 4. Book Covers.
- 5. Suitable for offset and gravure printing
- 6. Product approved as per CFTRI
- 7. Free from flavor and odour
- 8. Low level of heavy metals contents.
- 9. No detectable levels of Dixons

#### **BOARD CONSTRUCTION**

Top Coat with blade - 10 (+/-1) g / m2

Pre Coat -10 (+/-1) g/m2

Surface Sized / Starch Coat

Top Layer - Selected Recycled white Pulp

Under layer / Recycled Bleached waste paper

Filler Layer - Recycled Grey Pulp

Back Layer - Selected Recycled Grey Pulp

Surface Sized / Starch Coat

SUBSTANCE	BULK	CALIPER	TABER STIFFNESS		PARAMETER	UNITEDS	VALUE
(g/m2)	(cc/gms)	(microns)	gm-cm		PARAMETER	UNITEDS	VALUE
			MD	CD	COBB (TOP)	g/m2	30-40
200	1.2	240	35	16			
230	1.2	276	50	23	COBB (BOTTOM)	g/m2	35-50
250	1.21	302	60	28			
260	1.21	314	65	30	BRIGHTNESS	%	78(+/-1)
285	1.24	353	90	40			
300	1.24	372	105	48	GLOSS	%	40(+/-5)
310	1.25	388	120	55			
320	1.25	400	130	58	P.P.S.	microns	<3.0
330	1.25	412	140	65			
350	1.25	437	160	70	I.G.T	mts/sec.	>0.7
360	1.25	450	180	80			
380	1.25	475	205	90	PLY BOND	ft.ib in thousand	>65
400	1.26	504	230	105			
420	1.26	529	260	120	BRUST FACTOR		>16
450	1.26	567	310	140			
(+/-3%)	(+/-5%)	(+/-5%)	(+/-10%)		SOAT	sec.	250

Moisture Content: 7 +/-1%

#### Note:

- 1. Tolerances are based upon 95% confidence limit on single mill measurements of random samples.
- 2. Specifications are subject to changes without any prior notice.