Turbo Codes for Deep Space Communications: CCSDS 131.0-B-2 standard implementation

Final project for the Channel Coding course

Gianluca Marcon
gianluca.marcon.1@studenti.unipd.it
University of Padova
April 1, 2017

DEPARTMENT OF INFORMATION ENGINEERING
UNIVERSITY OF PADOVA

Electro-optic modulators

Convert electronic signal to high bit-rate optical signal.

Desired features:

- high switching speed
- high bandwidth
- small footprint (*Nanoscale...*)
- compatibility with on-chip electronic components
- low insertion loss
- energy efficiency

Graphene: why?



- Flexible
- Robust
- Small footprint
- Great thermal characteristics
- High electron mobility
- **Voltage-dependent optical conductivity**

Great for high speed optical modulators!

However...

...small dimensions of graphene can be a problem:

- operating wavelength (1550 nm) is huge in comparison
- need to enhance interaction with light
- new waveguide designs must be studied





[Xu et al., 2004, Sun et al., 2007]

Light-graphene interaction

Two different phenomena:

- **Interband absorption:** photon get absorbed and electron moves to conduction band
- **Intraband absorption:** photon get absorbed and electron stays in same band but in a higher level

Conductivity

$$\begin{aligned}\sigma_g &= \sigma_{inter}(\omega, \mu_c, T) + \sigma_{intra}(\omega, \mu_c, T) \\ &\simeq \sigma_{inter}(\omega, \mu_c, T) \qquad \text{when } \mu_c < \hbar\omega/2\end{aligned}$$

Conductivity of graphene



First type of modulator



[Cho et al., 2011]

Large footprint required to obtain adequate modulation depth

Novel design: slot waveguides





$\lambda = 1550$ nm, $n_{co} = 1.46$, $n_{cl} = 3.48$, $w_{co} = 101$ nm. [Xu et al., 2004]

Absorbed power per unit area

$$P \propto \frac{1}{2}|\mathbf{E}| \cdot \frac{Im\{\varepsilon_{eff}\}}{|\varepsilon_{eff}|}$$

Wavelength and Voltage dependency



Bandwidth > 1.25 THz



$\Delta V = 1.32\,V$

Plasmonic-graphene waveguide modulator



Cu is preferred (CMOS compatible), but has higher losses than Au, Ag.

Plasmonic-graphene waveguide modulator

200 nm wide, silicone nitride 10 nm thick (both layers), length 120 nm.



Footprint $\sim 2 - 3\ \mu m^2$

Wavelength and Voltage dependency





Bandwidth > 1 THz

$\Delta V = 1.38\,V$

Energy consumption ∼ 0.12-0.13 pJ/bit

Did we meet any requirement?

- high bandwidth Yes
- energy efficiency Yes
- compatibility with on-chip electronic components Yes
- low insertion loss Yes
- small footprint Kinda
- high switching speed Potentially

Recent advances: graphene-on-silicon MZI

- Fix one arm in ”dielectric state” (low loss) of graphene
- Exploit changes in $Re\{\varepsilon_{eff}\}$ wrt gate voltage to induce phase change



[Phatak et al., 2016]

References I

Cho, S., Yoon, M. C., Kim, K. S., Kim, P., Kim, D., Ulin-avila, E., and Zentgraf, T. (2011).
A graphene-based broadband optical modulator.
Nat. (UK), 474(7349):64–6767.

Phatak, A., Cheng, Z., Qin, C., and Goda, K. (2016).
Design of electro-optic modulators based on graphene-on-silicon slot waveguides.
Optics Letters, 41(11):2501.

References II

Sun, R., Dong, P., Feng, N.-n., Hong, C.-y., Michel, J., Lipson, M., and Kimerling, L. (2007).
Horizontal single and multiple slot waveguides: optical transmission at lambda = 1550 nm.
Optics express, 15(26):17967–17972.

Xu, Q., Almeida, V. R., Panepucci, R. R., and Lipson, M. (2004).
Experimental demonstration of guiding and confining light in nanometer-size low-refractive-index material.
Optics letters, 29(14):1626–1628.

Thank you!