

Calcium Silicate Corporation  
Columbia, TN

WASHED PHOSPHATE ORE  
OMRI Listed as Tennessee Brown Rock  
for use in Organic Production

Quantity Available: Approximately 220,000 Tons

TYPICAL ANALYSIS:

Moisture: 15.0%

<u>Chemical Analysis (Dry Base):</u>	<u>Typical</u>	<u>Range</u>
P <sub>2</sub> O <sub>5</sub>	22.7%	21.0 - 25.0%
P <sub>2</sub> O <sub>5</sub> , Available	5.0%	4.0 - 7.0%
Fe <sub>2</sub> O <sub>3</sub>	3.5%	3.5 - 4.5%
CaO	39.9%	37.0 - 41.0%
SiO <sub>2</sub>	22.0%	20.0 - 24.0%

<u>Dry Screening:</u>	97%	- 4 Mesh
	78%	- 16 Mesh
	31%	- 50 Mesh
	13%	- 100 Mesh
	3%	- 200 Mesh
	1%	- 325 Mesh

For additional information contact: Mark C. Elizer  
Phone: 863-902-0217  
Fax: 863-902-0107

Last revised: September 2003  
January 2006