



Customer / Kunde
Plastic Processor SE

Plastik Street 1
1230 Wien, AT
s1seven.certificates@gmail.com

**Certificate recipient /
Zertifikatsempfänger**

Plastic Processor SE
Plastik Street 1
Werk 1
1230 Wien, AT
s1seven.certificates@gmail.com

Green Plastics AG

Kunststoffgasse 1
10003 Berlin, DE
s1seven.certificates@gmail.com

Goods recipient / Warenempfänger

Plastic Processor SE
Plastik Street 1
Werk 1
1230 Wien, AT
s1seven.certificates@gmail.com

Certificate / Zertifikat EN 10204:2004 3.1

<i>Certificate ID / Zertifikatsnummer</i>	43	<i>Date / Datum</i>	2021-12-12
---	----	---------------------	------------

Business data / Geschäftsdaten

Order / Bestellung		Delivery / Lieferung	
<i>ID / Nummer</i>	1000/12/12/2021	<i>ID / Nummer</i>	3000/20
<i>Item no. / Position</i>	000010	<i>Item no. / Position</i>	1
<i>Quantity / Menge</i>	100 kg	<i>Quantity / Menge</i>	90 kg
<i>Date / Datum</i>	2021-12-01	<i>Date / Datum</i>	2021-12-13
<i>Product ID / Produktnummer</i>	10011	<i>Order ID / Auftragsnummer</i>	3384048234
<i>Product name / Produktname</i>	Plastic	<i>Order item no. / Auftragsposition</i>	000020
<i>Goods receipt ID / Wareneingangnummer</i>	1000_10_10	<i>Transport</i>	W345678

Product / Produkt

<i>Product ID / Produktnummer</i>	20000 01
<i>Product designation</i>	Manufactured Product Name
<i>Country of origin / Herkunftsland</i>	DE
<i>Place of origin / Herkunftsort</i>	Berlin
<i>Filling batch ID / Abfüllcharge</i>	210000
<i>Filling batch date / Abfülldatum</i>	2021-12-12
<i>Production batch ID / Produktionscharge</i>	100001
<i>Production date / Produktionsdatum</i>	2017-12-01
<i>Expiry date / Ablaufdatum</i>	2021-12-12
<i>Standards / Normen</i>	ASTM D-4066 PA0111, ASTM D-4066 PA0121
<i>Additional information / Zusätzliche Informationen</i>	Information 1, Information 2

Inspections / Prüfungen

<i>Lot ID / Prüflös</i>		123456789 10				
<i>Property / Eigenschaft</i>	<i>Method / Methode</i>	<i>Unit / Einheit</i>	<i>Value / Wert</i>	<i>Minimum</i>	<i>Maximum</i>	<i>Inspection conditions / Prüfbedingungen</i>
MFR	DIN EN ISO 1133	g/10m ₂	31	15	35	2,16 kg 190° Celsius
Density	DIN EN ISO 1183-1A	g/cm ³	85	85	89	

Additional information / Zusätzliche Informationen

Samples: tempered at 100°C for 20 hours

Declaration / Erklärung

This document is valid without signature.

Contact persons / Ansprechpartner

Name	Post / Rolle	Department / Abteilung	Email	Phone / Telefon
Josef Manager	Quality Manager	Factory Production Control	contact1@email.com	+31 6 12345678
Joe Inspector	Inspector	Factory Production Control	contact2@email.com	+31 6 12345678

Attachments / Anlagen

logo.png

Data schema maintained by [Material Identity](#) .

<https://schemas.s1seven.com/coa-schemas/v1.1.0/schema.json>