HOME COMPOSTABLE

60gsm Kraft Paper + 50µ Compostable Inner Film

TECHNICAL DATA SHEET

POUCH.ECO / ACHIEVE PACK

PRODUCT OVERVIEW

Product Name	60gsm Kraft Paper + 50µ Compostable Inner Film
Structure	Kraft paper + Compostable film
Total Thickness	0.13 mm (130 µm) nominal
Total Weight	130 g/m²
Composting Type	Home Compostable (ambient temperature)
Shelf Life	+12 months (dry goods)

BARRIER PROPERTIES

Property	Value	Test Standard	Conditions
WVTR (Water Vapor Transmission Rate)	**< 150 g/m²/day**	ASTM E96	38°C / 90% RH
OTR (Oxygen Transmission Rate)	**< 80 cc/m²/day**	ASTM D3985	23°C / 0% RH

CONSTRUCTION & MATERIAL DATA

Layer	Material	Basis Weight g/m²	Thickness mm	Thickness µm	Weight Share	Thickness Share
Outer	**Kraft Paper (uncoated)**	60	0.08	80	46.2%	61.5%
Inner	**Compostable Film (50µ, density 1.4)**	70	0.05	50	53.8%	38.5%
Total	**Laminated Structure**	**130**	**0.13 nominal**	**130**	**100%**	**100%**

** Kraft paper typical thickness range 70–85 µm; nominal 80 µm (0.08 mm) used as outer layer.*

** Compostable film 50 µm at density 1.4 g/cm³ gives approx. 70 g/m² basis weight.*

** Thickness share = layer thickness ÷ total thickness × 100% (Paper: 0.08 / 0.13 ≈ 61.5%, Film: 0.05 / 0.13 ≈ 38.5%)*

CERTIFICATIONS & STANDARDS

Certification	Standard	Scope
TUV OK Home Compost	TUV Austria AT cert.	Home composting at ambient temperature

EN 13432	European Standard	Industrial composting (packaging)
ASTM D6400	US Standard	Industrial composting (plastics)
FSC Certified Paper	Forest Stewardship Council	Responsibly sourced kraft (on request)

IDEAL APPLICATIONS

+ Bakery products & cookies	+ Dried herbs & spices	+ Farmers market products
+ Tea bags & loose leaf tea	+ Organic dry snacks	+ Artisan food brands
+ Pet treats (dry)	+ Granola & cereal	+ Eco-conscious retail packaging