

Factory Inspection Report for Multi-layer Composite Food Packaging Films and Bags

Sample Name: Customer Name:		Stand-up pouch zipper		Material composition:		MOPP-Double Electrification/Reinforced VMPET///Reinforced PE		Product Specifications:		300*340+75 mm		Sampling quantity:		315个	
Test Conditions:		25/50		Production Date:		2025/7/8		Production Batch Number : SC3340634				Delivery Quantity:		10500个	
Name of Inspection Item				Inspection Standard								Test Speed	Inspection Result	Conclusion	
Appearance		Printing		The finished products are clean, without obvious dirt, defects, knife marks, or scratches. The text printing is clear and complete, with smooth edges of the imprints. The mesh pattern is clear and uniform, without obvious deformation or damage. The overprinting is basically accurate, with almost no color difference between the same colors, and the black layer has a glossy finish.									Conform to	Qualified	
		Wrinkles		Minor wrinkles are allowed (for bags, minor wrinkles that do not penetrate the heat-sealed edges are permitted).									Conform to	Qualified	
		Contamination marks		No foreign objects, oil stains, or other contaminants are allowed. Slight unevenness in adhesive application or marks caused by pressure rollers are permitted.									Conform to	Qualified	
		Scratch、Scorch		No burns or holes in single-layer films are allowed, and no scratches are permitted.									Conform to	Qualified	
		Perforation、Bubble		No perforations or bubbles that affect usability are allowed.									Conform to	Qualified	
		Flatness of rolled film		The surface of the rolled film is flat, and the end face is basically neat.									Conform to	Qualified	
Dimensional deviation		Number of joints in rolled film		No more than 2 per kilometer; the joints must be firm, accurate, and marked.									Conform to	Qualified	
		Length deviation		As per the customer's needs (Film > 0, Bag seeQ/JHX01-2018)									Conform to	Qualified	
		Width deviation		As per the customer's needs (Film ±2mm, Bag seeQ/JHX01-2018)									Conform to	Qualified	
		Thickness deviation		As per the customer's needs (Tolerance ±10%)									Conform to	Qualified	
Physical and mechanical properties		Tensile strength		≥30								250	101.1	Qualified	
		Elongation at break		≥25								250	26.3	Qualified	
		Peel strength		≥0.2								250	Cannot be peeled off	Qualified	
		Heat-seal strength		≥7								300	63	Qualified	
Pressure resistance performance of the bag				No penetration, no rupture.								6h	Conform to	Qualified	
Drop performance of the bag				No penetration, no rupture.								/	Conform to	Qualified	

Conclusion: This batch of products has passed the inspection and is approved for delivery.

'Signature of the analyst: Lin Fang

'Signature of the factory director: Wu Xiongwei

