ArcelorMittal

Granite® HDX

guarantee 35 years
free of chromates and heavy metals

Properties	• Very good UV resistance • Excellent corrosion resistance • Very good formability • Robust coating • Thermosetting paint • Surface treatment and paint: free of hexavalent chromium and heavy metals	
Applications	**External uses in severe environments: profiles, sandwich panels for roofing and cladding, building materials (tiles etc). Internal uses in aggressive indoor environments (swimming pools, industrial buildings etc)**	
Description	Thickness (1)	55 microns
	Composition	Front: 25 microns primer + 30 microns top coat Back: 10 or 12 microns backing coat recommended 25 microns backing coat also available Double-side finish available
	Gloss (Gardner 60°) (1)	30 GU Other gloss levels on request
	Colours	Colour palette Other colours on request
	Appearance	Grained
	Temporary protection (optional)	Not applicable
Performance	Adhesion of the coating (T-bend)	≤ 1 T
	Resistance to cracking on bending (T-bend)	≤ 1.5 T
	Impact resistance	18 J
	Clemen scratch resistance	≥ 3 kg
	Corrosion resistance: • Salt spray test • Corrosion resistance category	 700 hours RC5+ for colour categories 1 to 4, RC5 for colour category 5
	Condensation resistance: • QCT test • Corrosion protection (interior) category	 1500 hours CPI4
	UV resistance: • QUV (UVA + H_2O) test (2000 hours) • UV resistance category	 ΔE ≤ 2; GR ≥ 80% RUV4
	Fire behaviour classification (EN 13501-1)	A1
	Resistance to acids and bases	Good to very good
	Resistance to solvents: • Aliphatics and alcohols • Ketones • Aromatics	 Very good Low Good to very good
	Resistance to mineral oils	Very good
	Maximum continuous operating temperature	100°C
Automatic guarantee	• Non-perforation of the sheet metal • Non-delamination of the paint • Aesthetic appearance (ΔE ≤ 3; Gloss retention ≥ 80%)	≤ 35 years, depending on the external environment ≤ 35 years, depending on the external environment ≤ 5 years, depending on the geographic location and the paint colour category
Remarks	These performance characteristics refer specifically to metallic coating Z225 (guaranteed minimum). If any product (film, oil, foam, glue, paint etc) is to be applied after coil delivery, compatibility with the coating needs to be checked first. Although we take great care to reproduce the same aesthetic aspect on each coil, ArcelorMittal cannot guarantee the visual consistency from one single order item to another. Consequently, you need to consider placing one single order for one building; standard samples can only serve as a guide.	

(1) Nominal value, tolerance according to EN 10169