

Escala	Material	Tipo test	IFSS	Referencia paper
Micro	CF-Epoxy	SFFT (single-fibre fragmentation)	23.8±6.6 / 47.3±15.4	[15]
Micro	AS4 CF-Epoxy	SFFT (single-fibre fragmentation)	68.3	[145]
Micro	PAN-based T50 CF-Epoxy	SFFT (single-fibre fragmentation)	40±1	[71]
Micro	AS4 CF-Epoxy	SFFT (single-fibre fragmentation)	-	[146]
Micro	AS4 CF-Epoxy	SFFT (single-fibre fragmentation)	-	[81]
Micro	AS4 CF-Epoxy	SFFT (single-fibre fragmentation)	48	[147]
Micro	IM6G CF-Epoxy	SFFT (single-fibre fragmentation)	58	[147]
Micro	HMS4 CF-Epoxy	SFFT (single-fibre fragmentation)	40	[147]
Micro	HMS CF-Epoxy	SFFT (single-fibre fragmentation)	36±6	[148]
Micro	IMD CF-Epoxy	SFFT (single-fibre fragmentation)	66±15	[148]
Micro	CF-Epoxy	SFFT (single-fibre fragmentation)	30.1±0.9 / 41.9±7.2	[149]
Micro	Unsize CF-Epoxy	SFFT (single-fibre fragmentation)	25.9±0.9 / 36.8±6.5	[149]
Micro	T300 CF-Epoxy	SFFT (single-fibre fragmentation)	56.1 / 54.3	[150]
Micro	T700 CF-Epoxy	SFFT (single-fibre fragmentation)	39.9 / 41.9	[150]
Micro	T1000 CF-Epoxy	SFFT (single-fibre fragmentation)	42.1 / 45.2	[150]
Micro	T300 CF-Epoxy (FEM)	SFFT (single-fibre fragmentation)	60–75 / 100 / 125	[38]
Micro	T700S CF-Epoxy	SFFT (single-fibre fragmentation)	18.7	[]
Micro	CF-Epoxy	Single-fibre pull-out	64.6±8.2 / 84.1±19.4	[15]
Micro	AS4–DGEBA Epoxy	Single-fibre pull-out	61±2 / 88±5	[174]
Micro	AS2–EPON 815	Single-fibre pull-out	48±4	[174]
Micro	T300–Epoxy	Single-fibre pull-out	43.7±4.8	[231]
Micro	T700SC–Epoxy	Single-fibre pull-out	36.3±4.3	[231]
Micro	HMS40–Epoxy	Single-fibre pull-out	41±2	[188]
Micro	CF-Epoxy	Single-fibre pull-out	72.7	[??]
Micro	CF-Epoxy	Microbond	48.3±14.1 / 69.7±19.7	[15]
Micro	Celion CF-Epoxy	Microbond	57	[238]
Micro	AS4 CF-Epoxy (quasi-disk)	Microbond	20±1.65	[256,273]
Micro	AS4 CF-Epoxy (droplet)	Microbond	33.7±8.93	[256,273]
Micro	AS4 CF-Epoxy	Microbond	35.7–54.7	[265]
Micro	AS4 CF-Epoxy	Microbond	50.3	[250]
Micro	AU4 CF-Epoxy	Microbond	23.4	[250]
Micro	AS4 CF-Epoxy	Microbond	55.3 / 37.1–73.3	[264]
Micro	HM40 CF-Epoxy	Microbond	33±4 / 40±4 / 39±5	[291]
Micro	HMS40 CF-Epoxy	Microbond	37±4 / 47±4 / 50±5	[291]
Micro	CNT Fibre-Epoxy	Microbond	14.4	[314]
Micro	T300 CF-Epoxy	Microbond	65±3 / 59±2	[319]
Micro	CF-Epoxy	Push-in	1.67–8.7	[338]
Micro	CF-Epoxy (FEM)	Push-in	50–100	[330]
Micro	T800 CF-Epoxy	Push-in	63±5	[330]
Micro	AS4-8552 Epoxy	Push-in	64±2.6	[350]
Micro	AS4-8552 Epoxy	Push-in	31±1.9	[351]
Micro	CF-Epoxy (FEM)	Push-in	100	[332]
Micro	CF-Epoxy	Push-in	75±9 / 102±10	[328]
Micro	CF-BMI	Push-in	103±7 / 117±10	[328]
Micro	CF-PPS	Push-in	3.79–18.72	[338]
Micro	AS4-PEEK	Push-in	37±1.2	[350]

Micro AS4-PEEK	Push-in	16±0.8	[351]
Micro IM7-BMI (FEM)	Push-in	40–100	[352]
Micro CF-Epoxy	Push-out	4.7–42.6	[338]
Micro HS40-Epoxy	Push-out	95 / 101	[335]
Micro HM63-Epoxy	Push-out	89 / 93	[335]
Micro PAN-based CF-Epoxy	Push-out	49.5 / 50.6	[131]
Micro T700SC CF-PPS	Push-out	24 / 57	[325]
Micro AS4-PEEK	Push-out	171±10	[353]
Micro T300 CF-Epoxy (FEM)	Push-out	13.7 / 13–32	[336]
Micro T700SC CF-Epoxy	Push-out	56.4 / 36.3	[354]
Micro E-GF-Epoxy	Push-in	73±5	[327]
Micro GF-Epoxy	Push-in	80	[329]
Micro GF-TP	Push-in	59±24	[328]
Micro GF-PA	Push-in	21±5 / 45±8	[328]
Micro GF-UPPH	Push-out	52.9–64.2	[340]