This datasheet of **ACRYMID® TT50** from **Röhm GmbH** is provided by the international plastics database **CAMPUS**.

ACRYMID® TT50 | PMMI | Röhm GmbH

Product Texts

Productprofil:

ACRYMID® TT50 is a highly heat distortion-resistant poly(n-methyl methacrylimide) (PMMI). Besides showing the properties common to all ACRYMID® molding compounds, such as

• high heat deflection temperature under load,
• excellent transmission and clarity,
• very high strength and rigidity, as well as
• good weather resistance.

ACRYMID® TT50 is special in that it is
• listed by AMECA.

Application:

ACRYMID® molding compound is particularly suitable for injection molding of items meant for applications that involve high heat loads.

Example:

automotive lighting, lenses, fiber optics, luminaire covers, nameplates, sightglasses.

Processing:

ACRYMID® molding compound can be processed on injection molding machines with standard 3-zone general purpose screws for thermoplastics.

Physical Form / Packaging:

ACRYMID® is supplied as pellets of uniform size in aluminum-laminated, 25kg polyethylene bags.

Rheological properties	Value	Unit
Melt volume-flow rate, MVR	**5**	cm³/10min
Temperature	**260**	°C
Load	**10**	kg

Mechanical properties	Value	Unit

Tensile modulus	**4000**	MPa
Stress at break	**80**	MPa
Strain at break	**3**	%
Charpy impact strength, +23°C	**20**	kJ/m²

Thermal properties	Value	Unit
Temp. of deflection under load, 1.80 MPa	**132**	°C
Temp. of deflection under load, 0.45 MPa	**140**	°C
Vicat softening temperature, 50°C/h 50N	**150**	°C
FMVSS	**B**	-

Other properties	Value	Unit
Density	**1210**	kg/m³

Material specific properties	Value	Unit
Luminous transmittance	**91**	%

Characteristics

Processing
Injection Molding

Delivery form
Pellets

Special Characteristics
Light stabilized or stable to light, U.V. stabilized or stable to weather, Heat stabilized or stable to heat, Transparent

Regional Availability
North America, Europe, Asia Pacific, South and Central America, Near East/Africa

Other text information

Injection molding

PREPROCESSING

Predrying temperature: max. 100 °C

Predrying time in a desiccant-type drier: 2 - 3 h

PROCESSING

Melt temperature: 250 - 280°C

Mold temperature: approx. 110°C

Chemical Media Resistance

Acids

Acetic Acid (5% by mass) (23°C)

Lactic Acid (10% by mass) (23°C)

Sulfuric Acid (38% by mass) (23°C)

Sulfuric Acid (5% by mass) (23°C)

Alcohols

Isopropyl alcohol (23°C)

Hydrocarbons

n-Hexane (23°C)

Mineral oils

SAE 10W40 multigrade motor oil (23°C)

Standard Fuels

Standard fuel without alcohol (pref. ISO 1817 Liquid C) (23°C)

Standard fuel with alcohol (pref. ISO 1817 Liquid 4) (23°C)

Diesel fuel (pref. ISO 1817 Liquid F) (23°C)

Other

Water (23°C)

All listed technical data are typical values intended for your guidance.
They are given without obligation and do not constitute a materials specification. Should you have any further questions concerning material behavior or properties, please contact us at the following address :

Röhm GmbH
Deutsche-Telekom-Allee 9
64295 Darmstadt
Germany
E-Mail: plexiglas.polymers@roehm.com
Internet: http://www.plexiglas-polymers.com

® = registered trademark

This information and all further technical advice is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be

verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

NAFTA:
This information and all technical and other advice are based on Roehm's present knowledge and experience. However, Roehm assumes no liability for such information or advice, including the extent to which such information or advice may relate to third party intellectual property rights. Roehm reserves the right to make any changes to information or advice at any time, without prior or subsequent notice. ROEHM DISCLAIMS ALL REPRESENTATIONS AND WARRANTIES, WHETHER EXPRESS OR IMPLIED, AND SHALL HAVE NO LIABILITY FOR, MERCHANTABILITY OF THE PRODUCT OR ITS FITNESS FOR A PARTICULAR PURPOSE (EVEN IF ROEHM IS AWARE OF SUCH PURPOSE), OR OTHERWISE. ROEHM SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND. It is the customer's sole responsibility to arrange for inspection and testing of all products by qualified experts. Reference to trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used.

Sales range and technical data subject to alteration.