

This datasheet of **Akulon® F236-C** from **Envalior** is provided by the international plastics database **CAMPUS**.

Akulon® F236-C | PA6 | Envalior

Product Texts

High Viscosity, Lubricated, Food Contact Quality

ISO 1043 PA6

Mechanical properties	dry / cond	Unit
Tensile modulus	2700 / -	MPa
Yield stress	78 / -	MPa
Yield strain	4.2 / -	%
Charpy notched impact strength, +23°C	6.6 / -	kJ/m²
Charpy notched impact strength, -30°C	3.3 / -	kJ/m²
Thermal properties	dry / cond	Unit
Melting temperature, 10°C/min	220 / *	°C
Burning behavior at 1.5 mm nominal thickness	HB/*	class
Thickness tested (1.5)	1.5 / *	mm
Yellow Card available	Yes / *	-
Burning behavior at thickness h	HB/*	class
Thickness tested (h)	3.0 / *	mm
Yellow Card available	Yes / *	-
Other properties	dry / cond	Unit
Water absorption	9.5 / *	%
Humidity absorption	2.5 / *	%

DeThist website uses cookies. By using this website, you pggey to the பூக்கு of cookies.

Privacy Policy

Material specific properties

Viscosity number

dry / cond Unit

244 / *

Film Properties


dry / cond Unit

cm³/g

Type of extrusion

blown / * -

Diagrams



Characteristics

Processing

Film Extrusion, Sheet Extrusion, Other Extrusion

Delivery form

Pellets

Additives

Lubricants

Regional Availability

Europe

Other text information

Film extrusion

Processing of Akulon® Film Grades

Chemical Media Resistance

Alcohols

Methanol (23°C)

Ethanol (23°C)

	Toluene (23°C)
Ketones	Acetone (23°C)
Ethers	
	Diethyl ether (23°C)

Other

Ethyl Acetate (23°C)

Water (23°C)

All the trademarks mentioned here are trademarks of Envalior.

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.

Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.

Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.

Copyright © Envalior 2024. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.

The CAMPUS internet database is hosted by Altair Engineering GmbH. Altair Engineering GmbH assumes no liability for the system to be free of errors. Any decision about the application of materials must be double checked with the producer of this material.

CAMPUS® is a registered trademark of CWFG mbH, Frankfurt am Main, 2024