
# **HM Wire International, Inc.**

Ph: 330-244-8501 Fax: 330-244-8561





### Insulated Flat Wire 11 AWG - 32 AWG Half Sizes 1.2 Ratio - 1.4 Ratio

AWG Sizes		Ratios - Millimeter Dimensions										
		1:2		1:2.5		1:3		1:3.5		1:4		
AWG	Dia.	Т	W	Т	W	Т	W	Т	W	Т	W	
AWG	mm	mm	mm	mm	mm	mm	mm	mm	mm	mm	mm	
11	2.39	1.50	3.00									
12	2.14	1.34	2.68									
12.5	2.02	1.27	2.53									
13	1.92	1.20	2.40	1.07	2.68							
13.5	1.81	1.13	2.27	1.01	2.54							
14	1.71	1.07	2.15	0.96	2.40	0.88	2.63					
14.5	1.62	1.02	2.03	0.91	2.27	0.83	2.49					
15	1.53	0.96	1.92	0.86	2.15	0.78	2.35					
15.5	1.45	0.91	1.82	0.81	2.03	0.74	2.23					
16	1.37	0.86	1.71	0.77	1.91	0.70	2.10	0.65	2.27	0.61	2.42	
16.5	1.30	0.81	1.62	0.73	1.82	0.66	1.99	0.61	2.15	0.57	2.30	
17	1.22	0.77	1.53	0.69	1.72	0.63	1.88	0.58	2.03	0.54	2.17	
17.5	1.16	0.73	1.45	0.65	1.62	0.59	1.78	0.55	1.92	0.51	2.05	
18	1.09	0.69	1.37	0.61	1.53	0.56	1.68	0.52	1.81	0.49	1.94	
18.5	1.03	0.65	1.30	0.58	1.45	0.53	1.59	0.49	1.71	0.46	1.83	
19	0.98	0.61	1.23	0.55	1.37	0.50	1.50	0.46	1.62	0.43	1.73	
19.5	0.93	0.58	1.17	0.52	1.30	0.48	1.43	0.44	1.54	0.41	1.65	
20	0.88	0.55	1.10	0.49	1.23	0.45	1.35	0.42	1.46	0.39	1.56	
20.5	0.83	0.52	1.04	0.47	1.16	0.42	1.27	0.39	1.38	0.37	1.47	
21	0.79	0.49	0.99	0.44	1.10	0.40	1.21	0.37	1.31	0.35	1.40	
21.5	0.74	0.47	0.93	0.42	1.04	0.38	1.14	0.35	1.23	0.33	1.32	
22	0.70	0.44	0.88	0.39	0.98	0.36	1.08	0.33	1.16	0.31	1.24	
22.5	0.68	0.42	0.85	0.38	0.95	0.35	1.04	0.32	1.12	0.30	1.20	
23	0.63	0.40	0.79	0.35	0.89	0.32	0.97	0.30	1.05	0.28	1.12	
23.5	0.60	0.37	0.75	0.33	0.84	0.31	0.92	0.28	0.99	0.26	1.06	
24	0.57	0.35	0.71	0.32	0.79	0.29	0.87	0.27	0.94	0.25	1.00	
24.5	0.54	0.34	0.67	0.30	0.75	0.27	0.82	0.25	0.89	0.24	0.95	

AWG Sizes		Ratios - Inches Dimensions										
AWG	31263	1:2		1:2.5		1:3		1:3.5		1:4		
AWG	Dia.	Т	W	T	W	T	W	T	W	T	W	
	in.	in.	in.	in.	in.	in.	in.	in.	in.	in.	in.	
11	0.0949	0.059	0.118									
12	0.0846	0.053	0.105									
12.5	0.080	0.050	0.100									
13	0.0756	0.047	0.094	0.042	0.106							
13.5	0.071	0.045	0.089	0.040	0.100							
14	0.0669	0.042	0.085	0.038	0.095	0.035	0.104					
14.5	0.064	0.040	0.080	0.036	0.089	0.033	0.098					
15	0.0609	0.038	0.076	0.034	0.084	0.031	0.093					
15.5	0.057	0.036	0.072	0.032	0.080	0.029	0.088					
16	0.054	0.034	0.067	0.030	0.075	0.028	0.083	0.025	0.089	0.024	0.095	
16.5	0.051	0.032	0.064	0.029	0.071	0.026	0.078	0.024	0.085	0.023	0.090	
17	0.048	0.030	0.060	0.027	0.068	0.025	0.074	0.023	0.080	0.021	0.085	
17.5	0.046	0.029	0.057	0.026	0.064	0.023	0.070	0.022	0.076	0.020	0.081	
18	0.043	0.027	0.054	0.024	0.060	0.022	0.066	0.020	0.071	0.019	0.076	
18.5	0.041	0.026	0.051	0.023	0.057	0.021	0.062	0.019	0.067	0.018	0.072	
19	0.039	0.024	0.048	0.022	0.054	0.020	0.059	0.018	0.064	0.017	0.068	
19.5	0.037	0.023	0.046	0.021	0.051	0.019	0.056	0.017	0.061	0.016	0.065	
20	0.035	0.022	0.043	0.019	0.048	0.018	0.053	0.016	0.057	0.015	0.061	
20.5	0.033	0.020	0.041	0.018	0.046	0.017	0.050	0.015	0.054	0.014	0.058	
21	0.031	0.019	0.039	0.017	0.043	0.016	0.048	0.015	0.051	0.014	0.055	
21.5	0.029	0.018	0.037	0.016	0.041	0.015	0.045	0.014	0.049	0.013	0.052	
22	0.028	0.017	0.035	0.015	0.039	0.014	0.042	0.013	0.046	0.012	0.049	
22.5	0.027	0.017	0.033	0.015	0.037	0.014	0.041	0.013	0.044	0.012	0.047	
23	0.025	0.016	0.031	0.014	0.035	0.013	0.038	0.012	0.041	0.011	0.044	
23.5	0.024	0.015	0.029	0.013	0.033	0.012	0.036	0.011	0.039	0.010	0.042	
24	0.023	0.014	0.028	0.012	0.031	0.011	0.034	0.011	0.037	0.010	0.040	
24.5	0.021	0.013	0.026	0.012	0.030	0.011	0.032	0.010	0.035	0.009	0.037	

Insulation Type:

Polyester / Polyamideimide. Heavy Build. UL recognized, Class 200\*C as round wire. Polyester / Polyamideimide. Heavy Build. UL recognized, Class 240\*C as round wire. Polyester / Polyamideimide / Bondcoat. Heavy Build. UL recognized, Class 180\*C as round wire.

Product can be shipped:

10 lbs. / 4.5 kgs. 20 lbs. / 9.1 kgs. 80 lbs. / 36.3 kgs Spool Size:

6" OD x 3.5" (10 lbs.)


INFORMATION TO BE USED AS A GUIDE ONLY.

Copyright © 2008 HM Wire International, Inc.

Rev.5.06.08.2010

## **HM Wire International, Inc.**

Ph: 330-244-8501 Fax: 330-244-8561





### Insulated Flat Wire 11 AWG - 32 AWG Half Sizes 1.2 Ratio - 1.4 Ratio

AWG Sizes		Ratios - Millimeter Dimensions										
		1:2		1:2.5		1:3		1:3.5		1:4		
AWG	Dia.	Т	W	Т	W	Т	W	Т	W	Т	W	
	mm	mm	mm	mm	mm	mm	mm	mm	mm	mm	mm	
25	0.51	0.32	0.63	0.28	0.71	0.26	0.78	0.24	0.84	0.22	0.90	
25.5	0.48	0.30	0.60	0.27	0.67	0.25	0.74	0.23	0.80	0.21	0.85	
26	0.45	0.28	0.57	0.25	0.63	0.23	0.69	0.21	0.75	0.20	0.80	
26.5	0.43	0.27	0.54	0.24	0.61	0.22	0.66	0.20	0.72	0.19	0.77	
27	0.41	0.26	0.51	0.23	0.57	0.21	0.63	0.19	0.68	0.18	0.72	
27.5	0.39	0.24	0.49	0.22	0.54	0.20	0.60	0.18	0.64	0.17	0.69	
28	0.37	0.23	0.46	0.20	0.51	0.19	0.56	0.17	0.61	0.16	0.65	
28.5	0.35	0.22	0.44	0.20	0.49	0.18	0.53	0.16	0.58	0.15	0.62	
29	0.33	0.21	0.41	0.19	0.46	0.17	0.51	0.16	0.55	0.15	0.59	
29.5	0.31	0.20	0.39	0.18	0.44	0.16	0.48	0.15	0.52	0.14	0.55	
30	0.29	0.18	0.37	0.17	0.41	0.15	0.45	0.14	0.49	0.13	0.52	
30.5	0.28	0.177	0.353	0.158	0.395	0.144	0.432	0.133	0.467	0.125	0.499	
31	0.27	0.166	0.333	0.149	0.372	0.136	0.407	0.126	0.440	0.118	0.470	
31.5	0.25	0.159	0.318	0.142	0.356	0.130	0.390	0.120	0.421	0.113	0.450	
32	0.24	0.150	0.301	0.135	0.336	0.123	0.368	0.114	0.398	0.106	0.425	

AWG Sizes		Ratios - Inches Dimensions										
		1:2		1:2.5		1:3		1:3.5		1:4		
AWG	Dia.	Т	W	Т	W	Т	W	Т	W	Т	W	
AVVG	in.	in.	in.	in.	in.	in.	in.	in.	in.	in.	in.	
25	0.020	0.012	0.025	0.011	0.028	0.010	0.031	0.009	0.033	0.009	0.035	
25.5	0.019	0.012	0.024	0.011	0.026	0.010	0.029	0.009	0.031	0.008	0.033	
26	0.018	0.011	0.022	0.010	0.025	0.009	0.027	0.009	0.030	0.008	0.032	
26.5	0.017	0.011	0.021	0.010	0.024	0.009	0.026	0.008	0.028	0.008	0.030	
27	0.016	0.010	0.020	0.009	0.023	0.008	0.025	0.008	0.027	0.007	0.029	
27.5	0.015	0.010	0.019	0.009	0.021	0.008	0.023	0.007	0.025	0.007	0.027	
28	0.014	0.009	0.018	0.008	0.020	0.007	0.022	0.007	0.024	0.006	0.026	
28.5	0.014	0.009	0.017	0.008	0.019	0.007	0.021	0.006	0.023	0.006	0.024	
29	0.013	0.008	0.016	0.007	0.018	0.007	0.020	0.006	0.022	0.006	0.023	
29.5	0.012	0.008	0.015	0.007	0.017	0.006	0.019	0.006	0.020	0.005	0.022	
30	0.012	0.007	0.015	0.007	0.016	0.006	0.018	0.005	0.019	0.005	0.021	
30.5	0.011	0.007	0.014	0.006	0.016	0.006	0.017	0.005	0.018	0.005	0.020	
31	0.01	0.007	0.013	0.006	0.015	0.005	0.016	0.005	0.017	0.005	0.019	
31.5	0.01	0.006	0.013	0.006	0.014	0.005	0.015	0.005	0.017	0.004	0.018	
32	0.009	0.006	0.012	0.005	0.013	0.005	0.015	0.004	0.016	0.004	0.017	

Insulation Type:

Polyester / Polyamideimide. Heavy Build. UL recognized, Class 200\*C as round wire. Polyester / Polyamideimide. Heavy Build. UL recognized, Class 240\*C as round wire.

Polyester / Polyamideimide / Bondcoat. Heavy Build. UL recognized, Class 180\*C as round wire.

Product can be shipped:

10 lbs. / 4.5 kgs. 20 lbs. / 9.1 kgs. 80 lbs. / 36.3 kgs. Spool Size: 6" OD x 3.5" (10 lbs.)

INFORMATION TO BE USED AS A GUIDE ONLY

Copyright © 2008 HM Wire International, Inc.

Rev.5.06.08.2010

#### THE PROCESS

The pre-insulated wire or bare wire is flattened utilitizing proprietary equipment in a single step deformation between mirror polished work surfaces. It is special for the process that the deformation is performed with negligible elongation. This means the cross sectional area is reduced only marginally. The result is that even at the maximum ratio of deformation 1:4, the insulation is stretched no more than 25% on the flats, and in one direction only (crosswise).

It has shown that the flattening preserves the integrity of practically all types of insulation including solderable polyurethanes and bondcoats as well as high temperature polymide/imide coatings. Studies of sections of flattened wire show a continuous rather than an angular transition from the flats into semi elliptical edges practically without any stress concentrations. The product also does not exhibit the "dogbone" shape often encountered in post insulated rectangular wire due to surface tension drawing the varnish away from the wire edges.

#### WORK HARDENING

Depending on the flattening ratio the process normally involves a degree of work hardening, which leaves the wire somewhat harder than post insulated wire. The increased stiffness is percieved as an advantage in certain applications.