

-2

SMD SE(SMD)

Study

Heterogeneity:  $I^2 = 76\%$ , p < 0.01

Standardised Mean

**Difference** 

2

3

**SMD** 

95%-CI Weight