

-1.5 -1 -0.5

SMD SE(SMD)

Study

Heterogeneity: $I^2 = 58\%$, p = 0.05

Standardised Mean

Difference

0

0.5

1.5

SMD

95%-CI Weight