

THIRD PARTY TEST REPORT

SGS India Pvt Ltd, Bengaluru Laboratory
Report No. SGS/BLR/2026/08/2214 | Date: 02 August 2026

Client: Sri Balaji Corrugators Pvt Ltd
Sample: 5-ply corrugated box, 500x400x350 mm, BF-18 grade
Sample received: 28 July 2026

Test	Method	Specified	Result	Verdict
Bursting strength	IS 7063	$\geq 16 \text{ kg/cm}^2$	17.4 kg/cm ²	Pass
Edge crush (ECT)	IS 14871	$\geq 5.2 \text{ kN/m}$	5.8 kN/m	Pass
Grammage, outer liner	IS 1060	180 $\pm$ 8 GSM	183 GSM	Pass
Moisture content	IS 1060	$\leq 9\%$	7.2%	Pass
Drop test, 10 drops	IS 7028	No rupture	No rupture	Pass
Compression, stacked	IS 7028	$\geq 250 \text{ kgf}$	268 kgf	Pass

Results relate only to the sample tested. This report shall not be reproduced except in full.