



LUBRICANTS

POWER TO PERFORM

ENKLO HVLP 68 P (H)

SPECIAL FEATURES:

ENKLO HVLP 68 P is a long drain, premium quality lubricating oil formulated with high quality base stock and carefully selected additives.

ENKLO HVLP 68 P offers outstanding high viscosity index, top of the line anti-wear properties, top tier oxidation stability and a high FZG rating.

SPECIFICATIONS:

IS:11656-1986, NF E 48603 CLASS HV, CM-P-68, 69 & 70.

DIN 51524 PART 3 (HVLP),

DENNISON HF-0 & HF-2,

CINCINNATI MILACRON P-68 (VG 32), P-69 (VG 68), P-70 (VG 46),

USS 127 and Passes Vickers Vane Pump Test .

APPLICATION AREA:

Used in mobile hydraulics requiring high viscosity index (HVI FLUIDS), hydraulic systems, mining machinery, machine tools systems, etc. wherein oil is recirculated and used for extensive periods.

PERFORMANCE BENEFITS:

- Resistance to thermal degradation
- Very high resistance to oxidation
- Very good hydrolytic stability & high viscosity index
- Enhanced filterability
- Improved FZG rating
- Exceptional anti-wear properties
- Longer drain period 5000 hrs

PACKAGES:

210 LT.(HDPE & EPICOATED MS BARREL) Filtered to NAS Class 7 Cleanliness.

PHYSIOCHEMICAL PROPERTIES:

Specification	Test Method	HCE Premium 68 (5000 hrs)	ENKLO HVLP 68 P (H) (5000 hrs) (Typical Values)
Aspects (color & Odour)	Visual	C & B	C & B
KV @ 40 deg Celsius, cSt	ASTM D 445	62-74	68.71
KV @ 100 deg Celsius, cSt	ASTM D 445	REPORT	10.8
Viscosity Index	ASTM D 2270	MIN 140	147
Total Acid Number,mgKOH/g	ASTM D 664	REPORT	0.7
Pour Point, Deg C	ASTM D 97	MAX -30	-30



LUBRICANTS

POWER TO PERFORM

ENKLO HVLP 68 P (H)

PHYSIOCHEMICAL PROPERTIES:

Specification	Test Method	HCE Premium 68 (5000 hrs)	ENKLO HVLP 68 P (H) (5000 hrs) (Typical Values)
Flash Point, Deg C	ASTM D 92	MIN 200	230
Demulsibility, ml (Minutes)	ASTM D 1401	MAX 30	12
Moisture Content, ppm	Crackle	NONE	NONE
FOAMING, ml, SEQUENCE I	ASTM D 892	50/0	40/0
SEQUENCE II		50/0	30/0
SEQUENCE III		50/0	40/0
Copper plate corrosion, 3hr/100C	ASTM D 130	MAX 1B	1A
Rust Proof performance, Method A	ASTM D 665	PASS	PASS
Method B		PASS	PASS
Oxidation Stability, RBOT, Min	ASTM D 2272	MIN 600	650
Abrasion Wear Resistance, 4 ball wear Scar diameter,mm	ASTM D 4172	MAX 0.48	0.44
Filterability, sec – DRY	Denison TP	MAX 600	191
WET		REPORT	258
Air Discharge Performance	ASTM D 3427	MAX 7' 00"	5
Metal component, ppm- Zinc	ASTM D 4951	REPORT	625
Pentane/ Toulene		REPORT	NIL
Pollution Degree	NAS 1638	MAX 7	7
Shear Stability, SONIC, 30 min 40 C, Viscosity Reduction rate (%)	ASTM D 2603	MAX 5	4
Thermal Stability,150C, 168 hr Total Sludge(mg/100ml)	ASTM D 2070	MAX 10	7