

		CTP		DOC .NO	CTE0.06-FR.02
		LIST OF ITEMS FOR MINIMUM AND MAXIMUM AGE LIMITS			
(FOR RADIAL COMPONENTS BOTH TBR AND PCR)					
SR.NO	COMPONENTS			MINIMUM	MAXIMUM
1	Dipped Fabric			REFER DOCUMENT NUMBER - CORP/TECH/A-110	
2	Steel wire(From DOM)				
3	Bead wire (From DOM)			NA	6 Months
4	MASTER COMPOUND				
	MASTER COMPOUND TBR	a	Non silica	4 Hrs	15 Days
		b	Master with silane coupling agent & silica upto 10 Phr	4 Hrs	7 Days
		c	Master with silane coupling agent & silica 11- 30 Phr	4 Hrs	4 Days
		d	Master with silane coupling agent & silica more than 30 Phr	4 Hrs	3 Days
		e	Master compound stage containing Cobalt salts	2 Hrs	24 Hrs
		f	Master Compounds with Butyl rubber	4 Hrs	1 Day
5	MASTER COMPOUND PCR	a	Non silica	4 Hrs	15 Days
				MB 231	4 days
		b	Silica and silane coupling agent up to 10 Phr	4 Hrs	3 Days
		c	Silica and silane coupling agent more than 10 Phr (First Master)	24 Hrs	3 days
		d	Silica and silane coupling agent more than 10 Phr (Second Master)	8 Hrs	3 days
		e	Silica and silane coupling agent more than 10 Phr (Repass / Third Master)	8 Hrs	3 Days
		f	Master compound stage containing Cobalt salts	2 Hrs	24 Hrs
g	Master Compounds with Butyl rubber	4 Hrs	1 Day		
6	FINAL COMPOUND				
	FINAL COMPOUND TBR	a	Non silica	4 Hrs	5 Days
		b	Containing Only Silica	4 Hrs	3 Days (B96, B99, B99EG, B176)
		c	Silica and silane coupling agent > 6 phr	4 Hrs	3 Days (T6629 , B186)
		d	T636/T639	4 Hrs	2 Days
		e	Butyl compound	4 Hrs	3 Days
7	FINAL COMPOUND PCR	a	Non silica	4 Hrs	5 Days
		b	Silica and silane coupling agent up to 10 Phr	4 Hrs	3 Days
		c	Silica and silane coupling agent more than 10 Phr	8 Hrs	3 Days
		d	Butyl compound	4 Hrs	3 Days
		e	Belt skim/edge gum B460/B-127	4 Hrs	4 Days
		f	White sidewall & cover gum compound(Outsourced)	NA	7 Days
	END CEMENT	f	END CEMENT FINAL COMPOUND	1 Hrs	2 Days
8	GPC	a	Cement paint	4 Hrs	5 Days and 7 Days (Closed containers)
	FINAL	b	Repair compound-TBR	4 Hrs	7 Days
	Out sourced	c	Final compound	NA	7 Days
	Rework -TBR	e	Tread ,SW/IL/SHOULDER PAD/APEX	NA	5 Days
	Rework -PCR	f	Tread ,SW/IL/APEX	NA	5 Days
9	INNER LINER				
	PCR	a	Inner liner+squeegee	6 Hrs	3 Days
	TBR	b	Squeegee	2 Hrs	
		c	Inner liner+squeegee	8 Hrs	

		CTP			DOC .NO	CTE0.06-FR.02
		LIST OF ITEMS FOR MINIMUM AND MAXIMUM AGE LIMITS				
(FOR RADIAL COMPONENTS BOTH TBR AND PCR)						
10	BELT EDGE GUM					
	TBR	a	Calendered edge gum	2 Hrs	3 Days	
		b	Slitted edge gum	NA	2 Days	
	PCR	c	Calendered edge gum	2 Hrs	3 Days	
		d	Slitted edge gum	NA	2 Days	
11	EXTRUDED SIDEWALL					
	PCR/TBR	a	Sidewall	2 Hrs	3 Days	
b		Belt edge filler				
12	EXTRUDED TREAD					
	PCR/TBR	a	Carbon tread	2 Hrs	3 Days	
		b	Silica tread	2 Hrs	1 Day	
13	APEX-Manual application	a	TBR	1 Hrs	2 Days	
14	CALENDERED MATERIAL					
	TBR-STEEL	a	Steel Bodyply	4 Hrs	4 Days	
		b	Belts & STC(Except B186 skim compound)	4 Hrs	4Days	
		c	Belts (with B186 skim compound)	4 Hrs	3 days	
	PCR-STEEL	c	Steel Belt	4 Hrs	4 Days	
	TBR-FABRIC	d	Calendered Textile fabric	4 Hrs	3 Days	
	PCR-FABRIC	e	Calendered Textile fabric	4 Hrs	3 Days	
15	CUT PLIES/BREAKER					
	TBR	a	Steel	NA	1 Day	
		b	Cut Fabric			
		c	Slitted Fabric			
	PCR	d	Steel			
		e	Cut Fabric			
		f	Slitted Fabric			
16	BEADS					
	PCR	a	Insulated	Covered	3 Days	
				Uncovered	2 Days	
		b	Fillered	NA	1 Day	
	TBR	c	Insulated	NA	2 Days	
d		Apexed	NA	1 Day		
17	GREEN TYRE					
	TBR SUPER SINGLE	a	Painted GT	15minutes	24 hrs	
	TBR Except SUPER SINGLE	b	Painted GT	NA	2 Days	
18	CARCASS					
	PCR	a	1st stage	NA	1 Day	
		b	2 nd stage GT (Unpainted)	NA	1 Day	
		c	2 nd stage GT (Painted)	15minutes	2 Days	
19	TBR	a	Cured tyre under proper ware house condition			1 year (Under Proper Storage Condition)
	PCR	b	Cured tyre under proper ware house condition			1 year (Under Proper Storage Condition)
20	Tubes	a	Stored under proper ware house condition			1 year (Under Proper Storage Condition)
	Flaps	b	Stored under proper ware house condition			1 year (Under Proper Storage Condition)
	Bladder	c	Stored under proper ware house condition	30 days	1 year (Under Proper Storage Condition in Dark room)	
REVISION HISTORY						
Rev no	Date	Change			Originator	Approved
12	20.01.2024	White sw & cover gum ageing added				
11	31.07.2023	PCR IL ageing revised				
10	30.11.2022	Revised as per Corp Standard for RM				
9	13.02.2021	Revised as per Corp Spec				