



ZHEJIANG TSINGSHAN STEEL PIPE CO.,LTD.

XIAOZHI INDUSTRIAL ZONE, QINGTIAN COUNTY, ZHEJIANG PROVINCE, P.R. CHINA

MILL TEST CERTIFICATES to EN 10204/3.1 PED 2014/68/EU

PED Certificate no.: 01 202 CHN/Q-16 0600

Customer : STAINALLOY NEDERLAND B.V.
P.O Number : P34432
Specification : ASTM A312 ✓
Steel Grade : TP317L ✓
Goods : STAINLESS STEEL SEAMLESS PIPE

Cert No. : TS210421-02-05 ✓
Delivery Condition : Solution Treated
Appearance : Passivate & Pickling
Item No. : 8
Tag No. : ATM-C04-L2 ✓

Heat No.		Chemical Composition (%)							
Spec.	Min.	C	Si	Mn	P	S	Cr	Ni	Mo
	Max.	0.035	1.00	2.00	0.045	0.030	20.00	11.00	3.00
Ladle Analysis	✓	0.015	0.28	1.61	0.036	0.001	18.30	11.43	3.03
Product Analysis	210219AE02-01	0.017	0.31	1.59	0.034	0.003	18.35	11.54	3.11
		0.029	0.28	1.55	0.038	0.003	18.42	11.52	3.14

Batch No.	Size	Quantity	Dimension & Surface
T210610-04	141.3*6.55*7621 ✓	3 PCS	509 KGS
		22.863 M	OK

Mechanical Properties(Acc to ASTM A370)									
Test No.		Tensile Strength	Yield Strength	Elongation	Flattening	Flaring	Ring	Hardness	Impact
		MPa	MPa	G.L.50mm	Test	Test	Expanding	Test	Test
		MPa	Rp0.2	A(%)			Test	HRB	Size No.
Spec.	Min.	515	205	35					
	Max.								
LS21061206		610	307	54	GOOD	/	/	/	/

Nondestructive Examination			
100% Hydrostatic Test Acc to ASTM A999	Eddy Current Test	Longitudinal Ultrasonic Test Notch 12.5%	100% wall thickness check by UT inline
	Acc to ASTM E426	Acc to ASTM E213	Acc to ASTM A312/A999
10Mpa/10S	/	GOOD	Qualified

Additional Remarks:

- Country of Origin: China
- 100% PMI as per ASTM A312 and A999
- No weld repair
- Heat Treatment: Solution annealing done at 1040 °C (Min.)
- Cooling Type: Rapid Water Cooling
- 100% visual ASTM A312/A999, Dimensional ASTM A312/A999/B36.19 and Qty check by mill
- SE acc to ASME B16.25 FIG. 4

We hereby certify that the material was found to be free of mercury contamination, every heat, dimension and batch has been tested for radioactivity and has been found within the limit of background radiation, the material described in the certificate has been tested as described and complies with the order/contract and it is of Chinese origin.

Revised by: [Signature]
For: [Signature]
Date: 07-Jul-21

Date

