

PAGE	CUSTOMER	DESTINATION	
2	COEN STEEL LTD	DEERPARK INDUSTRIAL ESTATE	
ORDER	DENOMINATION		DATE
22/1896/3	STANDARD BS 4449:2005	GRADE B 500 B	10/08/2022

REMARKS	
Dimensions in mm	
Re and Rm in MPa (N/mm ²)	
Elongation and Agt %	



SN MAIA - SIDERURGIA NACIONAL S.A.

4425-514 S. Pedro Fins - Maia - Portugal
Tel.: +351 229 699 000 - Fax: +351 229 699 036

CAST			CHEMICAL COMPOSITION OF THE STEEL IN % OF:												MEASUREMENT OF RIBS			TENSILE TESTS				
N°	Ø	LENGTH	C	P	S	Mn	Cr	Ni	Cu	V	Mo	N	Ceq	Si	h	c	fR	Rm	Re	Agt	Kg/m	BEND-REBEND
453335/4	20	6000	0,21	0,026	0,024	0,53	0,12	0,14	0,44	0,000	0,024	0,011	0,37	0,10	1,74	12,6	0,081	691	588	8,4	2,423	S
																		681	578	10,4	2,421	S
																		690	587	12,2	2,432	S
																		684	579	9,1	2,425	S
453337/2	20	6000	0,20	0,028	0,026	0,55	0,11	0,11	0,38	0,001	0,019	0,010	0,35	0,11	1,76	12,5	0,083	677	576	10,0	2,445	S
																		667	564	10,1	2,449	S
																		676	579	10,3	2,447	S
																		668	559	10,2	2,444	S
453341/2	20	6000	0,20	0,026	0,023	0,59	0,13	0,12	0,39	0,002	0,023	0,010	0,36	0,13	1,54	12,6	0,073	682	584	8,9	2,454	S
																		681	582	10,1	2,449	S
																		687	589	11,4	2,472	S
																		681	583	10,4	2,466	S

MANUFACTURING PROCESS ROUTE: QUENCHED AND SELF TEMPERED

HEREBY THE COMPANY CERTIFIES THAT THE PRODUCTS INCLUDED IN THIS CERTIFICATE ARE FREE OF RADIOACTIVITY.



IDENTIFICATION MARKS



QUALITY DEPARTMENT

Amela