

PURCHASER : PROVEEDORA INDUSTRIAL LAREDO S.A DE C.V.
 ORDER NO. : RK1322
 SPEC. FOR RAW MATERIAL : ASTM A106 Gr. B, ASTM A234 Gr. WPB
 SPEC. FOR INSPECTION : ASTM A234 - 13e1 WPB
 ASME SA234 - 2013 WPB
 ASME B16.9-2012 / ASME B16.25-2012
 BS EN 10204 3.1-2004

JOB NO. : PI1502019
 CERTIFICATE NO. : Q150518019-01
 DATE : MAY. 18, 2015

	PO. Item No.	Product & Size(Inch)				Heat Code		Quantity		Heat No.		Certificate No.					
1	5	45 ELBOW LR	2-1/2	STD	118	126	14304118	BGSAG1412030001100									
2	6	45 ELBOW LR	4	STD	792	270	15305792	BGSAG1503260004500									
3	26	90 ELBOW LR	2-1/2	XH	291	20	14303291	BGSAG1410270002900									
4	27	90 ELBOW LR	3	STD	895	1000	14303895	BGSAG1412030001300									
5	1	90 ELBOW LR	4	STD	792	2080	15305792	BGSAG1503260004500									
Spe.	Chemical Composition %												Tension Test			Hardness Test	Magnetic Particle Exam.
	C	Si	Mn	P	S	Cu	Ni	Cr	Mo	V	Nb	CE	Yield Strength	Tensile Strength	Elongation		
	X100	X100	X100	X1000	X1000	X100	X100	X100	X1000	X1000	X100	P.S.I	P.S.I	%	HBW		
	MIN		10	29									35000	60000	30		
MAX	25		106	50	58	40	40	40	15	80	20	42		95000		197	
1	13	26	127	9	1	3	2	6	1	<10	1	36	42775	65540	36	137	N/A
2	15	22	126	7	1	2	2	5	1	<10	1	38	45820	63510	34	142	N/A
3	13	24	123	7	1	3	3	5	2	<10	1	35	47125	75400	35	122	N/A
4	13	28	126	7	1	2	2	12	3	<10	1	37	50895	82505	35	143	N/A
5	15	22	126	7	1	2	2	5	1	<10	1	38	52490	81635	35	126	N/A
	Visual Examination				Dimensional Inspection				Heat Treatment								
	Acceptable				Acceptable				N/A								

$$CE = C + Mn/6 + (Cr + Mo + V) / 5 + (Ni + Cu) / 15$$

MATERIAL CONFORMS TO NACE MR0103-2012/ NACE MR0175-2009 and ISO 15156-2009

We hereby certify that the products described here in have been manufactured and tested in accordance with specifications and also the purchaser's requirements concerned.

NOTE:

1. ABOVE - LISTED ELBOWS HAVE BEEN HOT - FORMED AT A TEMPERATURE ABOVE 1150° F (621°C) AND BELOW 1800°F (982° C) AND SUBSEQUENTLY COOLED IN STILL AIR.
 2. THE QUALITY MANAGEMENT SYSTEM OF ISO 9001-2008 AND PED 97/23/EC, ANNEX I SEC. 4.3 HAVE BEEN APPROVED BY LRQA
 3. ANOTHER PED 97/23/EC, ANNEX I SEC. 4.3 TUV-NORD 0045
 4. ITEM NUMBER 1, 2, 3, 4 & 5 USE RAW MATERIAL A106 GR.B/ A333 GR.6.
- THE MANGANESE ABOVE THE SPECIFIED MAXIMUM WILL BE PERMITTED UP TO A MAXIMUM OF 1.65%. (FOOTNOTE D IN TABLE 1 OF ASTM A234 - 13e1 WPB).



Quality Assurance Section/ Manager

PURCHASER : PROVEEDORA INDUSTRIAL LAREDO S.A DE C.V.
 ORDER NO. : RK1322
 SPEC. FOR RAW MATERIAL : ASTM A106 Gr. B, ASTM A234 Gr. WPB
 SPEC. FOR INSPECTION : ASTM A234 - 13e1 WPB
 ASME SA234 - 2013 WPB

JOB NO. : PI1502019

ASME B16.9-2012 / ASME B16.25-2012
 BS EN 10204 3.1-2004

CERTIFICATE NO. : Q150518019-02
 DATE : MAY. 18, 2015

	PO. Item No.	Product & Size(Inch)				Heat Code		Quantity		Heat No.		Certificate No.					
6	28	90 ELBOW LR	6	STD	24V			120		1436824V	C201504927-1						
7	2	90 ELBOW SR	2	STD	292			80		14303292	BGSAG1410270002500						
8	3	90 ELBOW SR	3	STD	857			40		14302857	BGSAG1409010001900						
9	4	90 ELBOW SR	4	STD	793			20		15305793	BGSAG1503260004900						
Spe.	Chemical Composition %											Tension Test			Hardness Test	Magnetic Particle Exam.	
	C	Si	Mn	P	S	Cu	Ni	Cr	Mo	V	Nb	CE	Yield Strength	Tensile Strength			Elongation
	X100	X100	X100	X1000	X1000	X100	X100	X100	X1000	X1000	X1000	X100	P.S.I	P.S.I	%	HBW	
MIN		10	29										35000	60000	30		
MAX	25		106	50	58	40	40	40	15	80	20	42		95000		197	
6	16	24	89	12	8	8	3	6	1	3	1	33	39585	63510	36	140	N/A
7	13	25	129	8	1	4	3	3	1	<10	1	36	46980	74095	39	138	N/A
8	13	26	125	6	2	4	3	6	2	<10	1	36	48575	73515	38	142	N/A
9	13	24	126	9	<1	2	2	5	1	<10	1	36	43645	69890	37	143	N/A
	Visual Examination				Dimensional Inspection				Heat Treatment								
	Acceptable				Acceptable				N/A								

CE = C + Mn/6 + (Cr + Mo + V) / 5 + (Ni + Cu) / 15

MATERIAL CONFORMS TO NACE MR0103-2012/ NACE MR0175-2009 and ISO 15156-2009

We hereby certify that the products described here in have been manufactured and tested in accordance with specifications and also the purchaser's requirements concerned.

NOTE:

- ABOVE - LISTED ELBOWS HAVE BEEN HOT - FORMED AT A TEMPERATURE ABOVE 1150° F (621°C) AND BELOW 1800°F (982° C) AND SUBSEQUENTLY COOLED IN STILL AIR.
 - THE QUALITY MANAGEMENT SYSTEM OF ISO 9001-2008 AND PED 97/23/EC, ANNEX I SEC. 4.3 HAVE BEEN APPROVED BY LRQA
 - ANOTHER PED 97/23/EC, ANNEX I SEC. 4.3 TUV-NORD 0045
 - ITEM NUMBER 7, 8 & 9 USE RAW MATERIAL A106 GR.B/ A333 GR.6.
- THE MANGANESE ABOVE THE SPECIFIED MAXIMUM WILL BE PERMITTED UP TO A MAXIMUM OF 1.65%. (FOOTNOTE D IN TABLE 1 OF ASTM A234 -13e1 WPB).



Quality Assurance Section/ Manager

PURCHASER : PROVEEDORA INDUSTRIAL LAREDO S.A DE C.V.
 ORDER NO. : RK1322
 SPEC. FOR RAW MATERIAL : ASTM A516 Gr. 65, ASTM A234 Gr. WPB
 SPEC. FOR INSPECTION : ASTM A234 - 13e1 WPB
 ASME SA234 - 2013 WPB
 ASME B16.9-2012 / ASME B16.25-2012
 BS EN 10204 3.1-2004

JOB NO. : PI1502019
 CERTIFICATE NO. : Q150518019-03
 DATE : MAY. 18, 2015

	PO. Item No.	Product & Size(Inch)				Heat Code		Quantity		Heat No.		Certificate No.					
10	9	CAP	2	STD	Z34	185		1EZ34		040226A0005							
11	9	CAP	2	STD	729	55		N10729		20140701-PS-025-001							
12	10	CAP	8	STD	M72	130		2RM72		040401A0004							
13	11	CAP	10	STD	B83	25		3VB83		040226A0008							
Spe.	Chemical Composition %												Tension Test			Hardness Test	Magnetic Particle Exam.
	C	Si	Mn	P	S	Cu	Ni	Cr	Mo	V	Nb	CE	Yield Strength	Tensile Strength	Elongation		
	X100	X100	X100	X1000	X1000	X100	X100	X100	X1000	X1000	X100	P.S.I	P.S.I	%	HBW		
	MIN		10	29									35000	60000	30		
MAX	25		120	50	58	40	40	40	15	80	20	42		95000		197	
10	21	22	103	15	3	<1	1	2	<1	1	<1	39	42775	69165	39	130	Acceptable
11	16	23	106	13	2	1	1	1	0	0	1	34	46690	66265	33	121	
12	17	22	111	11	5	1	1	2	<1	1	1	36	44950	69310	34	133	
13	19	21	106	15	2	1	1	2	<1	1	1	37	46400	72935	35	111	
	Visual Examination				Dimensional Inspection				Heat Treatment								
	Acceptable				Acceptable				S.R 700°C x 0.5H								

CE = C + Mn/6 + (Cr + Mo + V) / 5 + (Ni + Cu) / 15


MATERIAL CONFORMS TO NACE MR0103-2012/ NACE MR0175-2009 and ISO 15156-2009

We hereby certify that the products described here in have been manufactured and tested in accordance with specifications and also the purchaser's requirements concerned.

NOTE

1. THE QUALITY MANAGEMENT SYSTEM OF ISO 9001-2008 AND PED 97/23/EC, ANNEX I SEC. 4.3 HAVE BEEN APPROVED BY LRQA

2. ANOTHER PED 97/23/EC, ANNEX I SEC. 4.3 TUV-NORD 0045



Quality Assurance Section/ Manager

PURCHASER : PROVEEDORA INDUSTRIAL LAREDO S.A DE C.V.
 ORDER NO. : RK1322
 SPEC. FOR RAW MATERIAL : ASTM A106 Gr. B, ASTM A234 Gr. WPB
 SPEC. FOR INSPECTION : ASTM A234 - 13e1 WPB
 ASME SA234 - 2013 WPB
 ASME B16.9-2012 / ASME B16.25-2012
 BS EN 10204 3.1-2004

JOB NO. : PI1502019
 CERTIFICATE NO. : Q150518019-04
 DATE : MAY. 18, 2015

	PO. Item No.	Product & Size(Inch)				Heat Code		Quantity		Heat No.		Certificate No.					
14	18	RED. CON	1-1/2 x 1	STD	858				80		14302858		BGSAG1409010002400				
15	19	RED. CON	2-1/2 x 1	STD	080				40		14302080		BGSAG1406170013800				
16	20	RED. CON	6 x 4	STD	25V				210		1436825V		C201504930-1				
17	21	RED. CON	8 x 4	STD	10V				50		1437010V		C201504928-1				
18	22	RED. CON	12 x 6	STD	74V				30		1436374V		C201504916-1				
Spe.	Chemical Composition %												Tension Test			Hardness Test	Magnetic Particle Exam.
	C	Si	Mn	P	S	Cu	Ni	Cr	Mo	V	Nb	CE	Yield Strength	Tensile Strength	Elongation		
	X100	X100	X100	X1000	X1000	X100	X100	X100	X100	X1000	X1000	X100	P.S.I	P.S.I	%	HBW	
MIN		10	29										35000	60000	30		
MAX	25		106	50	58	40	40	40	15	80	20	42		95000		197	
14	13	26	127	8	2	3	2	5	1	<10	1	36	44660	66410	34	112	Acceptable
15	18	24	56	8	2	3	3	6	2	<10	<1	29	50315	72500	34	110	Acceptable
16	14	30	99	13	8	8	3	5	0	3	1	32	47850	66555	38	133	Acceptable
17	16	24	86	12	6	8	2	7	2	2	2	33	42485	64960	35	127	Acceptable
18	11	28	130	17	3	9	2	6	1	4	7	35	42775	66120	34	141	Acceptable
	Visual Examination				Dimensional Inspection				Heat Treatment								
	Acceptable				Acceptable				S.R 700°C x 0.5H								

$$CE = C + Mn/6 + (Cr + Mo + V) / 5 + (Ni + Cu) / 15$$

MATERIAL CONFORMS TO NACE MR0103-2012/ NACE MR0175-2009 and ISO 15156-2009

We hereby certify that the products described here in have been manufactured and tested in accordance with specifications and also the purchaser's requirements concerned.

NOTE

1. THE QUALITY MANAGEMENT SYSTEM OF ISO 9001-2008 AND PED 97/23/EC, ANNEX I SEC. 4.3 HAVE BEEN APPROVED BY LRQA
2. ANOTHER PED 97/23/EC, ANNEX I SEC. 4.3 TUV-NORD 0045
3. ITEM NUMBER 14 & 18 USE RAW MATERIAL A106 GR.B/ A333 GR.6.

THE MANGANESE ABOVE THE SPECIFIED MAXIMUM WILL BE PERMITTED UP TO A MAXIMUM OF 1.65%. (FOOTNOTE D IN TABLE 1 OF ASTM A234 -13e1 WPB).



Quality Assurance Section/ Manager

PURCHASER : PROVEEDORA INDUSTRIAL LAREDO S.A DE C.V.
 ORDER NO. : RK1322
 SPEC. FOR RAW MATERIAL : ASTM A106 Gr. B, ASTM A234 Gr. WPB
 SPEC. FOR INSPECTION : ASTM A234 - 13e1 WPB
 ASME SA234 - 2013 WPB

JOB NO. : PI1502019

ASME B16.9-2012 / ASME B16.25-2012
 BS EN 10204 3.1-2004

CERTIFICATE NO. : Q150518019-05
 DATE : MAY. 18, 2015

	PO. Item No.	Product & Size(Inch)				Heat Code		Quantity		Heat No.		Certificate No.					
19	23	RED. CON	12 x 10	STD	74V			15	1436374V		C201504916-1						
20	24	RED. CON	14 x 8	STD	034			15	93-03034		00028656						
21	25	RED. CON	16 x 14	STD	132			20	437132		C13313645015						
22	12	RED. ECC	1-1/2 x 1	STD	858			30	14302858		BGSAG1409010002400						
23	13	RED. ECC	2 x 1	STD	444			224	14301444		BGSAG1404300001900						
Spe.	Chemical Composition %												Tension Test			Hardness Test	Magnetic Particle Exam.
	C	Si	Mn	P	S	Cu	Ni	Cr	Mo	V	Nb	CE	Yield Strength	Tensile Strength	Elongation		
	X100	X100	X100	X1000	X1000	X100	X100	X100	X100	X1000	X1000	X100	P.S.I	P.S.I	%	HBW	
MIN		10	29										35000	60000	30		
MAX	25		106	50	58	40	40	40	15	80	20	42		95000		197	
19	11	28	130	17	3	9	2	6	1	4	7	35	42775	66120	34	131	Acceptable
20	20	22	58	18	10	3	2	4	1	3	1	31	42340	65830	36	129	Acceptable
21	20	23	54	16	14	1	9	14	0	<10	20	32	43500	72065	37	138	Acceptable
22	13	26	127	8	2	3	2	5	1	<10	1	36	44660	66410	34	119	Acceptable
23	18	22	55	8	3	2	3	9	5	<10	<1	30	49155	79605	35	126	Acceptable
	Visual Examination				Dimensional Inspection				Heat Treatment								
	Acceptable				Acceptable				S.R 700°C x 0.5H								

CE = C + Mn/6 + (Cr + Mo + V) / 5 + (Ni + Cu) /15

MATERIAL CONFORMS TO NACE MR0103-2012/ NACE MR0175-2009 and ISO 15156-2009

We hereby certify that the products described here in have been manufactured and tested in accordance with specifications and also the purchaser's requirements concerned.


NOTE

1. THE QUALITY MANAGEMENT SYSTEM OF ISO 9001-2008 AND PED 97/23/EC, ANNEX I SEC. 4.3 HAVE BEEN APPROVED BY LRQA

2. ANOTHER PED 97/23/EC, ANNEX I SEC. 4.3 TUV-NORD 0045

3. ITEM NUMBER 19 & 22 USE RAW MATERIAL A106 GR.B/ A333 GR.6.

THE MANGANESE ABOVE THE SPECIFIED MAXIMUM WILL BE PERMITTED UP TO A MAXIMUM OF 1.65%. (FOOTNOTE D IN TABLE 1 OF ASTM A234 -13e1 WPB).


 Quality Assurance Section/ Manager

PURCHASER : PROVEEDORA INDUSTRIAL LAREDO S.A DE C.V.
 ORDER NO. : RK1322
 SPEC. FOR RAW MATERIAL : ASTM A106 Gr. B, ASTM A234 Gr. WPB
 SPEC. FOR INSPECTION : ASTM A234 - 13e1 WPB
 ASME SA234 - 2013 WPB

JOB NO. : PI1502019

ASME B16.9-2012 / ASME B16.25-2012
 BS EN 10204 3.1-2004

CERTIFICATE NO. : Q150518019-06
 DATE : MAY. 18, 2015

	PO. Item No.	Product & Size(Inch)				Heat Code		Quantity		Heat No.		Certificate No.					
24	13	RED. ECC	2 x 1		STD	12V		46		1415412V		C201504939-1					
25	14	RED. ECC	2 x 1-1/4		STD	12V		250		1415412V		C201504939-1					
26	14	RED. ECC	2 x 1-1/4		STD	685		65		14302685		BGSAG1409010001800					
27	15	RED. ECC	2-1/2 x 1-1/2		STD	543		80		14301543		BGSAG1404300002200					
28	16	RED. ECC	2-1/2 x 2		STD	791		280		15305791		BGSAG1504160005900					
Spe.	Chemical Composition %												Tension Test			Hardness Test	Magnetic Particle Exam.
	C	Si	Mn	P	S	Cu	Ni	Cr	Mo	V	Nb	CE	Yield Strength	Tensile Strength	Elongation		
	X100	X100	X100	X1000	X1000	X100	X100	X100	X100	X1000	X1000	X100	P.S.I	P.S.I	%	HBW	
MIN		10	29										35000	60000	30		
MAX	25		106	50	58	40	40	40	15	80	20	42		95000		197	
24	15	23	84	15	6	7	2	10	2	4	1	32	50315	79895	34	119	Acceptable
25	15	23	84	15	6	7	2	10	2	4	1	32	50315	79895	34	129	Acceptable
26	13	25	126	9	1	5	4	7	2	<10	2	37	43790	66555	38	122	Acceptable
27	18	23	54	9	4	3	5	8	4	<10	<1	30	42050	68585	36	139	Acceptable
28	15	23	125	8	2	2	2	6	1	<10	1	38	41035	65250	37	110	Acceptable
	Visual Examination				Dimensional Inspection				Heat Treatment								
	Acceptable				Acceptable				S R 700°C x 0.5H								

CE = C + Mn/6 + (Cr + Mo + V) / 5 + (Ni + Cu) / 15

MATERIAL CONFORMS TO NACE MR0103-2012/ NACE MR0175-2009 and ISO 15156-2009

We hereby certify that the products described here in have been manufactured and tested in accordance with specifications and also the purchaser's requirements concerned.

NOTE

1. THE QUALITY MANAGEMENT SYSTEM OF ISO 9001-2008 AND PED 97/23/EC, ANNEX I SEC. 4.3 HAVE BEEN APPROVED BY LRQA

2. ANOTHER PED 97/23/EC, ANNEX I SEC. 4.3 TUV-NORD 0045

3. ITEM NUMBER 26 & 28 USE RAW MATERIAL A106 GR.B/ A333 GR.6.

THE MANGANESE ABOVE THE SPECIFIED MAXIMUM WILL BE PERMITTED UP TO A MAXIMUM OF 1.65%. (FOOTNOTE D IN TABLE 1 OF ASTM A234 - 13e1 WPB).

Quality Assurance Section/ Manager

PURCHASER : PROVEEDORA INDUSTRIAL LAREDO S.A DE C.V.
ORDER NO. : RK1322
SPEC. FOR RAW MATERIAL : ASTM A106 Gr. B, ASTM A234 Gr. WPB
SPEC. FOR INSPECTION : ASTM A234 - 13e1 WPB
ASME SA234 - 2013 WPB

JOB NO. : PI1502019

ASME B16.9-2012 / ASME B16.25-2012
BS EN 10204 3.1-2004

CERTIFICATE NO. : Q150518019-07
DATE : MAY. 18, 2015

	PO. Item No.	Product & Size(Inch)				Heat Code		Quantity		Heat No.		Certificate No.					
29	17	RED. ECC	8 x 6	STD	10V		30	1437010V		C201504928-1							
30	7	TEE	3	STD	14V		90	1415414V		C201504946-1							
31	7	TEE	3	STD	909V		414	1426909V		C201504946-1							
32	8	TEE	6	STD	510		104	WF50712510		32120000853007-1							
Spe.	Chemical Composition %												Tension Test			Hardness Test	Magnetic Particle Exam.
	C	Si	Mn	P	S	Cu	Ni	Cr	Mo	V	Nb	CE	Yield Strength	Tensile Strength	Elongation		
	X100	X100	X100	X1000	X1000	X100	X100	X100	X100	X1000	X1000	X100	P.S.I	P.S.I	%	HBW	
MIN		10	29										35000	60000	30		
MAX	25		106	50	58	40	40	40	15	80	20	42		95000		197	
29	16	24	86	12	6	8	2	7	2	2	2	33	42485	64960	35	153	Acceptable
30	14	25	85	14	6	7	3	8	2	4	1	31	47270	70615	35	119	Acceptable
31	14	27	84	18	6	7	3	7	2	4	1	31	42340	67860	36	124	Acceptable
32	12	23	121	11	8	4	2	7	1	2	1	34	45095	62495	37	115	Acceptable
	Visual Examination				Dimensional Inspection				Heat Treatment								
	Acceptable				Acceptable				S R 700°C x 0.5H								

CE = C + Mn/6 + (Cr + Mo + V) / 5 + (Ni + Cu) / 15

MATERIAL CONFORMS TO NACE MR0103-2012/ NACE MR0175-2009 and ISO 15156-2009

We hereby certify that the products described here in have been manufactured and tested in accordance with specifications and also the purchaser's requirements concerned.

NOTE

1. THE QUALITY MANAGEMENT SYSTEM OF ISO 9001-2008 AND PED 97/23/EC, ANNEX I SEC. 4.3 HAVE BEEN APPROVED BY LRQA

2. ANOTHER PED 97/23/EC, ANNEX I SEC. 4.3 TUV-NORD 0045

3. ITEM NUMBER 32 USES RAW MATERIAL A106 GR.B/ A333 GR.6

THE MANGANESE ABOVE THE SPECIFIED MAXIMUM WILL BE PERMITTED UP TO A MAXIMUM OF 1.65%. (FOOTNOTE D IN TABLE 1 OF ASTM A234 -13e1 WPB).


Quality Assurance Section/ Manager