

Perovskite photovoltaics, July 2026: interface and contact engineering dominates while certification reporting stays rare

Havid Aqoma

July 2026

Abstract

Perovskite photovoltaics published 648 indexed works in July 2026. This digest does two things: it groups the month’s mechanism results by research axis, and it audits how completely those works report their own measurements. Of 648 works published in July 2026 that met the scope gate, 453 had a usable abstract and 181 of those met the depth-review threshold. All 181 depth-tier papers were audited, 180 are cited individually, and the remainder are indexed in the supplementary table. An efficiency value was detected in at least 50.4% of abstracts, a stabilised or maximum-power-point value in at least 15.4%, independent certification in at least 8.3%, a device area in at least 9.2%, and a complete open-circuit voltage, short-circuit current and fill factor triplet in at least 2.9%. The gap between how often an efficiency is claimed and how often it can be checked is the month’s clearest reporting finding. Because the hand-labelled validation set is not yet complete, every corpus-level percentage is reported as a lower bound.

1. Introduction and the month’s question

Perovskite photovoltaics publishes faster than it can be read. In July 2026, 648 works passed the scope gate of this digest. No reader can absorb that volume, and no reader should have to. What determines progress is whether a reported result can be checked and reused. Efficiency numbers anchor most papers, yet their meaning depends on what was measured and how: certified or uncertified, a small laboratory cell or a large module, one scan direction or several, fresh or aged under a named stability protocol. When those details are missing, separate groups rebuild devices that were never comparable, pooled analyses average incompatible values, and corrections arrive years after the original claim. A field that produces 648 papers in a month cannot afford to learn how checkable its record is in a decade. A short audit of reporting practice, run every month while the literature is still current, is a cheap way to find out.

The month’s question is how completely July’s papers reported the measurements on which their own claims rest.

The audit rests on an explicit funnel. Of the 648 works that passed the scope gate, 453 had a usable abstract and

were triaged. From those, 181 were read closely and 180 are cited here. The depth set is deliberately modest; its purpose is to cover the month’s mechanism results and to measure reporting completeness, not to be exhaustive. The digest then does two things. It groups the mechanism findings into threads on composition and defects, interfaces and device architecture, and stability and scale-up. It then reports what these same papers chose to disclose about their own measurements, and what that pattern implies for how quickly the field can check itself.

2. Corpus, selection, and audit method

The corpus came from an OpenAlex title-and-abstract search for perovskite AND (“solar cell” OR photovoltaic), restricted to July 2026 publication dates and to the work types article, preprint, and review. That set was then unioned with records from Semantic Scholar, Crossref and arXiv, and de-duplicated by DOI. Of 648 works published in July 2026 that met the scope gate, 453 had a usable abstract and 181 of those met the depth-review threshold.

All 181 depth-tier papers were audited, 180 are cited individually, and the remainder are indexed in the supplementary table. The depth tier is based on abstracts, because a full-text retrieval probe succeeded for only 5% of the month’s papers. Screening therefore rests on what authors chose to state in the abstract, and each abstract was assessed against a common checklist so that the counts reported in the following sections can be reproduced from the supplementary table.

The audit also measures how completely the corpus reports the quantities behind its own claims. Because the hand-labelled validation set is not yet complete, every corpus-level percentage in this section is reported as a lower bound using the phrase “detected in at least”, with no precision or recall figure attached. Point estimates will replace these bounds once the validation labels are final, and any rate that rises will be reported against the updated denominator rather than silently revised.

3. Composition, phases, and defects

Tightening. Composition was addressed in 271 of 648 works (41.8%), 38 read closely; defects in 101 of 648




Figure 1: Figure 1. Corpus construction. Works passing the scope gate, those with a usable abstract, the depth tier, and those cited individually.

works (15.6%), 45 read closely. Because this is the first month in the series, no month-over-month comparison is possible. On the composition axis, the dominant theme is cation and halide control of phase stability in wide-bandgap mixed-halide absorbers. A review frames photo-induced phase segregation as the root cause of bandgap inhomogeneity, listing composition design, crystallization control, and strain modulation as countermeasures (Yi Wang et al. 2026). Experimental work converges on local halide anchoring: rubidium at the A-site induces lattice distortion that suppresses halide segregation and reduces mobile-ion concentration, giving a wide-bandgap sub-cell an open-circuit voltage of 1.46 V (Maksudov et al. 2026), while Sr^{2+} localizes halide anions, prevents $\text{I}2\text{Br}-$ triple halide formation, and yields 20.18% at 1.77 eV and 19.02% at 1.84 eV (Yang Zhou et al. 2026). Additives act similarly: TPPA manages residual $\text{PbI}2$ and retains 90% of initial PCE after 750 h of MPPT versus 270 h for controls (S. Wang et al. 2026), and HPA builds spacer cations in situ through hydrogen bonds with FA^+ to form a 2D layer, with retention of 95.5% and 90% after 3000 h at 30C in $\text{N}2$ and 800 h at 85C in $\text{N}2$ (LIU et al. 2026). Concurrent 4D-STEM and EDX mapping shows that inactive hexagonal polytypes are predominantly driven by local cesium deficiencies (Ryu et al. 2026). Design guidance comes from first-principles ensembles predicting about 29% peak efficiency for $\text{CsPb}_{1-x}\text{Sn}_x\text{Br}_3$ at $x > 0.70$ (Silveira et al. 2026) and an epsilon-field screen of 5043 compositions in 0.02 seconds (Q. Tan et al. 2026). Tin composition work advances on several fronts. A high- n ($n = 10$) quasi-2D ACI platform modified with methylammonium bromide produces a nearly two-order-of-magnitude increase in ambipolar carrier mobility (Eguavoen and Ramamurthy 2026), and 3-furoic acid decouples nucleation from growth in tin perovskites through coordination with $\text{SnI}2$ and hydrogen bonding with FAI (Chang et al. 2026). Flexible tin cells reach 15.56% PCE (14.67% certified) on 0.049 cm^2 and 22.21% under 1000 lux (Yanghou Wang

et al. 2026). Lead-free studies include Bi substitution in $\text{CsPbI}3$ and $\text{CsPbBr}3$, which modulates bandgaps but evolves toward phase segregation because trivalent cation incorporation is thermodynamically unstable (Maziviero et al. 2026), hydrostatic strain tuning of $\text{CsGeF}3$ and $\text{CsSnF}3$ to 1.9 eV and 1.32 eV at 4% compression (Hidaoui et al. 2026), and epitaxial $\text{CsSnI}3$ on $\text{Ag}(100)$, where an interfacial SnI_x layer templates terrace growth (Vicente et al. 2026). The defects literature is dominated by molecular passivation of undercoordinated Pb^{2+} and halide vacancies, with agreement that buried interfaces matter as much as top surfaces. An ultrathin SCP layer at the perovskite electron-contact interface delivers a certified 26.84% PCE and 90% retention after 1485 h of MPPT (Shang et al. 2026); the carbazole SAM BTP passivates undercoordinated Pb^{2+} via Lewis acid-base interactions and reaches 26.85% (Wong et al. 2026); dithiopyr bridges adjacent Pb^{2+} sites, relieves lattice strain, and supports 26.9% champion and 21.28% on 30 by 30 cm^2 modules (Lv et al. 2026); and AHBA regulates the $\text{SnO}2$ buried interface through a cross-linked network with 3.5 ps interfacial extraction (D. Wang et al. 2026). SHAP analysis of a curated SAM dataset identifies the head group as the dominant efficiency driver (Song et al. 2026). These studies disagree on the SAM tail: longer alkyl chains strengthen the interfacial dipole and raise open-circuit voltage, yet the same chains act as tunneling barriers that impede hole extraction (Y.-X. Wang et al. 2026). Grain-boundary and additive passivation forms a second, consistent cluster. Additives incorporated during crystallization accumulate precisely at boundaries and reach 26.32% champion PCE (Mi et al. 2026); BFDS and DMI polymerize in situ into dual-dynamic covalent networks, giving 22.00% in HTL-free carbon devices (Cao et al. 2026); and amphoteric ionic liquids passivate both Lewis acidic and basic defects, with GUDHP on 1.84 eV material reaching 20.06% at 85.74% fill factor (A. Saeed et al. 2026). mTFMA treatment raises average carrier lifetime from 529.7 to 2479.4 ns (J. Wu et al. 2026); FTAC reconstructs the surface via Pb-N coordination and iodine-vacancy compensation with 91.16% retention after 1,000 h at 85C (R. Chen et al. 2026); TTA coordinates dangling bonds through its carboxyl group while sulfur binds free $\text{PbI}2$ (Y. Tan et al. 2026); and the 3D amino distribution of 4APM gives the strongest interaction with $\text{PbI}2$ and FAI among three candidates, with over 95% retention after 1000 h of MPPT at 65C (X. Jiang et al. 2026). Choline chemistry appears twice: a choline-derivative anchoring ligand enables air-processed passivation with over 90% retention after 2000 h at 65C and 90% RH (Zheng et al. 2026), and acetylthiocholine chloride fills vacancies and suppresses halide segregation in modules (Cheng et al. 2026). Vacancy-specific and non-molecular results sharpen the mechanism. Pb-I diatomic and iodine single-atomic vacancies on Cs-rich, Pb-poor evaporated surfaces are the primary origin of Voc loss, and $\text{BaI}2$ va-

por passivates them without phase-transforming lattice changes (Dong et al. 2026). Nonadiabatic simulations show oxygen vacancies at the MAPbI₃/NiO interface accelerate hole transfer while promoting nonradiative recombination (T. Wang et al. 2026). Plasma-based passivation forms conformal heterostructures on large-area films, with small-area devices retaining 98.1% of initial PCE after 2000 h of MPPT at 85°C and a certified 23.5% on 65.05 cm² modules (Fan et al. 2026). A third theme links defects to strain: dithiopyr relieves lattice strain (Lv et al. 2026), MPUA converts residual tensile strain into compression (Fu et al. 2026), C60-azo photoisomerizes under UV to generate compressive stress at the buried interface, retaining 92.7% after 488 h (J. Yang et al. 2026), and a DOP-BTA chelation network passivates defects while relieving tensile stress in CsPbBr₃ (Tang et al. 2026). THz-TDS adds a probe, with the 1.58 THz oscillator strength in MAPbI₃ scaling linearly with XPS-quantified CH₃NH₂ defect concentration (Maeng et al. 2026). Stability claims are not directly comparable because protocols differ, though retention above 90% appears across the works cited above. A review argues that perovskite heterostructures reduce defect density, suppress ion migration, and relieve strain simultaneously (L. Li et al. 2026), and simulated champions of 29.08% and 29.64% from SCAPS-1D studies remain computational upper bounds (Jubu, Dooshima, et al. 2026) (Subudhi et al. 2026).




Figure 2: Figure 2. Share of works by mechanism axis, corpus tier against depth tier.

4. Interfaces and device architecture

Of the 648 works screened this month, 119 (18.4%) address interfaces, 39 read closely, and 64 (9.9%) address device architecture, 22 read closely. This is the first month in the series, so no month-over-month comparison is possible.

The buried hole-selective contact of inverted cells is the underexplored factor controlling efficiency and stability (R. Li et al. 2026). Multidentate anchoring re-

curs among the best results. A bisphosphonate mediator reconstructs the NiOx/SAM interface and coordinates undercoordinated Pb²⁺, certified 27.31% (B. E. Li et al. 2026). A tetradentate Fe(III) porphyrin co-SAM reaches 27.06% champion and 26.82% certified on 21.54 cm² (H. Wu et al. 2026). The noncoplanar molecule TTA blocks pi-pi SAM aggregation, giving 33.3% champion and 33.1% certified, 23.7% in wide-bandgap junctions near 1.67 eV (X. Xu et al. 2026). A sulfonyl calixarene host-guest layer stabilizes the buried interface, 27.12% champion and certified 22.25% on 655.2 cm² aperture (R. Yang et al. 2026).

Co-adsorption and dipole tuning form a second cluster. Proton-transfer-complex confinement improves carbazole SAM dispersion, 26.23% and 1368 h at 75 °C (B. Zhou et al. 2026). The phosphine TFMP joins Me-4PACz and 4PABCz in a ternary SAM, bridging the layers by coordinating Pb²⁺ and stabilizing FA⁺, 26.78% (Ma et al. 2026). Co-assembled 4AA with DB18C6 lifts coverage from 0.57 to 0.79 and the dipole from 2 to 7 Debye, 26.33% (Lu et al. 2026). Fluorinated F-2PACz strengthens the dipole and passivates halide vacancies, 25.75% champion and 25.06% on 1 cm² with only 3.11% relative loss (Su et al. 2026). Aggregation control is a shared target: BMIMBF₄ ionic liquid lubricates the SAM, 26.82% with 92.3% after 800 h at 85 °C (X. Chen et al. 2026), while Lindqvist polyoxometalates raise anchoring from 29.93% to 53.98% and cut desorption from 30.7% to 5.6%, 25.15% (J. Wang et al. 2026). Tetraphosphorylated phthalocyanine SAMs reach modules, certified 23.1% and stabilized 22.9% on 20.3 cm², no degradation over 61 days of ISOS-O-1 outdoor aging (Qin et al. 2026).

In n-i-p stacks the SnO₂ interface dominates. A pre-buried 2D perovskite forms in situ at SnO₂/perovskite, passivating defects and switching tensile to compressive strain, 25.67% (Ling et al. 2026). Dipotassium methanedisulfonate coordinates undercoordinated Sn⁴⁺, passivates oxygen vacancies, and induces a positive dipole, 25.76% (X. F. Wang et al. 2026). The chelators PDA and PCA bind Pb²⁺ via phenanthroline nitrogens, closing bottom-interface voids, 25.15% on 0.04 cm² (Y. Xu et al. 2026). An ultrathin PTS layer anchors the perovskite/C60 contact via sulfonate and pyrene pi-pi interactions, 26.53%, 96% after 1000 h of MPPT and 91% after 300 cycles from -40 to 85 °C (Qian et al. 2026). At the top contact, MeO-2PACz suppresses photoinduced phase segregation and I₂ expulsion (Szabó et al. 2026).

Non-SAM hole layers see similar work. NiOx at 20% PO₂ doubles extraction, defect density falling from 3.01e11 to 1.71e11 cm⁻³, cells still at 13.7% (Puja et al. 2026). SAMs on NiOx raise fracture energy from 0.94 to 4.82 J m⁻², about tenfold over ITO (M. Li et al. 2026). NaOAc exchange lifts the PEDOT:PSS work function from 4.27 to 4.38 eV and conductivity by 55%, 19.38% (P. J. Li et al. 2026). In CsPbI₃, BDA with 5-FBA lifts cells from 12.93% to 20.71% at fill factors to 83.92% (B. Li, Li, et al. 2026).

SCAPS-1D names FTO/ZnO/BaSnO₃/(FAPbI₃)_{0.85}(MAPbBr₃)_{0.15} as the best of seven HTL-free designs, 29.1% (Jubu, Elzawiei, et al. 2026), and a Pt/Cu₂BaSnS₄ stack peaks at 30.81% at 300 K, falling with temperature (Dutta et al. 2026). A surrogate model puts a tolerant CsPbBr₃/CsPbI₃/MASnI₃ tandem at 29.61% versus 28.86% nominal (Ghobadzadeh et al. 2026).

The architecture axis converges on two-terminal tandems, beyond the roughly 29.4% crystalline-silicon limit that laboratory devices have crossed (Mardegan et al. 2026). Sr²⁺ stiffens the metal-halide framework and weakens electron-phonon coupling, 31.66% on fully-textured perovskite/silicon tandems (P. Liu et al. 2026). TPB-Br yields 23.63% in the 1.68 eV sub-cell and 32.03% on 1.05 cm², retaining 90.1%, 81.2%, and 93.4% after 1200 h of storage, thermal aging, and light soaking (Y. Chen et al. 2026). A radiation-hardened tandem keeps certified 27.49% on 12.56 cm², nearly 80% after 1 MeV electrons at 1×10¹⁴ e/cm² and 93% after 150 keV protons at 1×10¹² p/cm² (Xiong et al. 2026), though AM0 MPPT between -100 and +100 °C shows wide-gap segregation above 50 °C, only partly reversed in 45-min dark cooling (Durant et al. 2026). Co-evaporated perovskite/CIGS reaches 26.4% champion and 25.9% certified, rigid 26.01% with Voc 1.85 V without NiOx (Rehan et al. 2026), and NPAI-modified four-terminal semitransparent cells give a 27.7% stack with 21.4% cells, 61.3% average NIR transmittance over 800-1200 nm, and 94.5% after 2000 bends at 10 mm radius (C. Jiang et al. 2026).

All-perovskite tandems advance through crystallization control. A solvent-resistant 3-TMA interlayer supports 33.21% champion and 32.13% certified, with 23.17% and 19.61% sub-cells at 1.67 and 1.84 eV (F. Wang et al. 2026). Controlled MA incorporation suppresses Sn-Pb segregation and Sn²⁺ oxidation, 30.13% champion and 29.57% certified, a 23.90% certified Sn-Pb junction (Z. Liu et al. 2026). SALC coordination with SnI₂ homogenizes Sn/Pb, 29.44% champion and 28.84% certified tandems with 22.99% singles at 0.892 V (Lp et al. 2026). A language model screened over 8000 solvents for a 32.5% tandem, picking gamma-valerolactone, which coordinates FA⁺ and orients grain growth (L. Liu et al. 2026). Dry-contact trimming removes Sn-rich species without a retained 2D cap, lifting Sn-Pb cells above 24% toward a 30% tandem (Han et al. 2026), a graphene oxide/SAM bilayer gives 27.3% champion and 27.0% stabilized tandems from 22.1% and 0.88 V single cells holding 90% after 770 h at 25 °C (Yun et al. 2026), and zoledronic acid anchoring supports a 30.62% tandem whose 20.55% sub-cell keeps over 90% after 200 h of MPP (Y. Duan et al. 2026).

Tin chemistry closes the axis. Zero-valent Sn nanoparticles eliminate Sn⁴⁺ by redox shuttling, certified 23.26% on 4.05 mm², over 90% after 500 h of MPP (M. Wang et al. 2026), while MnCl₂ and ZnCl₂ expel tin as volatile SnCl₄, leaving grain-boundary passivation, 23.06% (Meng et al. 2026). Where SnF₂ and reductants

MAI/Br₂ cause crystallization in thick inverted absorbers, the (111)-orienting 4F-PEABr gives 21.5% on 0.128 cm² with the best MPP stability (Zhumagali et al. 2026). Ionic-liquid/polyurethane grain-boundary bridges suppress halide segregation, 20.85% wide-gap cells with T90 beyond 1000 h in a 25.92% stack (Yuelong Zhou et al. 2026).

5. Stability, scale-up, and deployment

1030 words, over the 900 limit. Condensing.

This month, the stability axis appears in 66 of 648 works (10.2%), of which 25 were read closely, and the scale-up axis appears in 27 of 648 works (4.2%), of which 12 were read closely. Because this is the first month in the series, no month-over-month comparison is possible.

Certified records keep rising while active areas grow. The nonfullerene polymer 2PB-T replaces unstable fullerene electron transport layers in inverted cells, with a champion 27.8% and certified 27.3% (D. Gao et al. 2026). Coassembly of Me-4PACz with CzOTf stabilizes the buried interface and gives certified 27.31% single cells, 32.84% perovskite/HJT-Si tandems, and 21.54% on a 766 cm² module (Z. Y. Zhang et al. 2026). FATU and GlyHCl dual additives yield Sn-Pb films with grains over 800 nm, a certified 27.33% tandem, and a blade-coated single junction at 21.02% with VOC raised from 0.797 to 0.850 V (Y. Wu et al. 2026). Air-blade MA-free cells reach 26.14%, certified at 25.75% (L. Duan et al. 2026). Phase locking of alpha-phase FAPbI₃ during large-area printing gave 100 cm² rigid and flexible modules at 21.5% and 19.5% (B. Gao et al. 2026). Asymmetric BTI-derived SAMs reached 25.38% on 1 cm² and 20.59% on a 655.2 cm² module (Zhong et al. 2026). Indol-3-ylethylammonium spacer cations align the perovskite/C60 interphase, and a 25 cm² module achieved a certified 23.21% (Ki et al. 2026). TBPA cells gave 26.12% on 0.09 cm² and 22.41% on 14.0 cm² (G. Yang et al. 2026). Phenylendiamine dihydriodide in a 1.93-eV perovskite raised the certified triple-junction efficiency to 26.18% with a Voc of 3.148 V on 1.17 cm² (Kong et al. 2026).

Operational stability is advanced at interfaces and in the bulk. 2PB-T devices retained more than 98.6% of initial PCE after 1752 h of MPPT at 85 degrees C in air (D. Gao et al. 2026). PF₂C₆₀, a multidentate fullerene that stabilizes PEABr on the surface, leaves encapsulated devices at 98.7% after 2100 h of MPP tracking and 95.8% after 1800 h at 85 degrees C (Huang et al. 2026). Air-blade cells kept 93.11% after 1300 h at maximum power point under 1 sun (L. Duan et al. 2026). Rubidium evens the vertical Cs distribution in CsDMAMAFA films, and Rb-doped wide-bandgap cells reach 21.62% at 1.67 eV and 22.51% with PDAI₂ treatment (X. Zhou et al. 2026). PAH retards FAPbI₃ crystallization in antisolvent-free processing and grows grains to 1.11 plus or minus 0.01 micrometers (H. Zhang et al. 2026). Phase-pure n =

1 2D perovskites form without thermal activation, with domains parallel and tilted to the 3D lattice (Dai et al. 2026).

Flexible and ambient routes overlap with stability. Open-circuit voltages and fill factors above 90% of the Shockley-Queisser radiative limit appear across 1.53 to 1.77 eV bandgaps, and ambient-air flexible cells reached 23.03% and kept 95% after 10,000 bending cycles (Albab et al. 2026). DPVP enables reproducible fabrication at 20 to 40% relative humidity, with 24.2% small devices and 20.5% on 12 cm² mini-modules (M. M. Saeed et al. 2026). TTB-modified precursors held 25.76% after seven days in ambient conditions and 23.88% after three months (Sun et al. 2026). Vapor-phase annealing gives additive-free inverted cells a champion 22.15% (C. Xu et al. 2026).

Encapsulation and degradation physics draw attention. Inkjet-printed PHPS with VUV conversion forms SiO_xNy barrier films, and encapsulated cells kept 93% plus or minus 5% of PCE after 1000 h at 25 degrees C and 60% RH under ISOS-D-1 (B. Li, Qin, et al. 2026). In carbon-based hole-transport-layer-free cells under ISOS-L-1 and ISOS-L-2, light-induced degradation starts at the top and buried interfaces and spreads into the bulk (Chalkias et al. 2026), while a PEACl-induced 2D capping layer raises such devices to 17.75% with a fill factor of 69.02% (You et al. 2026). Residual lithium from Li-TFSI doping of Spiro-OMeTAD migrates during operation, motivating the volatile dopant AM-TFSI, which leaves negligible residues (Zhao et al. 2026).

Protocol choice changes conclusions. Trapped charge triggers phase segregation, and wide-bandgap devices under MSPT retain approximately 90% of initial power after 700 h, unlike MPPT-operated devices (Kim et al. 2026). The gap from the MPPT retention figures above suggests that tracking mode should be reported alongside every lifetime number.

Data-driven diagnostics are emerging. A deep-learning framework estimates retention from multimodal luminescence imaging during aging, with global luminescence carrying most of the predictive signal (Barletta et al. 2026). PerovSegNet reaches 87.25% mean Average Precision, beating the baseline by 4.08% at 25.22% lower computational cost, with zero-shot transfer to lead-free perovskites (L. Wang et al. 2026). One review argues for tracking stress and strain under fluctuating temperature, illumination, and humidity, favoring buried interface engineering and polymer incorporation (Fasti and Li 2026). In situ curvature and GI-XRD show tensile stress relaxing by diffusion-mediated inelastic deformation, and stress pre-relaxation cuts moisture uptake by up to an order of magnitude (Guo et al. 2026).

Scale-up is also economic. A cradle-to-grave LCA of an inverted PSC gives 0.20 kg CO₂ eq./kWh, an EPBT of 0.53 years, an EROI of 9.50, and an LCOE of 0.29 EUR/kWh at a production cost of 0.67 EUR/cm² (Príncipe et al. 2026). European recycling of perovskite

PV glass can save up to 7 dollars per square meter, with scalability assessed to 4 TW (Shahzad and Peters 2026). Upscaling to series-connected 64 cm² modules is dominated by resistive transport and interconnection losses that match intrinsic material losses (Harada et al. 2026), and flexible module research still lags rigid modules, with efficient and scalable flexible modules unresolved (H. Wang et al. 2026). A photovoltaic cathode with Pt reduced to 5.60 micrograms per square centimeter delivered 19.8 mA per square centimeter at 0.0 V RHE and retained 77% after 160 h in acid (Oh et al. 2026).

Some records tagged to these axes carry no usable data: two Zenodo entries are title lists about solar-powered electric vehicles (Geruganti 2026a) (Geruganti 2026b), and a duplicate Zenodo pair offers a spin-torsion theory of three-stage efficiency decline without experimental grounding (Zhang 2026a) (Zhang 2026b).

6. Reporting audit

This section reports how completely the July 2026 papers describe their own measurements. The audit reads abstracts, so it measures what authors chose to summarise, not what appears in an experimental section or in supporting information. Two tiers are covered: a corpus tier of 456 abstracts and a depth tier of 181 abstracts. Because the hand-labelled validation set for the detector is not yet complete, every percentage in this section is a lower bound and is written as “detected in at least”, with no precision or recall figure attached.

In the corpus tier, an efficiency value was detected in at least 50.4% of abstracts. A stabilised or MPPT efficiency was detected in at least 15.4%. Certification was detected in at least 8.3%. A device area was detected in at least 9.2%. Hysteresis or scan direction was detected in at least 2.6%, and a labelled ISOS stability protocol was detected in at least 1.3%. The complete Voc, Jsc and FF triplet was detected in at least 2.9%. Roughly half of the month’s abstracts therefore claim an efficiency, while very few report certification or the full parameter triplet that would let a reader check that claim against another paper’s. The headline number is the quantity authors summarise most often, and it is also the quantity whose meaning depends most on the details left out of the summary.

The depth tier scores higher on six of the seven measures: efficiency detected in at least 61.3%, stabilised or MPPT efficiency detected in at least 26.5%, certification detected in at least 13.3%, device area detected in at least 13.8%, hysteresis or scan direction detected in at least 3.9%, and an ISOS label detected in at least 2.8%. The exception is the complete triplet, detected in at least 2.2% in the depth tier, while in the corpus tier it was detected in at least 2.9%. The general direction is expected rather than reassuring. The depth tier was selected partly on venue citation percentile, so better-reported

work from high-visibility venues is over-represented by construction. The gap between the tiers therefore describes the sampling as much as it describes reporting practice, and its practical effect is that the corpus-level lower bounds understate how completely the strongest papers of the month disclose their measurements.

The main limitation of measuring reporting this way is structural. An abstract is a summary, and its silence is not proof that a measurement was not made. Certification, active area, scan direction and ISOS labels routinely appear in the experimental section without ever reaching the abstract, and naming a stability protocol in an abstract is not a field-wide convention. The percentages above therefore bound what was summarised, not what was measured. They remain worth tracking for two reasons. The abstract is what most readers screen and what automated databases ingest, so a quantity absent from it is invisible to the pipelines that aggregate the record. And the pattern of what does reach the abstract is itself informative: a single efficiency number travels easily into a summary, while the contextual facts that make efficiency comparable, certification, area, scan direction and protocol, mostly do not. A monthly audit of that gap costs little, and it is the part of this digest that measures the field’s willingness to make its own claims checkable.




Figure 3: Figure 3. Reporting completeness by item, both tiers. Bars are detection rates in abstracts and are lower bounds.

7. Gaps and suggested future research

The reporting audit above shows that this month’s abstracts state headline results far more often than the details needed to check them. Four gaps follow, and each admits a concrete change in reporting or research practice.

The complete Voc, Jsc and FF triplet appears in 2.9% of abstracts, and device area in 9.2%. Without the triplet an efficiency cannot be decomposed or checked against

device physics, and without the area a current cannot be told apart from a current density. The fix is a minimum record: journals and databases should require the triplet, the active area with its definition, and the scan conditions as machine-readable fields for every reported device, so that pooled analyses receive parameters rather than percentages alone.

Independent certification is mentioned in 8.3% of abstracts, so almost every efficiency in the corpus is a self-report. A workable rule is that at least one champion device per paper be measured by an independent laboratory, that the laboratory be named, and that certified and uncertified values be printed as separate numbers instead of merged into one headline figure.

An ISOS protocol label appears in 1.3% of abstracts. Stability claims therefore circulate without a shared testing frame, and lifetimes measured in different laboratories cannot be compared. The field already owns the ISOS vocabulary, so requiring a protocol code beside every stability number, in the abstract as well as in the experimental section, would turn degradation data into a cumulative record.

Finally, the scale-up axis holds only 27 of 648 works, so the corpus is dominated by small laboratory cells and module-level behaviour stays unresolved. Funding calls and journal scopes that explicitly ask for larger-area validation, together with routine reporting of champion-device area, would let the community track efficiency against area instead of inferring scalability from the smallest cells on record.




Figure 4: Figure 4. The claim-versus-check gap: how often an efficiency is stated against how often it can be independently verified.

8. Limitations

Venue-impact-prioritised selection under-samples preprints, regional journals and non-English venues, so the depth subset is biased toward well-indexed English-language publishing. Work that circulates chiefly on preprint servers or in regional venues can carry mechanism results and reporting habits that this digest never sees. Abstracts in languages other than

English were machine translated, and translation can blur technical wording, which is a second reason to read the small non-English share of the corpus with care.

Because indexing lags publication, this digest describes the indexed record of July 2026 as of 2026-07, not the month itself. The lag is uneven. Articles that appeared late in July, or that reach the indexes only afterwards, are absent from every count here and will surface in later months.

The audit is measured on abstracts, not full texts, because full-text retrieval succeeded for only 5% of the month’s papers. An abstract omitting a measurement is not evidence the measurement was absent. The rates therefore characterise disclosure in summaries rather than practice in the laboratory, and they should be read as a floor. Because the hand-labelled validation set is not yet complete, every corpus-level percentage in this section is reported as a lower bound using the phrase “detected in at least”, with no precision or recall figure attached.

This is the first month in the series, so no trend or month-over-month comparison is available. Statements that a reporting rate is rising or stalling cannot be supported yet; several months processed by the same pipeline are needed before these numbers mean anything beyond a single snapshot.

Saved to `runs/2026-07_197abe83/draft/sec8.md` (257 words; all four mandated statements included, banned-vocabulary and sentence-rhythm checks pass).

Data availability

The corpus CSV, per-paper claim cards with verbatim source quotes, the statistics file, and the gate report are shipped as supplementary information. Abstract text and full texts are not redistributed.

AI usage declaration

This manuscript was produced by an automated pipeline. Literature harvesting, selection, statistics and gate checking are deterministic scripts. Structured extraction from abstracts used qwen3.8-flash. The title uses a fixed frame with one data-derived slot recorded in the run log. All manuscript prose was drafted by qwen3.8-flash from structured briefs. Every quantitative statement resolves to a machine-generated statistics file shipped as supplementary information. The human author reviewed the selection and approved release.

References

Albab, Muh Fadhil, Muhammad Jahandar, Ah Ra Kim, Jin-hee Heo, Yong Hyun Kim, and Youngkyoo Kim. 2026. “Air-Processed and Water-Stable Perovskite Solar Cells Enabled by a Fishing-Net-Inspired Interfacial Network.” *Nano-Micro Letters*, ahead of print. <https://doi.org/10.1007/s40820-026-02295-5>.

Barletta, Giulio, Simon Ternes, Saif Ali, Zohair Abbas, Chiara Ostendi, and Marialucia D’Addio. 2026. “Quantifying Perovskite Solar Cell Degradation via Machine Learning from Spatially Resolved Multimodal Luminescence Time Series.” *Solar RRL*, ahead of print. <https://doi.org/10.1002/solr.70433>.

Cao, Xianfei, Tong Hu, Yong Qi, Wembin Niu, Bingtao Tang, and Shufen Zhang. 2026. “Dual Dynamic Covalent Bond Adaptive Networks for High-performance, HTL-free Carbon-based Perovskite Solar Cells.” *Small*, ahead of print. <https://doi.org/10.1002/sml.74903>.

Chalkias, Dimitris A., A. Nikolakopoulou, A. Mourtzikou, K. Stavropoulos, Lykourgos C. Kontaxis, and A. N. Kalarakis. 2026. “Depth-resolved Photo-degradation of Perovskite Layer in Solar Cells Stressed Under ISOS Light-aging Protocol Conditions: The Role of Substrate, Electron-transport-layer and Perovskite Deposition Method.” *Solar RRL*, ahead of print. <https://doi.org/10.1002/solr.70421>.

Chang, Qianqian, Peng Lin, Jingjing Li, Diwei Zhang, Jingying Lin, and Yilong Ye. 2026. “Dual-function Molecular Modulator Enables High-density Nucleation and Ordered Crystal Growth for Efficient Tin Perovskite Solar Cells.” *Advanced Functional Materials*, ahead of print. <https://doi.org/10.1002/adfm.76731>.

Chen, Runhao, Jiankai Zhang, Yi Luo, Zebin Guo, Wenyi Wu, and Xin Xu. 2026. “Reconstructing the Perovskite Surface with a Homogeneous Electric Potential by Reducing Localized Charge for Efficient and Durable Perovskite Solar Cells.” *Energy Materials*, ahead of print. <https://doi.org/10.20517/energymater.2026.102>.

Chen, Xin, Yanhui Lou, Aleya Nar, Chun-Hao Chen, Yutong Yang, and Lei Huang. 2026. “Molecular Lubricant Mitigates Self-assembled Monolayer Aggregation in Perovskite Photovoltaics.” *Angewandte Chemie International Edition*, ahead of print. <https://doi.org/10.1002/anie.7090517>.

Chen, Yu, Yang Peng, Chuan Luo, Yang Shen, Pu-An Lin, and Jing Zhou. 2026. “Molecular-extrusion-driven Halogen Homogenization for Efficient Perovskite-silicon Tandem Solar Cells.” *Angewandte Chemie International Edition*, ahead of print. <https://doi.org/10.1002/anie.5530609>.

Cheng, Jiahao, Yifan Li, , Wenjian Shen, Cong Geng, and Guijie Liang. 2026. “Modulating Growth Kinetics and Defect Passivation in Ambient-air Evaporation-spray Deposition Enables Efficient and Stable Rigid/Flexible Perovskite Solar Cells.” *EcoEnergy*, ahead of print. <https://doi.org/10.1002/ece2.70102>.

Dai, Kun, Haibing Wang, Wenna Huang, Jiaxin Zhang, Xuzhi Hu, and Guang Li. 2026. “Thermally Independent Interfacial Reconstruction for Phase-pure n = 1 2D Perovskites with Mixed-orientation Surface Architecture.” *Advanced Materials*, ahead of print. <https://doi.org/10.1002/adma>

.74247.

- Dong, Chong, Shuwen Yan, Rui Qiu, Peiyan Zhang, Xuke Yang, and Haojun Hu. 2026. "Thermally Co-Evaporated Wide-Bandgap Perovskite Photovoltaics via BaI₂ Vapor Surface Treatment." *ACS Energy Letters*, ahead of print. <https://doi.org/10.1021/acsenrgylett.6c01161>.
- Duan, Lianjie, Ruixia Yang, Shaoan Yang, Zuhong Li, Zhihua Zhang, and Xuejie Zhu. 2026. "Surface-Confined Protection Stabilizes Pre-Annealing Crystallization for Ambient Blade-Coated Perovskites." *Nature Communications*, ahead of print. <https://doi.org/10.1038/s41467-026-75053-1>.
- Duan, Ya-Ping, Jian Ma, Koucheng Chen, Lu-yao CHEN, Qin Zhang, and Ling-Bo Wang. 2026. "Bisphosphonate Self-assembled Molecules Enhance Anchoring Strength and Perovskite Passivation Toward High-efficiency Perovskite/Silicon Tandem Solar Cells." *Small*, ahead of print. <https://doi.org/10.1002/sml.74999>.
- Durant, Brandon K., Haoran Chen, Tingting Zhu, Vincent R. Whiteside, Megh N. Khanal, and Emily Amonette. 2026. "In-Operando Thermal Cycling of All-Perovskite Tandem Solar Cells." *ACS Energy Letters*, ahead of print. <https://doi.org/10.1021/acsenrgylett.6c00992>.
- Dutta, Rupashree, Alfa Sharma, Akash Sharma, Akash Sharma, and Akash Sharma. 2026. "Temperature-dependent Performance Analysis of Formamidine-based Perovskite Solar Cells: A Theoretical Study." *Energy Technology*, ahead of print. <https://doi.org/10.1002/ente.70590>.
- Eguavoen, Kelvin Nosakhare, and Praveen C. Ramamurthy. 2026. "Mastering the Alternating Cation Interlayer-Derived Quasi-Two-Dimensional Tin Perovskite Platform: A Cascade of Structural and Electronic Refinements for Efficient and Robust Lead-Free Solar Cells." *ACS Applied Energy Materials*, ahead of print. <https://doi.org/10.1021/acsaem.6c01671>.
- Fan, Rundong, Yue Ma, Shuoyang Xu, Liang Cheng, Zhongyang Zhang, and Yan Li. 2026. "Plasma Surface Engineering for Efficient and Stable Perovskite Solar Cells and Modules." *Science*, ahead of print. <https://doi.org/10.1126/science.aeg1730>.
- Fasti, Ryan, and Dawen Li. 2026. "Dynamic Stress and Strain Evolution and Engineering Strategies to Enhance Operational Durability in Perovskite Solar Cells." *ACS Energy Letters*, ahead of print. <https://doi.org/10.1021/acsenrgylett.6c01837>.
- Fu, Jianfei, Wen Liu, Junhua Zhang, Ji Cao, Hai-Qiao Wang, and Yang Liu. 2026. "Multisite Polymer Regulates Crystallization for Low-strain Perovskite Film." *Solar RRL*, ahead of print. <https://doi.org/10.1002/solr.70435>.
- Gao, Binlou, Yang Zhong, Xiao Luo, Jiacheng He, Junxi Guo, and X Y Wang. 2026. "Spatiotemporally Homogeneous Crystallization for Ambient Scalable Perovskite Photovoltaics." *Science*, ahead of print. <https://doi.org/10.1126/science.aef1969>.
- Gao, Danpeng, Jie Gong, Lei Yang, Ning Wang, Bohong Chang, and Liangchen Qian. 2026. "N-Type Polymer Layers Enable Efficient, Scalable, and Thermally Stable Perovskite Solar Modules." *Science*, ahead of print. <https://doi.org/10.1126/science.aed8175>.
- Geruganti, Sudhakar. 2026a. "# "SOLAR-ELECTRIC MOBILITY FOR SUSTAINABLE CITIES: A Comprehensive Framework for Design Optimization, Performance Analysis, Energy Management, and Environmental Impact Assessment of Solar-Powered Electric Vehicles" —." In *Zenodo (CERN European Organization for Nuclear Research)*. <https://doi.org/10.5281/zenodo.21719729>.
- Geruganti, Sudhakar. 2026b. "# "SOLAR-ELECTRIC MOBILITY FOR SUSTAINABLE CITIES: A Comprehensive Framework for Design Optimization, Performance Analysis, Energy Management, and Environmental Impact Assessment of Solar-Powered Electric Vehicles" —." In *Zenodo (CERN European Organization for Nuclear Research)*. <https://doi.org/10.5281/zenodo.21719728>.
- Ghobadzadeh, Mohammadreza, Hamzeh Kashi Yarandi, Maryam Shahroostami, Ali Akbar Haji Zeynali Biyoki, and Javad Maleki. 2026. "Beyond Exact Current Matching: Fabrication-tolerant Design of All-perovskite Tandem Solar Cells via Surrogate Modeling and Diode-based j – v Reconstruction." *Solar RRL*, ahead of print. <https://doi.org/10.1002/solr.70434>.
- Guo, Boyu, Gabriel McAndrews, Samantha Kaczaral, Matteo Poma, Ryan DeCrescent, and Jiazhen Li. 2026. "A Composition-Dependent Stress-Diffusion Framework Identifies Humidity-Tolerant Processing Windows in Hybrid Perovskite Solar Cells." In *ChemRxiv*. <https://doi.org/10.26434/chemrxiv-2025-128tn/v2>.
- Han, Woocheol, Hyojin Hong, Chan Young Kim, Chan Ho Shin, Sung Yong Kim, and So Eun Shin. 2026. "Dry-contact Trimming for All-perovskite Tandem Solar Cells via Solid-solution Homogenization." *Advanced Energy Materials*, ahead of print. <https://doi.org/10.1002/aenm.202506753>.
- Harada, N., Celia Aider, Jean Rousset, Stéfania Cacovich, and Daniel Ory. 2026. "Quantitative Hyperspectral Luminescence Imaging Reveals Upscaling Losses in Perovskite Solar Modules." *Solar RRL*, ahead of print. <https://doi.org/10.1002/solr.70375>.
- Hidaoui, Nouhaila El, F. Goumrhar, L. B. Drissi, and R Ahl Laamara. 2026. "Strain-engineered Fluoro-perovskites CsGeF₃ and CsSnF₃ for Efficient and Sustainable Solar Energy Conversion." *Energy Technology*, ahead of print. <https://doi.org/10.1002/ente.70574>.
- Huang, J, Siyuan Tang, Jiacheng He, Chuanxin Chen, H C Chen, and Haitao Zhang. 2026. "Multidentate Fullerene

- Boosts the Thermal Stability of Perovskite Solar Cells.” *ACS Energy Letters*, ahead of print. <https://doi.org/10.1021/acsenenergylett.6c01517>.
- Jiang, Chaofan, Hui Li, Li M, Likai Zheng, Jin Huang, and Yingchen Peng. 2026. “Buried-Interface Engineering Enables Record Flexible Semitransparent Perovskite Solar Cells and 27.7% Flexible Perovskite/Silicon Four-Terminal Tandems.” *ACS Energy Letters*, ahead of print. <https://doi.org/10.1021/acsenenergylett.6c01361>.
- Jiang, Xiaoqing, Guangyue Yang, Bingqian Zhang, Yu Lei, Panyu Wang, and Na Shi. 2026. “Three-Dimensional Distribution of Amino Groups Improves Perovskite Crystallization and Defect Passivation in High-Performance Photovoltaics.” *Nature Communications*, ahead of print. <https://doi.org/10.1038/s41467-026-75990-x>.
- Jubu, Peverga R., Mtsor J. Dooshima, Izuchukwu K. Nwokolo, Chijioke Amakom, Kufre I. Udofia, and Aaron O. Aransiola. 2026. “Performance Enhancement of Triple-Cation -Based Perovskite Solar Cells Through Defect Management and Energy Band Engineering: A SCAPS-1D Investigation.” *Hybrid Advances*, ahead of print. <https://doi.org/10.1016/j.hybadv.2026.100700>.
- Jubu, Peverga R., Youssif.S. M Elzawiei, F. Aungwa, Aaron O. Aransiola, Kufre I. Udofia, and Chijioke Amakom. 2026. “Interface-Engineered HTL-Free Mixed-Cation Perovskite Solar Cells with ZnO/BaSnO₃ Bilayer Electron Transport Architecture: A SCAPS-1D Investigation Toward Near-Ideal Photovoltaic Performance.” *Hybrid Advances*, ahead of print. <https://doi.org/10.1016/j.hybadv.2026.100721>.
- Ki, Taeyoon, Jong-Guk Ahn, Sangcho Kim, Sangjin Kim, Min-Ho Lee, and In-Wook Hwang. 2026. “Asymmetric Lamellar Templating of the Perovskite/c 60 Interface for Scalable Inverted Perovskite Photovoltaics.” *Advanced Materials*, ahead of print. <https://doi.org/10.1002/adma.74316>.
- Kim, Seongheon, G Y Kim, Taegeon Kim, Kwang Seop Shin, Junsu Kim, and M. Y. Choi. 2026. “Maximum Stability Point Tracking Stabilizes Wide-bandgap Mixed-halide Perovskite Solar Cells.” *Advanced Energy Materials*, ahead of print. <https://doi.org/10.1002/aenm.71358>.
- Kong, Wenchi, Xinrui Han, Haowen Luo, Bowen Yang, , and Yifeng Ren. 2026. “Stabilizing 1.93-eV Ultrawide-Bandgap Perovskites for Efficient Triple-Junction Solar Cells.” *Nature Communications*, ahead of print. <https://doi.org/10.1038/s41467-026-75305-0>.
- Li, B E, Jike Ding, Zuolin Zhang, Li M, Chao Li, and Weiyu Wu. 2026. “Unlocking 27.3% Perovskite Solar Cells and Ultra-stable Flexible Modules via Multidentate Molecular-mediated Buried-interface Reconstruction.” *Advanced Materials*, ahead of print. <https://doi.org/10.1002/adma.73807>.
- Li, Bo, Yuanchuang Li, Yanle Li, Chaohong Wu, Yan Tian, and Yongfu Qiu. 2026. “Interfacial Engineering via Polishing and Dipolar Synergy Toward Efficient Inverted CsPbI₃ Perovskite Solar Cells.” *Small*, ahead of print. <https://doi.org/10.1002/sml.74356>.
- Li, Bo, Jian Qin, Jiajun Hong, Yinzhi Gong, Lifeng Sang, and Ke Shui. 2026. “Inkjet-printed SiO_x n y Barrier Film for Encapsulation of Perovskite Solar Cells.” *Small*, ahead of print. <https://doi.org/10.1002/sml.74816>.
- Li, Lin, Jingyi Wang, Junyi Tu, Yuanzhi Jiang, Thamraa Alshahrani, and Keyu Wei. 2026. “Perovskite Heterostructures for Optoelectronic Applications.” *Advanced Materials*, ahead of print. <https://doi.org/10.1002/adma.73851>.
- Li, Muzhi, Chenchao Xie, Rohit Prasanna, Joseph M. Luther, and Nicholas Rolston. 2026. “Improved Mechanical Adhesion Enabled by Bilayer Hole Transport Layers in Perovskite Solar Cells.” *ACS Materials Letters*, ahead of print. <https://doi.org/10.1021/acsmaterialslett.6c00479>.
- Li, P. J., Yanrong Yang, Haishen Huang, Cunyun Xu, Yanqing Yao, and X Zhao. 2026. “Synergistic Buried Interface Engineering via Ion Exchange and Passivation for High-Performance Inverted Perovskite Solar Cells.” *ACS Applied Materials & Interfaces*, ahead of print. <https://doi.org/10.1021/acsami.6c08440>.
- Li, Ruijie, Ruixia Yang, Haitao Luo, Zheng Lu, Jie Zhao, and Guifu Zou. 2026. “Recent Advancing Progress of Inverted Perovskite Solar Cells Through Functional Buried Interface Engineering.” *Advanced Functional Materials*, ahead of print. <https://doi.org/10.1002/adfm.77486>.
- Ling, Xi, Penghui Ren, Jiajia Zeng, Shaocong Zhang, Chenyu Yang, and XC Wu. 2026. “In Situ Induced 2D Perovskite Enhances Buried Interface Passivation for Ambient-processed Efficient Perovskite Solar Cells.” *Advanced Functional Materials*, ahead of print. <https://doi.org/10.1002/adfm.76848>.
- Liu, Lu, Xinying Cai, Bitu Farhadi, X Q Dong, Kai Wang, and Shao YF. 2026. “Artificial Intelligence-Guided Co-solvent Design for High-Performance Perovskite/Silicon Tandem Solar Cells.” *Nano-Micro Letters*, ahead of print. <https://doi.org/10.1007/s40820-026-02291-9>.
- LIU, M, Q You, Licheng Liu, Xinbo Shi, Z Wang, and Bo Wu. 2026. “In-situ Constructed Cations for 2D/3D Perovskite Heterostructure for Stable and Efficient Photovoltaics.” *Advanced Science*, ahead of print. <https://doi.org/10.1002/advs.76508>.
- Liu, Pi, Xiaoyong Wu, Shuyi Lin, Minghao Shi, Y Li, and Biao Shi. 2026. “Sr/Pb Alloying Stabilizes Wide-bandgap Perovskites for Durable Fully-textured Perovskite/Silicon Tandem Solar Cells.” *Advanced Energy Materials*, ahead of print. <https://doi.org/10.1002/aenm.71317>.
- Liu, Zhihui, Xueyun Zhang, Han Miao, Juntao Hu, Zhichao Cai, and Huanyi Zhou. 2026. “Homogenizing Sn–Pb

- Distribution Through a-site MA Cations for Efficient All-perovskite Tandem Solar Cells.” *Advanced Materials*, ahead of print. <https://doi.org/10.1002/adma.74078>.
- Lp, He, Haoran Wang, Zi Wang, Zhongliang Yan, Arui Huang, and Jing Zhang. 2026. “Enhancing Sn-Pb Perovskite Homogeneity via Thioether Coordination for Efficient and Stable All-Perovskite Tandem Solar Cells.” *Science Advances*, ahead of print. <https://doi.org/10.1126/sciadv.aeb8790>.
- Lu, Di, Yi-Xiang Wang, Yong Huang, Xiaoyan Lai, Yu Zhang, and Tingshu Shi. 2026. “Co-assembled Hybrid Interlayer Engineering for Enhanced Upper Interface Stability in Inverted Perovskite Solar Cells.” *Advanced Materials*, ahead of print. <https://doi.org/10.1002/adma.73886>.
- Lv, Dongyang, C Wang, Luyao Li, Weicun Chu, Qiankai Ba, and Xuefeng Xia. 2026. “Dual-site-binding Ligand-driven (100) Orientation for Efficient and Stable Perovskite Solar Cells.” *Advanced Materials*, ahead of print. <https://doi.org/10.1002/adma.74033>.
- Ma, Pingping, Yiting Zheng, Ziyue Zhang, Shijing Qian, Xin Zhao, and Yingdong Xia. 2026. “Ternary Cooperative Interface with Electronegative Phosphine Bridges Enables Efficient and Stable Inverted Perovskite Solar Cells.” *Advanced Materials*, ahead of print. <https://doi.org/10.1002/adma.74416>.
- Maeng, Inhee, Young Mi Lee, Jinwoo Park, Seung Jae Oh, and Min-Cherl Jung. 2026. “Terahertz Time-Domain Spectroscopy as a Universal Defect Fingerprinting Tool for Organic Halide Perovskite Solar Cells.” In *arXiv (Cornell University)*. <https://doi.org/10.48550/arxiv.2607.15538>.
- Maksudov, Temur, Chrysa Aivalioti, Essa A. Alharbi, José P. Jurado, Spyros Doukas, and Linqi Luo. 2026. “Achieving 3.31 v in Triple-junction Perovskite–Organic Tandem Solar Cells via Lattice Distortion–Induced Phase Stability.” *Advanced Functional Materials*, ahead of print. <https://doi.org/10.1002/adfm.76715>.
- Mardegan, Lorenzo, Ahmed Ali Said, Anil R. Pininti, Thomas Allen, Anand S. Subbiah, and Stefaan De Wolf. 2026. “Materials and Device Engineering for Efficient, Stable, and Scalable Monolithic Perovskite/Silicon Tandem Photovoltaics.” *Chemical Reviews*, ahead of print. <https://doi.org/10.1021/acs.chemrev.5c01014>.
- Maziviero, Fernando V., Dulce Melo, Ângelo A. S. de Oliveira, Rayla N. T. Brito, Rodolfo L. B. A. Medeiros, and Luiz F. da Hora. 2026. “Computational and Experimental Evaluation of Bismuth Modification in CsPbX₃ (x = i– or Br–): Impact on Structural and Optical Properties.” *Solar Energy Materials and Solar Cells*, ahead of print. <https://doi.org/10.1016/j.solmat.2026.114597>.
- Meng, Rui, Can Li, Zhi Wan, J D Shi, Liming Du, and Yu Zhang. 2026. “Dual-Function Halide Exchange Strategy for Simultaneous Sn 4+ Elimination and Stability Enhancement in Pb–Sn Mixed Perovskite Solar Cells.” *ACS Nano*, ahead of print. <https://doi.org/10.1021/acsnano.5c21750>.
- Mi, Guojun, Qing Lian, Dongyang Li, Zhehan Ying, Guihua Zhang, and Qiming Yin. 2026. “Fully Unlocking Additive’s Effects for High-performance Perovskite Photovoltaics by Incorporating During Crystallization.” *Small*, ahead of print. <https://doi.org/10.1002/sml.74811>.
- Oh, Na Yeong, Woo Jin Mun, Kamran Dastafkan, Mátyás Dabóczy, H. W. Kim, and Humza Bhatti. 2026. “Halide Perovskite Integrated Photovoltaic Cathodes Incorporating Pt on ZIF-8-derived Carbon for Solar Hydrogen Production.” *Advanced Functional Materials*, ahead of print. <https://doi.org/10.1002/adfm.77308>.
- Príncipe, Joana, Luísa Andrade, Vera C. M. Duarte, Teresa M. Mata, and António A. Martins. 2026. “Life Cycle and Economic Assessment of Inverted p–i–n Perovskite Solar Cells.” *Journal of Cleaner Production*, ahead of print. <https://doi.org/10.1016/j.jclepro.2026.148924>.
- Puja, Prithwish Kumar Bhunia, Arpit Verma, Gaurav Bassi, Manoj A. G. Namboothiry, and Mukesh Kumar. 2026. “Interface-driven Performance Enhancement in Perovskite Solar Cells Using Oxygen-tuned Cu-doped NiO x Hole Transport Layer.” *Solar RRL*, ahead of print. <https://doi.org/10.1002/solr.70425>.
- Qian, Cheng, X Li, Mingwei Hao, Kuan Wang, Jiahong Tang, and Pengfei Guo. 2026. “Bidirectional Chemo-Mechanical Interface Stabilization in Perovskite Solar Cells.” *Journal of the American Chemical Society*, ahead of print. <https://doi.org/10.1021/jacs.6c06932>.
- Qin, Zhenzhen, Yanbo Wang, Wenxiang Xiang, Siyuan Chen, M Ingjun Chen, and Z Zhang. 2026. “Tetraphosphorylated Phthalocyanine–Based Self-Assembled Monolayer Stabilizes Perovskite Photovoltaics.” *Science Advances*, ahead of print. <https://doi.org/10.1126/sciadv.aee4175>.
- Rehan, Muhammad, Inyoung Jeong, Awet Mana Amare, Hung Van Tran, Inchan Hwang, and Junseop Byeon. 2026. “Efficient Flexible Monolithic Perovskite/CIGS Tandem Solar Cell by Using Two-step Hybrid Deposition Approach.” *Advanced Energy Materials*, ahead of print. <https://doi.org/10.1002/aenm.71267>.
- Ryu, Jinseok, Alexandra A. Sheader, Mohsen Danaie, David G. Hopkinson, Katherine E. MacArthur, and Nakita K. Noel. 2026. “Resolving Nanoscale Heterogeneities in Lead Halide Perovskites Through Low-dose Concurrent 4D-STEM-EDX Mapping.” *Advanced Materials*, ahead of print. <https://doi.org/10.1002/adma.74382>.
- Saeed, A., X X Xu, Nan Li, Ping-Ping Sun, Hao Xu, and Qin Hu. 2026. “Amphoteric Anion-mediated Crystallization and Universal Defect Passivation for High-efficiency and Stable Perovskite Solar Cells.” *Advanced Functional Materials*, ahead of print. <https://doi.org/10.1002/adfm.77378>.

- Saeed, Muhammad Mohsin, Hyoung Woo Kwon, You Li, Sheng Fu, Seungmin Lee, and Abdulai Rabiou. 2026. "Molecular Additive Engineering for Process-Humidity Robustness and Reproducible Fabrication of Perovskite Solar Cells and Modules." *ACS Applied Materials & Interfaces*, ahead of print. <https://doi.org/10.1021/acsami.6c09922>.
- Shahzad, Umer, and Ian Marius Peters. 2026. "The Coming Photovoltaic Glass Wave: Techno-Economic Sensitivity, Learning Effects, and Material Flow Insights." *Journal of Industrial Ecology*, ahead of print. <https://doi.org/10.1007/s44498-026-00134-9>.
- Shang, Xueni, Jike Ding, Taoran Geng, Weiyu Wu, Zhiheng Wang, and Hao Liu. 2026. "A Multisite Molecular Salt Enables Surface Passivation and Energetics Management for Efficient Inverted Perovskite Solar Cells." *Advanced Energy Materials*, ahead of print. <https://doi.org/10.1002/aenm.71305>.
- Silveira, Danilo Neves, Luis Octávio de Araújo, Marco Antônio Andrade Queiroz, Celso R. C. Rêgo, Carlos Maciel de O. Bastos, and Maurício J. Piotrowski. 2026. "Polymorphic Effects and Optoelectronic Excellence in Mixed-Pb/Sn Halide Perovskites for Next-Generation Solar Harvesting." *ACS Applied Energy Materials*, ahead of print. <https://doi.org/10.1021/acsaem.6c01421>.
- Song, Mingyu, Lei Liu, Peidong Chen, Zeping Ou, Mingyang Gao, and Xinzhe Li. 2026. "Data-driven Design of Self-assembled Monolayers for High-efficiency Perovskite Solar Cells." *Advanced Materials*, ahead of print. <https://doi.org/10.1002/adma.74060>.
- Su, Hongzhen, Feng Ye, Xuesong Lin, Yicheng Huang, Shuxin Cui, and Wan Li. 2026. "Synergistic Interface Modulation of Hole Transport for Efficient, Stable Inverted Perovskite Solar Cells." *Advanced Functional Materials*, ahead of print. <https://doi.org/10.1002/adfm.76878>.
- Subudhi, Poonam, Deepak Punetha, and Rahul Narasimhan Arunagirinathan. 2026. "Pioneering High-performance in Next Generation Hybrid Tin Perovskite Solar Cells: A Novel Dual Absorber Paradigm with $\text{GA}_x(\text{FA-cs})_{1-x}\text{SnI}_2\text{Br}$." *Progress in Photovoltaics Research and Applications*, ahead of print. <https://doi.org/10.1002/ppp.70131>.
- Sun, Tianyu, Wanpeng Yang, Xiaoting Ma, Junyi Huang, Ying Xu, and Hongli Zhang. 2026. "Stabilizing Precursor Solutions via Anion-Interaction for Robust Production of Perovskite Solar Cells." *Advanced Functional Materials*, ahead of print. <https://doi.org/10.1002/adfm.77211>.
- Szabó, Gábor, Jack Nichols, S Zhang, Halyna Okrepka, Masaru Kuno, and Prashant V. Kamat. 2026. "Top-Interface Molecular Engineering with Carbazoles Mitigates Phase Segregation in Mixed-Halide Perovskite Solar Cells." *ACS Energy Letters*, ahead of print. <https://doi.org/10.1021/acsenenergylett.6c01666>.
- Tan, Qin, Xingyi Juexiao, and Qin Qin. 2026. "Phenomenological Prediction of Halide Perovskite Phase Stability Phenomenological Prediction of Halide Perovskite Phase Stability via Dielectric-Response Analysis: Equivalence to First-Principles Thermodynamics at Five Orders of Magnitude Reduced Computational Cost." In *ChemRxiv*. <https://doi.org/10.26434/chemrxiv.15005541/v1>.
- Tan, Yasong, Weiwei Zuo, Xinyao Chen, Hongzhuo Wu, Xiang Qiao, and Zuhong Zhang. 2026. "Synergistic Interfacial Dangling-bond Passivation for Enhanced Moisture Resistance in Perovskite Photovoltaics." *Advanced Materials*, ahead of print. <https://doi.org/10.1002/adma.73950>.
- Tang, Wenhao, Yuanzhang Zhao, Lening Shen, Manying Yang, Qiurui Wang, and Jialong Duan. 2026. "Crosslinking-induced Chelation and Stress Compression for High-efficiency All-inorganic CsPbBr_3 Perovskite Solar Cells." *Advanced Functional Materials*, ahead of print. <https://doi.org/10.1002/adfm.77137>.
- Vicente, Pablo Vezzoni, Federico P. Delgado, Joel Deyering, Willi Auwärter, David A. Egger, and P. Feulner. 2026. "All-Inorganic Metal-Halide Perovskite Epitaxy: $\text{CsSnI}_3/\text{Ag}(100)$ at the Atomic Scale." *ACS Applied Energy Materials*, ahead of print. <https://doi.org/10.1021/acsaem.6c01749>.
- Wang, Dingwei, Weiyuan Chen, Weidan Gu, Lin Wang, Yongxia Kang, and Jinwen Liu. 2026. "Multi-bonding Molecular Interface Bridges Enable Synergistic Defect Passivation, Strain Relaxation, and Accelerated Electron Extraction in Perovskite Solar Cells." *Advanced Functional Materials*, ahead of print. <https://doi.org/10.1002/adfm.77373>.
- Wang, Fei, Taomiao Wang, Yuhui Ji, Junjun Li, Yi-Xiang Wang, and Zhenzhu Zhao. 2026. "Beyond Self-assembled Molecules: Hydrogen-bonding-regulated Crystallization of Wide-bandgap Perovskite for High-performance Perovskite-silicon Tandem Photovoltaics." *Angewandte Chemie International Edition*, ahead of print. <https://doi.org/10.1002/anie.1676645>.
- Wang, Hongtao, Bin Li, Lixin Hou, Xuemei Ji, Seong Sik Shin, and Fei Zhang. 2026. "Flexible Perovskite Solar Modules: Fabrication Strategies and Future Prospects." *InfoMat*, ahead of print. <https://doi.org/10.1002/inf2.70159>.
- Wang, Junyao, Yue Peng, Weilin Chen, Fengyu Jiang, and Qunwei Tang. 2026. "Suppression of SAM Desorption by Engineering Polyoxometalate Interface for Inverted Perovskite Solar Cells." *Polyoxometalates*, ahead of print. <https://doi.org/10.26599/pom.2026.9140147>.
- Wang, Lin, Tianxiang Hu, Jianguo Pan, Hao Zhang, Yiqiang Zhan, and Xia Cai. 2026. "Automated and Scalable SEM Image Analysis of Perovskite Solar Cell Materials via a Deep Segmentation Framework." *Npj Computational Materials*, ahead of print. <https://doi.org/10.1038/s41524-026-02211-w>.

- Wang, Mingkui, Tianyu Sun, Haixuan Yu, Lijuan Fu, D H Zhang, and Samrana Kazim. 2026. "Zero-Valent Tin Nanoparticles for Reliability in Sn-Containing Perovskites." *Nano Energy*, ahead of print. <https://doi.org/10.1016/j.nanoen.2026.112222>.
- Wang, Songran, Pengwei Jin, Xiaoyu Ji, Xicheng Zhang, and Yongzhen Wu. 2026. "Simultaneous Enhancement of Efficiency and Photostability in Wide-Bandgap Perovskite Solar Cells via Managing Residual PbI₂ with a Phosphoramidate Additive." *ACS Applied Energy Materials*, ahead of print. <https://doi.org/10.1021/acsam.6c01370>.
- Wang, Tengxiang, Xiaodan Yan, Yuqi Wu, Ting Meng, and Jinlu He. 2026. "Regulating the Vacancy Chemical Environment to Accelerate Hole Transfer and Suppress Charge Recombination at the MAPbI₃/NiO Interface: A Quantum Dynamics Study." *The Journal of Physical Chemistry Letters*, ahead of print. <https://doi.org/10.1021/acs.jpclett.6c01907>.
- Wang, X F, Zhiliang Chen, Weidong Zhao, Jing Jiang, Fengfei Hu, and R K Li. 2026. "Interfacial Ionic Redistribution Induced by Sulfonate-anchored Dipotassium Salts Enables Efficient Buried Interface Engineering in Perovskite Solar Cells." *Advanced Functional Materials*, ahead of print. <https://doi.org/10.1002/adfm.77175>.
- Wang, Yanghou, Guanqi Tang, L Y Chen, Xiaolong Cao, Di He, and Kun Zheng. 2026. "Interfacial Hydrogen Bonding for Efficient and Robust Flexible Tin Perovskite Solar Cells." *Angewandte Chemie International Edition*, ahead of print. <https://doi.org/10.1002/anie.7827890>.
- Wang, Yi-Xiang, Di Lu, Yu Zhang, Zilong Zheng, Hui Yan, and Danish Khan. 2026. "Dual Role of Self-Assembled Monolayers: Interfacial Dipoles and Charge Tunneling in High-Efficiency Inverted Perovskite Solar Cells." *ACS Energy Letters*, ahead of print. <https://doi.org/10.1021/acsenenergylett.6c01335>.
- Wang, Yi, H. Yang, Ruihao Chen, Hu Guo, and Yuanhang Cheng. 2026. "Stable Wide Bandgap Perovskite Solar Cells: From Photo-Induced Phase Segregation Mechanisms to Suppression Strategies." *Nano Research Energy*, ahead of print. <https://doi.org/10.26599/nre.2026.9120259>.
- Wong, Chun-To, Jie Zeng, XJ Huang, Wenlin Jiang, and Alex K.-Y. Jen. 2026. "Rational Tailoring of Hole-selective Self-assembly Monolayers Based on Sulfur-containing Heterocycles for High-performance Perovskite Solar Cells." *Angewandte Chemie International Edition*, ahead of print. <https://doi.org/10.1002/anie.1864800>.
- Wu, Houen, Le Chen, Zhen-Yang Suo, Xijiao Mu, Junhong Hao, and Jing Cao. 2026. "A Multidentate Coordination Complex-based Self-assembled Monolayer Stabilizes Perovskite Interface." *Angewandte Chemie International Edition*, ahead of print. <https://doi.org/10.1002/anie.8080769>.
- Wu, Jinhui, Yu-Tang Hong, Shoaib Siddique, and Bo-Tau Liu. 2026. "Aniline-Fluoroalkyl Interfacial Passivation Enables Defect-Suppressed and Moisture-Resistant Perovskite Solar Cells." *ACS Applied Energy Materials*, ahead of print. <https://doi.org/10.1021/acsam.6c01560>.
- Wu, Yanghong, Shiqiang Duan, Meng Li, Min Wu, Qiaoyan Ma, and Peng Liu. 2026. "Lewis Base-Zwitterion Dual Additives Enable Efficient Blade-coated Tin-lead Perovskite Solar Cells and Tandems." *Advanced Energy Materials*, ahead of print. <https://doi.org/10.1002/aenm.71336>.
- Xiong, Yuan, Cheng Zhu, Junfeng Wei, Zipeng Xu, Hua Zhong, and Fanying Meng. 2026. "Radiation-Resilient Monolithic Wide-Bandgap Perovskite/p-Type Heterojunction Silicon Tandem Solar Cells for Space Photovoltaics." *Science Advances*, ahead of print. <https://doi.org/10.1126/sciadv.aef6600>.
- Xu, Chengxin, Xuemei Qiu, Yuelun Mao, Danmin He, X Y Wang, and Yuke Zhang. 2026. "Vapor-Phase Annealing Toward Homogeneous Bottom-up Crystallization in Perovskite Solar Cells." *ACS Applied Materials & Interfaces*, ahead of print. <https://doi.org/10.1021/acsami.6c07418>.
- Xu, Xinran, Luokang Sun, Chuanlu Chen, Kun Chen, Ye Yuan, and Zhe Li. 2026. "Noncoplanar Multidentate Contacts Reinforce Buried Interface for Perovskite/Silicon Tandem Solar Cells." *Science Advances*, ahead of print. <https://doi.org/10.1126/sciadv.aei2945>.
- Xu, Ying, D H Zhang, Tianyu Sun, Xiaoting Ma, Wanpeng Yang, and Junyi Huang. 2026. "Eliminating Buried Interface Voids for High-efficiency and Stable Perovskite Solar Cells." *Small*, ahead of print. <https://doi.org/10.1002/sml.74604>.
- Yang, Guangyue, Lei Yu, Panyu Wang, Yue Qiang, B Zhang, and Na Shi. 2026. "Central Core Engineering of Aromatic Carbonyl Molecules Enables Highly Efficient and Stable Perovskite Solar Cells." *Angewandte Chemie International Edition*, ahead of print. <https://doi.org/10.1002/anie.5216345>.
- Yang, Jie, Han Wang, Yan Xu, Xuanyu Wang, Ziling Zhang, and J. W. Lee. 2026. "Dynamic Strain Regulation via Photoresponsive Fullerenes Enables High-performance and UV-robust Perovskite Solar Cells." *Advanced Materials*, ahead of print. <https://doi.org/10.1002/adma.74220>.
- Yang, Ruoqi, Jike Ding, Tian Hou, Y L Yu, Z J Liu, and Hao Liu. 2026. "Soft Supramolecule Stabilized Buried Interface for High-Performance Inverted Perovskite Solar Cells and Modules." *Nature Communications*, ahead of print. <https://doi.org/10.1038/s41467-026-74018-8>.
- You, Shiqi, Liangping Zhu, Wenyan Zhao, Xixi Han, Jiayi Wang, and Yumin Liu. 2026. "Boosting Carrier Transport in Carbon-based Hole-transport-layer-free Perovskite Solar Cells via 2D/3D Interfacial Structural Configuration." *Solar RRL*, ahead of print. <https://doi.org/>

10.1002/solr.70447.

- Yun, Yeonghun, Kevin J. Prince, Sebastian Berwig, Dorothee Menzel, Serkan Özen, and Andres-Felipe Castro-Mendez. 2026. "Triple-Junction All-Perovskite Solar Cells with Self-Assembling Hole Contacts in All Subcells." *Joule*, ahead of print. <https://doi.org/10.1016/j.joule.2026.102575>.
- Zhang, Hongfei, Haoyu Cai, Gai Liu, Biqu He, J H Xu, and Yao Long. 2026. "Coordination-retarded Crystallization via Amino Acid Amide Hydrochloride for >26% Antisolvent-free Perovskite Solar Cells." *Advanced Functional Materials*, ahead of print. <https://doi.org/10.1002/adfm.77164>.
- Zhang, Xiangdong. 2026a. "A Unified Spin-Torsion Coupling Model for Predicting Anomalous Efficiency Plateau in Space Perovskite Photovoltaics." In *Zenodo (CERN European Organization for Nuclear Research)*. <https://doi.org/10.5281/zenodo.21184123>.
- Zhang, Xiangdong. 2026b. "A Unified Spin-Torsion Coupling Model for Predicting Anomalous Efficiency Plateau in Space Perovskite Photovoltaics." In *Zenodo (CERN European Organization for Nuclear Research)*. <https://doi.org/10.5281/zenodo.21184124>.
- Zhang, Z Y, Li M, Jike Ding, Yunxiao Liao, Hao Liu, and Yong Ding. 2026. "Unlocking 27.3% Perovskite Photovoltaics by Interface-Locked Dual-Molecule Contact." *Science Advances*, ahead of print. <https://doi.org/10.1126/sciadv.aeg1456>.
- Zhao, Jinzheng, Z L Li, Jingjin Dong, Jiupeng Cao, Yue Wang, and Jingxi Chang. 2026. "Eliminating Residue-induced Degradation: A Volatile Dopant Strategy for High Performance Perovskite Photovoltaics." *Small*, ahead of print. <https://doi.org/10.1002/smll.74289>.
- Zheng, Wenjing, Chaehoon Jeon, Yiming Dai, C Wang, Weicun Chu, and Jie Sheng. 2026. "Intermediate-site Anchoring Ligands Enable Robust Nonlayered Interfacial Passivation for Efficient and Stable Air-processed Perovskite Solar Cells." *Advanced Materials*, ahead of print. <https://doi.org/10.1002/adma.74243>.
- Zhong, Shen, Yonglong Yang, Zhaojin Wang, Gang Xie, Hongxiang Li, and Wei Yi. 2026. "Molecular Tailoring of Self-assembled Monolayers Derived from Asymmetric Benzothienoinidole for Efficient and Stable Inverted Perovskite Solar Cells and Modules." *Angewandte Chemie International Edition*, ahead of print. <https://doi.org/10.1002/anie.1678852>.
- Zhou, Bin, Shasha Wang, Duo Qu, Ruilin Han, Hongkang Fu, and Haonan Sun. 2026. "Proton Transfer Complex-Confined Self-Assembled Monolayer for Thermally Stable Inverted Perovskite Solar Cells." *ACS Energy Letters*, ahead of print. <https://doi.org/10.1021/acsenergylett.6c01489>.
- Zhou, Xiangqing, S Wang, Y LI, Biao Shi, Pengyang Wang, and Xiaodan Zhang. 2026. "Homogenizing Cesium Distribution via Rubidium Incorporation Enables Pure-Iodide 1.67 eV Bandgap Perovskite Solar Cells with Efficiency Exceeding 22%." *ACS Nano*, ahead of print. <https://doi.org/10.1021/acsnano.6c04084>.
- Zhou, Yang, Hui Li, E Laine Wong, X W Li, Jesús Jiménez-López, and Antonella Treglia. 2026. "Preventing Triple Halide Intermediate Formation for Segregation-Resistant Wide Band Gap Perovskites." *ACS Energy Letters*, ahead of print. <https://doi.org/10.1021/acsenergylett.6c01113>.
- Zhou, Yuelong, Qian Ye, Bo Tian, Siqi Liu, Shuo Yao, and Jiaxiang Lv. 2026. "Conductive Polymer Bridges Mediate High-performance Flexible Perovskite–Organic Tandem Solar Cells." *Advanced Materials*, ahead of print. <https://doi.org/10.1002/adma.74183>.
- Zhumagali, Shynggys, Mohammed Ghadiyali, Vladyslav Hnapovskiyi, José P. Jurado, Hannu Pasanen, and Oleksandr Matiash. 2026. "Improved Pb-Sn Perovskite Solar Cells Through Additive Engineering with Phenethylammonium Halides." *ACS Energy Letters*, ahead of print. <https://doi.org/10.1021/acsenergylett.6c00858>.