

V A L M I N - KEIVITSA (Seos)

=====

Koe n:o	Vaihe	Syöte	Mylly	(1)Kuulat (2)Tangot Kg	Jauhatus min	pH	H2SO4 kg/t	Ca(OH)2 kg/t	KEX g/t	NAX g/t	CuSO4 g/t	Dekstriini g/t	CMC g/t	Flotanol C-7 g/t	Dowfroth 250 g/t	Vaahd. rpm	Vaahd. min
100		-1 mm	Norm.	(1) 8 kg	20	5,0	10,8			750					210	1800	10+9+8+6
101		-1 mm	Norm.	(1) 8 kg	20	6,0	5,5			750					210	1800	8+6+5+5
102		-1 mm	Norm.	(1) 8 kg	20	Luont.				750					30	1800	6+5+5+5
103A		-1 mm	Norm.	(1) 8 kg	20	11,5		1,3	750						30	1800	6+5+5+5
103	1	-1 mm	Norm.	(1) 8 kg	20	11,2		1,3	90				100		15	1800	5+3
"	2					10,0	0,3		20		100				30	1800	8
"	3					5,5	5,4		100						30	1800	5
104		-1 mm	Norm.	(1) 8 kg	40	5,0	13,0			750					300	1800	10+9+8+6
105		-1 mm	Norm.	(1) 8 kg	40	6,0	6,7			750					240	1800	9+6+5+6
106		-1 mm	Norm.	(1) 8 kg	40	Luont.				750			100		60	1800	7+6+6+6
107		-1 mm	Norm.	(1) 8 kg	40	11,5		1,5	750				100		30	1800	6+5+5+5
108		-1 mm	Norm.	(1) 8 kg	60	5,0	15,2			750					300	1800	10+8+8+7
109		-1 mm	Norm.	(1) 8 kg	60	Luont.				750					60	1800	7+6+6+6
110		-1 mm	Norm.	(1) 8 kg	60	Luont.				750			100		75	1800	7+6+6+6
Murske	Magn.erot Seulonta	-1 mm EM															

V A L M I N - KEIVITSA (Seos)

=====

Koe n:o	Vaihe	Syöte	Myllä	(1)Kuulat (2)Tangot Kg	Jauhatus min	pH	H2SO4 kg/t	Ca(OH)2 kg/t	KEX g/t	NAX g/t	Hostaflot X231 g/t	Dekstriini g/t	CMC g/t	Flotanol c-7 g/t	Dowfroth 250 g/t	Vaahd. rpm	Vaahd. min
Kokeen n:o 111 alku tehty samasta jauhatuksesta, KR2 kahtioitu																	
111/1	EV	-1 mm	Mergan	(1) 22 kg	120	5,0	15,8			200					45	2600	20
	KV1	ER				5,5	0,2			50						1500	11
	KV2	KR1				5,5										1500	10
	KV3	KR2				12,0		0,51				100				1050	11
	Magn.erotus	KR3															
111/2	EV	-1 mm	Mergan	(1) 22 kg	120	5,0	15,8			200					45	2600	20
	KV1	ER				5,5	0,2			50						1500	11
	KV2	KR1				5,5										1500	10
	KV3	KR2	Norm.	(1) 8 kg	15	12,0		1,08				100				1050	9
	KV4	KR3				12,0		0,33								1050	7
	KV5	KR4				12,0		0,41								1050	5
112		-1 mm	Norm.	(1) 8 kg	90	5,0	18,2			750					300	1800	11+8+7+6
113	1	-1 mm	Norm.	(1) 8 kg	60	11,5		1,12			30		100		15	1800	3+5
	2					5,0	14,3			100					120	1800	21
114		-1 mm	Norm.	(1) 8 kg	60	Luont.				750			200	30	60	1800	9+7+7+7
115	EV1-3	-1 mm	Norm.	(1) 8 kg	40	11,0		1,2			40		200		15	1800	4+4+4
	KV1	ER1-3				9,3					2		30			1050	7
	EV4-6	EJ3	Norm.	(1) 8 kg	20	5,0	13,8			100					60	1800	5+5+8
116	EV1+2	-1 mm	Norm.	(1) 8 kg	60	11,5		1,58	150			100	100		15	1800	5+3
	CuKV1	ER1+2				11,9		0,34	30				30			1050	6+4
	EV3+4	EJ2				5,0	14,2			300				120	90	1800	16+8
	NiKV1	ER3+4				5,5	0,1			50			50	45		1050	10+7
	Magn.erotus	NiKR1															

V A L M I N - KEIVITSA (Seos)

Koe n:o	Vaihe	Syöte	Mylly	(1)Kuulat (2)Tangot Kg	Jauhatus min	pH	H2SO4 kg/t	Ca(OH)2 kg/t	KEX g/t	NAX g/t	Na2SO3 kg/t	Dekstriini g/t	CMC g/t	Flotanol C-7 g/t	Dowfroth 250 g/t	Vaahd. rpm	Vaahd. min
Kokeen n:o 117 alku tehty samasta jauhatuksesta, KR2 kahtioitu																	
117/1	EV	-1 mm	Mergan	(1) 22 kg	120	5,0	15,0			200					45	2600	20
	KV1	ER				5,5	0,2			50						1500	11
	KV2	KR1				5,5				30			100			1500	10
	KV3	KR2				11,7		0,33			3,0	100			3	1050	11
117/2	EV	-1 mm	Mergan	(1) 22 kg	120	5,0	15,0			200					45	2600	20
	KV1	ER				5,5	0,2			50						1500	11
	KV2	KR1				5,5				30			100			1500	10
	KV3	KR2	Norm.	(1) 8 kg	15	12,0		0,4			3,0	100			3	1050	11
Kokeen n:o 118 alku tehty samasta jauhatuksesta, KR2 kahtioitu																	
118/1	EV	-1 mm	Mergan	(1) 22 kg	120	5,0	15,8			200					45	2600	22
	KV1	ER				5,5	0,2			50						1500	12
	KV2	KR1				5,5				30			100			1500	10
	KV3	KR2	Norm.	(1) 1,5 kg	20	11,8		0,35	30		4,5	100		30		1050	25
118/2	EV	-1 mm	Mergan	(1) 22 kg	120	5,0	15,8			200					45	2600	22
	KV1	ER				5,5	0,2			50						1500	12
	KV2	KR1				5,5				30			100			1500	10
	KV3	KR2	Norm.	(1) 1,5 kg	20	11,9		0,35	40		6,0	100		30		1050	26
Kokeen n:o 119 alku tehty samasta jauhatuksesta, KR2/EM kahtioitu																	
119/1	EV	-1 mm	Mergan	(1) 22 kg	80	5,0	14,4			200					54	2700	22
	KV1	ER				5,5	0,11			50					1	1500	12
	KV2	KR1				5,5				30			100			1500	10
	Magn.erotus	KR2															
	KV3	KR2/EM				11,5		0,18	20		3,0	100		6		1050	19
119/2	EV	-1 mm	Mergan	(1) 22 kg	80	5,0	14,4			200					54	2700	22
	KV1	ER				5,5	0,11			50					1	1500	12
	KV2	KR1				5,5				30			100			1500	10
	Magn.erotus	KR2															
	KV3	KR2/EM				11,5		0,09	20		1,5	100		6		1050	19

V A L M I N - K E I V I T S A (S e o s)

Koe n:o	Vaihe	Syöte	Myllä	(1)Kuulat (2)Tangot Kg	Jauhatus min	pH	H2SO4 kg/t	Ca(OH)2 kg/t	KEX g/t	NAX g/t	Na2SO3 kg/t	Dekstriini g/t	CMC g/t	Flotanol C-7 g/t	Dowfroth 250 g/t	Vaahd. rpm	Vaahd. min
Kokeen n:o 120 alku tehty samasta jauhatuksesta, KR2 kahtioitu																	
120/1	EV	-1 mm	Mergan	(1) 22 kg	80	5,0	13,4			200					57	2700	23
	KV1	ER				5,5	0,2			50					1	1500	12
	KV2	KR1				5,5				30			100			1500	10
	KV3	KR2				11,5		0,19	20		4,5	100		6		1050	19
120/2	EV	-1 mm	Mergan	(1) 22 kg	80	5,0	13,4			200					57	2700	23
	KV1	ER				5,5	0,2			50					1	1500	12
	KV2	KR1				5,5				30			100			1500	10
	KV3	KR2				11,5		0,17	20		6,0	100		6		1050	19
Kokeen n:o 121 alku tehty samasta jauhatuksesta, KR2 kahtioitu																	
121/1	EV	-1 mm	Mergan	(1) 22 kg	80	5,0	12,3			NIBX 200					57	2700	23
	KV1	ER				5,5	0,1			50					1	1500	12
	KV2	KR1				5,5				30			100			1500	10
	KV3	KR2	Norm.	(1)1,5 kg	20	11,8		0,35	35		4,5	200		48	12	1050	24
121/2	EV	-1 mm	Mergan	(1) 22 kg	80	5,0	12,3			200					57	2700	23
	KV1	ER				5,5	0,1			50					1	1500	12
	KV2	KR1				5,5				30			100			1500	10
	KV3	KR2	Norm.	(1)1,5 kg	20	11,8		0,35	60		6,0	200		60	12	1050	28
Kokeen n:o 122 alku tehty samasta jauhatuksesta, KR2 kahtioitu. KV3:ssa pot.säätö CuK -250 mV, vaahdotus typellä																	
122/1	EV	-1 mm	Mergan	(1) 22 kg	80	5,0	13,4			200					57	2700	23
	KV1	ER				5,5	0,2			50					1	1500	12
	KV2	KR1				5,6				30			100			1500	10
	KV3	KR2	Norm.	(1)0,5 kg	20	12,0		0,35	60		6,0	200		6		1050	18
122/2	EV	-1 mm	Mergan	(1) 22 kg	80	5,0	13,4			200					57	2700	23
	KV1	ER				5,5	0,2			50					1	1500	12
	KV2	KR1				5,6				30			100			1500	10
	KV3	KR2	Norm.	(1)0,5 kg	20	12,0		0,35	60		6,0	300		6		1050	18

Lite 4e

V A L M I N - KEIVITSA (R713 , R725 ja R333)

[illegible]