

COMFORT SA SLAB 80

Ref. No: S-TDS-053-80

High performance Slabs for Building insulation

Excellent thermal insulation

Thermal conductivity (λ) of **0.0350** (W/m.K) provides excellent thermal performance reducing heat loss for residential and commercial buildings.

Excellent acoustic insulation

COMFORT SA Slabs provides optimal acoustic performance for better comfort.

Effective fire protection

COMFORT SA Slabs are non-combustible and classified as A1 Euro-class Reaction to fire.

COMFORT SA SLAB 80

Characteristic	Symbol	Unit	Quantities and measured Values	Standard
Description	KIMMCO ISOVER stone wool products are made from volcanic rock – a natural material present in large quantities throughout the earth. These raw materials are natural basalt and dolomite coming from Saudi Arabia, our product is compliance with ASTM C612 and EN 13162 standard.			
Mean Thermal Conductivity	λ	(W /m·K)	0.0350 at mean temperature 24 °C	EN 12 667 ASTM C518 ASTM C177
Bulk Density	ρ	(Kg/m^3)	80	EN 1602
Thickness	T	(mm)	35	EN 823 ASTM C303
Facing	-	-	Unfaced	
Reaction to Fire Class (Unfaced)	-	-	Euro-class A1 Non-combustible	EN 13501-1 ASTM E136
Surface Burning Characteristics -Flame Spread - Smoke Developed	-	-	≤ 25 ≤ 50	ASTM E84
Water VapourSorption	-	(%)	< 1 by volume	ASTM C1104
Water Vapour Diffusion	μ	-	~1	EN 12 086
Specific Thermal Capacity	c	(KJ/ Kg.K)	~1	EN 10 456 ASTM C518
Shot Contents	-	(%)	≤ 25% from the weight	ASTM C612
Maximum Service Temperature Max. (Fiber) Max. (Facing)	-	°c	+750	ASTM C411
Miscellaneous Delivery Forms	Our products are supplied in polyethylene packing. As mentioned in the MSDS product should be stored in a dry conditions.			

ThThe technical information corresponds to our present state of knowledge and experience at the date of printing (see imprint). But no legal guarantee can be given unless it has been explicitly agreed. The state of experience and knowledge is developing continuously. Please see to it that you always use the latest edition of this information. The described product applications do not take special circumstances in consideration. For further information, please contact our team. We deliver only according to our terms of trade and terms of delivery.

www.siimco.com.sa