Nitoproof 30

constructive solutions

Rubberised bitumen emulsion

Uses

Nitoproof 30 is a cold applied rubberised bitumen for use as a damp proof membrane in sandwich construction, as a general purpose waterproofer for walls, floors and other structures, and as a vapour seal. It is also an effective adhesive and bonding agent for insulation boards, expanded polystyrene, cork panels etc. Nitoproof 30 can also be used to fill cracks in concrete and asphalt up to 5 mm wide.

Advantages

- Single component.
- Water based - non toxic.
- Rubberised.
- Non-flammable.
- Resists attack by chloride and sulphate ions.
- Can be applied to green concrete.

Standard compliance

Nitoproof 30 complies with concrete curing requirements of ASTM C309-93 when applied at a rate of 1.25 m^2 per litre.

Description

Nitoproof 30 is a rubber reinforced bitumen emulsion. The emulsion is dark brown in colour and dries to form a black flexible coating.

Technical support

Fosroc offers a comprehensive range of high performance, high quality repair, maintenance and construction products. In addition, Fosroc offers a technical support package to specifiers, end-users and contractors, as well as on-site technical assistance in locations all over the world.

Properties

Drying time (approx.):	3 hours at 20ºC, 1 hour at 35ºC
Over-coating time:	3 ½ hours minimum
Solids content:	50 - 55 %

Note: These times will be extended under conditions of low temperature and high humidity.

Specification clause

Rubberised bitumen emulsion waterproofer.

The below ground concrete surfaces shall be water proofed with Nitoproof 30, a rubberised bitumen emulsion. Two coats shall be applied each at a rate of 2 m^2 per litre providing a total dry film thickness of 500 microns. The two coats shall be applied at right angles to each other.

Application instructions

Surface preparation

All surfaces must be clean, dry and free from dirt, dust, oil and grease. All loosely adhering particles such as rust, scale, cement laitance etc. should be removed. All organic growth should be removed using a fungicidal wash, followed by thorough washing with clean water.

Application

Nitoproof 30 should be applied by brush or squeegee to prepared surfaces. Stir well before use, replace lid when not in use. Soak up any spillage with sand or sawdust and wash down surface immediately.

Damp proof membrane and vertical vapour barrier

Apply Nitoproof 30 at the rate of 2 m^2 per litre per coat to a dry film thickness of approximately 500 microns. Two coats should be applied, allowing the first coat to dry completely before applying the second. The second coat should be applied at right angles to the first. All applications should be continued up verticals to the existing damp proof course. Ensure the membrane is not punctured or damaged during subsequent operations. Where the surface is to receive a render or plaster finish, a keyed surface should be formed by gritting the second coat of Nitoproof 30 with clean, dry sand. Allow a minimum of 48 hours drying period before plastering, rendering, or laying floor screed.

Flooring adhesive

Nitoproof 30 is a very effective waterproof adhesive for laying wood blocks, cork, asphalt and asbestos tiles. The surface should be clean, sound and smooth and the Nitoproof 30 should be applied to the screed with a notched trowel. Leave for a short period until the Nitoproof 30 becomes tacky, then the tiles should be pressed into place. Contamination of the upper surface of the tile should be cleaned off immediately with a clean cloth.

Follow any special recommendations made by the tile manufacturer carefully.

Nitoproof 30

Adhesive for insulation

Nitoproof 30 is suitable for bonding insulation materials such as expanded polystyrene, fibreboard and cork slabs onto walls and floors. The two surfaces to be bonded must be clean, level and free from all points of contact. Nitoproof 30 should be applied to both surfaces and allowed to become tacky (colour beginning to change from brown to black). The two surfaces should then be pressed together, using maximum pressure.

Note: Nitoproof 30 is not a structural adhesive, and mechanical fixing should also be used where appropriate.

Crack sealing

Nitoproof 30 is suitable for reinstating surfaces with leaks due to surface porosity or crazing and it may be used to seal cracks up to 5 mm wide. Nitoproof 30 should be poured into the prepared cracks and allowed to dry. It may be necessary to 'top-up' the cracks after full cure.

Repairs

Damaged areas of Nitoproof 30 can be readily over-coated to restore the continuity of the membrane.

Cleaning

Nitoproof 30 can be removed with clean water. Once the Nitoproof 30 has dried, it can only be removed with Fosroc Solvent 102.

Limitations

Application should not commence if the temperature is below 6ºC or above 45ºC. Nitoproof 30 is water based and remains soluble until thoroughly dry. It is therefore important that it should not be applied during rain or when rain is expected.

Estimating

Supply

Nitoproof 30:	18 and 200 litre drums

Coverage

5.3 m^2 per litre per coat at 100 microns dry film thickness depending upon substrate porosity and smoothness.

Storage

Shelf life

Minimum 12 months if stored below 35ºC in the original unopened containers.

Storage conditions

Nitoproof 100 will have a minimum shelf life of 12 months if stored in normal warehouse conditions between 15 and 35°C. Protect from temperatures below 10°C. Store away from direct sources of heat or naked flames.

Precautions

Health and safety

Some people are sensitive to resins and solvents, so gloves and a barrier cream, Kerodex Anti-Solvent, Rozalex Anti-paint, Debba-Wet work or similar, should be used when handling these products. Remove contamination from skin with soap and water or a resin-removing cream such as Kerocleanse standard grade skin cleanser or Rozaklens Industrial Skin Cleanser. Follow by washing with soap and water. **Do not use Solvent.** The use of goggles is recommended but should accidental eye contamination occur, wash thoroughly with plenty of water and seek medical treatment immediately.

Fire

Fosroc Solvent 102 is flammable. Ensure adequate ventilation. Do not use near a naked flame and do not smoke during use.

Flash point

Fosroc Solvent 102:	33ºC

For further information, refer to the Product Material Safety Data Sheet.

Important note
Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard Conditions for the Supply of Goods and Service. **All Fosroc datasheets are updated on a regular basis. It is the user's responsibility to obtain the latest version.**

Fosroc Jordan
P.O Box 253,
King Abdullah II Industrial Estate
Sahab 11512, Jordan
www.fosroc.com

Head Office / Khalda Showroom
Telephone: +962 6 535 9562 **Fax**.: +962 6 535 9563 **Email**: enquiryjordan@fosroc.com

Sahab Factory **Tel**: +962 6 402 2665 **Fax**: +962 6 402 7985

Distributors:
Iraq, Zam Zam Land LLC. **Tel**: +964 772 5555151 **Email**: enquiry.iraq@fosroc.com
Palestine, Omari Group Intl. Co. **Tel**: +970 2 2986829 **Email**: enquirypalestine@fosroc.com