

Duct covers (hardwood)	Natural
Concrete steps, ramps and aprons	Natural
Internal walls (painted)	Stone
Internal walls (tiled)	White eggshell
Ceilings	Light grey
Cills (tiled)	White eggshell
External walls (painted)	Cream sandtex
External walls (tyrolean)	Cream cullamix
Internal doors	Satin white
Kicking and push strips	Matte black
Door frames	Clear varnish
Aluminium	Satin silver anodised
GRP	Stone

Table 1-4: Surface Preparations.

All metals shall be high pressure washed to remove deposits of grease, oil, tar and other residues.

Material	Surface Preparation
Wood	Not applicable
a. Cabinet finish	Sand wood using 180 grit paper. Fill all holes, treat knots, sand to flat and smooth finish. Sand intercoating surfaces using 400 grit wet and dry paper.
b. Gloss or matt paint finish or varnish	
Mild Steel & Ductile Iron for low build coatings.	Sand blast to SA2 ¹ / ₂ to 25 to 35 microns profile