

01300 of the specification. These shall comprise but not necessarily be limited to:

2. Proposals for filling, testing and emptying of water retaining/ excluding concrete structures.
3. Proposals for repairing any leakage in accordance with the requirements of Section 03600 of the specification.

#### **14.1.5 Water**

- A Water used for testing shall be potable or irrigation water as agreed with the Engineer.

#### **14.1.6 Repair Materials**

- A Materials for repairing any leaks or damp areas shall be in accordance with the requirements of Section 03600 of the specification.

### **14.2 Part 2 Products**

Not Applicable

### **14.3 Part 3 Execution**

#### **14.3.1 General**

- A Testing shall be in accordance with the requirements of BS EN 1992 and this section of the specification.

#### **14.3.2 Cleaning**

- A All water retaining/excluding structures shall on completion, be carefully cleaned to the complete satisfaction of the Engineer.
- B All structures shall first be pumped dry and cleaned of all debris. The structure shall then be brushed down on all internal faces with a stiff broom while still dry and swept clean.
- C All associated pipe work shall be cleaned in accordance with the relevant specification requirements.

#### **14.3.3 Test Preparation**

- A General
  1. Testing shall not be undertaken until written approval has been obtained from the Engineer.
  2. Filling shall not take place earlier than 28 days after the casting of the final sections of the structure, unless otherwise agreed by the Engineer.
  3. In the case of structures which are sub-divided into individual tanks, each individual