

1 Variables

2 root

	var	symbol	documentation	type	units	eqs
10	$F_{N,A}$	F	basic directed graph incidence matrix	network		
48	$I_{N,A}$	I_N_A	project node on arc	projection		
96	I_N	I_N	vector of ones of length nodes	projection		
97	I_A	I_A	vector of ones of length arcs	projection		
7	Δt	t_interval	time interval	frame	<i>s</i>	5
6	t^e	te	time end	frame	<i>s</i>	4
4	t	t	time	frame	<i>s</i>	
5	t^o	to	time zero	frame	<i>s</i>	3
9	Δ	pulse	pulse of length time interval	frame		7
8	0.5	onehalf	numerical one half	constant		6
3	0	zero	numerical value zero	constant		2
1	#	value	numerical value	constant		
2	1	one	numerical one	constant		1

3 physical

	var	symbol	documentation	type	units	eqs
98	I_S	I_S	vector of ones of length sepecies	projection		
11	ℓ_N	l	length	frame	m	
13	r_{yN}	r_y	y-direction	frame	m	9
12	r_{xN}	r_x	x-direction	frame	m	8
14	r_{zN}	r_z	z-direction	frame	m	10
15	V_N	V	fundamental state - volume	state	m^3	11
25	C_N	C	fundamental state - charge	state	$A s$	
23	A_N	A	Helmholts energy	state	$kg m^2 s^{-2}$	17
16	U_N	U	fundamental state - internal energy	state	$kg m^2 s^{-2}$	
24	G_N	G	Gibbs free energy	state	$kg m^2 s^{-2}$	18
22	H_N	H	Enthalpy	state	$kg m^2 s^{-2}$	15
17	S_N	S	fundamental state - entropy	state	$kg m^2 K^{-1} s^{-2}$	
18	$n_{N,S}$	n	fundamental state - molar mass	state	mol	
34	R_N	R	Gas constant	constant	$kg m^2 mol^{-1} K^{-1} s^{-2}$	25
33	B_N	Boltz	Boltzmann constant	constant	$kg m^2 K^{-1} s^{-2}$	24
32	A^v	Av	Avogadro number	constant	mol^{-1}	
19	T_N	T	temperature	effort	K	16
35	U^e_N	Ue	electrical potential – voltage	effort	$kg m^2 A^{-1} s^{-3}$	26
20	p_N	p	pressure	effort	$kg m^{-1} s^{-2}$	13
21	$\mu_{N,S}$	chemPot	chemical potential	effort	$kg m^2 mol^{-1} s^{-2}$	14 88
27	v_{xN}	v_x	velocity in x-direction	secondaryState	ms^{-1}	19
29	v_{zN}	v_z	velocity in z-direction	secondaryState	ms^{-1}	21
28	v_{yN}	v_y	velocity in y-direction	secondaryState	ms^{-1}	20

4 reactions

	var	symbol	documentation	type	units	eqs
113	$P_{N,K}$	P_N_K	what node has what reaction	projection		
114	$T_{N,K}$	T_K	temparature of the nodes with reactions	effort	K	99
129	$\bar{n}_{N,S,K}$	cn_NK	normed concentration – context node and conversion	secondaryState		113
128	$\bar{n}_{N,S}$	cn	normed concentration	secondaryState		112
131	$\phi_{N,K}$	interactionProbability	probability for the species to meet to undergo reaction	properties		115
118	$N_{S,K}$	N	stoichiometric matrix	properties		
115	$E_{a,N,K}$	Ea	Arrhenius activation energy	properties	$kg\,m^2\,mol^{-1}\,s^{-2}$	100
130	$N_{N,S,K}$	N_NKS	stoichiometric matrix – context nodes	properties		114
116	K^o_K	Ko	Arrhenius frequency factor – a strange construction	properties	$m^{-3}\,mol^{-1}\,s^{-1}$	101
126	$c^n_{N,S}$	c_norming	norming concentration used in the definition of the species interaction probability	properties	$m^{-3}\,mol$	110
117	$K_{N,K}$	K	raction "constant"	properties	$m^{-3}\,mol^{-1}\,s^{-1}$	102

5 material

	var	symbol	documentation	type	units	eqs
50	k_{yA}^c	kc_y_A	convective mass conductivity in y-direction in arc	property	$m^{-1} s$	40
45	k_{yN}^c	kc_y	convective mass conductivity in y-direction	property	$m^{-1} s$	36
63	$k_z^{d,Fick}{}_{A,S}$	kd_z_Fick	Fick's diffusivity in arc and z-direction	property	ms^{-1}	53
89	ρ_A	density_A	density of arc material	property	$kg m^{-3}$	78
60	v_S	v	molar volume of species	property	$m^3 mol^{-1}$	50
39	k_{yN}^q	kq_y	thermal conductivity in y-direction	property	$kg K^{-1} s^{-3}$	30
61	$k_x^{d,Fick}{}_{A,S}$	kd_x_Fick	Fick's diffusivity in arc and x-direction	property	ms^{-1}	51
62	$k_y^{d,Fick}{}_{A,S}$	kd_y_Fick	Fick's diffusivity in arc and y-direction	property	ms^{-1}	52
59	ρ_N	density	density	property	$kg m^{-3}$	49
55	k_{xA}^q	kq_x_A	thermal conductivity in x-direction in arc	property	$kg K^{-1} s^{-3}$	45
49	k_{xA}^c	kc_x_A	convective mass conductivity in x-direction in arc	property	$m^{-1} s$	39
43	$k_{zN,S}^d$	kd_z	diffusional mass conductivity in z-direction	property	$kg^{-1} m^{-4} mol^2 s$	34
41	$k_{xN,S}^d$	kd_x	diffusional mass conductivity in x-direction	property	$kg^{-1} m^{-4} mol^2 s$	32
38	k_{xN}^q	kq_x	thermal conductivity in x-direction	property	$kg K^{-1} s^{-3}$	29
54	$k_{zA,S}^d$	kd_z_A	diffusional mass conductivity in z-direction in arc	property	$kg^{-1} m^{-4} mol^2 s$	44
26	λ_S	Mm	species' molecular mass	property	$kg mol^{-1}$	
42	$k_{yN,S}^d$	kd_y	diffusional mass conductivity in z-direction	property	$kg^{-1} m^{-4} mol^2 s$	33
40	k_{zN}^q	kq_z	thermal conductivity in z-direction	property	$kg K^{-1} s^{-3}$	31
46	k_{zN}^c	kc_z	convective mass conductivity in z-direction	property	$m^{-1} s$	37
52	$k_{xA,S}^d$	kd_x_A	diffusional mass conductivity in x-direction in arc	property	$kg^{-1} m^{-4} mol^2 s$	42
53	$k_{yA,S}^d$	kd_y_A	diffusional mass conductivity in y-direction in arc	property	$kg^{-1} m^{-4} mol^2 s$	43
57	k_{zA}^q	kq_z_A	thermal conductivity in z-direction in arc	property	$kg K^{-1} s^{-3}$	47
47	$h_{N,S}$	h	partial molar enthalpies	property	$kg m^2 mol^{-1} s^{-2}$	38

Continued on next page

	var	symbol	documentation	type	units	eqs
58	m_N	m	mass	property	kg	48
36	C_{pN}	Cp	total heat capacity at constant pressure	property	$kg\,m^2\,K^{-1}\,s^{-2}$	27
37	C_{vN}	Cv	total heat capacity at constant volume	property	$kg\,m^2\,K^{-1}\,s^{-2}$	28
56	k_{yA}^q	kq_y_A	thermal conductivity in y-direction in arc	property	$kg\,K^{-1}\,s^{-3}$	46
44	k_{xN}^c	kc_x	convective mass conductivity in x-direction	property	$m^{-1}\,s$	35
51	k_{zA}^c	kc_z_A	convective mass conductivity in z-direction in arc	property	$m^{-1}\,s$	41
107	$h_{AA,S}$	h_A	partial molar enthalpies of transport system	property	$kg\,m^2\,mol^{-1}\,s^{-2}$	93
102	$\mu_{N,S}^o$	chemPot_o	standard chemical potential	effort	$kg\,m^2\,mol^{-1}\,s^{-2}$	86

6 macroscopic

	var	symbol	documentation	type	units	eqs
86	d_A	d	flow direction of convective flow	transport		75
91	\dot{V}_A	fV	volumetric flow	transport	$m^3 s^{-1}$	80
101	$\hat{n}_{A,S}^d$	fnd	diffusional mass flow in arc	transport	$mol s^{-1}$	85 89
93	$\dot{n}_{N,S}^c$	anc	accumulation due to convective mass flow	transport	$mol s^{-1}$	82
105	\dot{H}_N^w	aw	accumulation due to work flow – instantiate	transport	$kg m^2 s^{-2}$	91
83	\hat{q}_{xA}	fq_x	heat flow in arc and x-direction	transport	$kg m^2 s^{-3}$	72
92	$\hat{n}_{A,S}^c$	fnc	convective mass flow in an arc	transport	$mol s^{-1}$	81
87	$c_{A,S}$	c_A	concentration in convective mass flow	transport	$m^{-3} mol$	76
111	\dot{H}_N^c	aHc	enthalpy accumulation due to convective mass flow	transport	$kg m^2 s^{-3}$	97
84	\dot{q}_N	aq	accumulation due to conductive heat flow	transport	$kg m^2 s^{-3}$	73
104	$\dot{n}_{N,S}^d$	and	accumulation due to diffusional mass transfer	transport	$mol s^{-1}$	90
109	\hat{H}_A^c	fHc	enthalpy flow due to convective mass flow	transport	$kg m^2 s^{-3}$	95
110	\hat{H}_A^d	fHd	enthalpy flow due to diffusive mass flow	transport	$kg m^2 s^{-3}$	96
112	\dot{H}_N^d	aHd	enthalpy accumulation due to diffusive mass flow	transport	$kg m^2 s^{-3}$	98
70	A_{yzA}	A_yz_A	cross sectional area yz of arc	geometry	m^2	59
66	A_{xzN}	A_xz	cross sectional area xz	geometry	m^2	55
69	A_{xzA}	A_xz_A	cross sectional area xz of arc	geometry	m^2	58
68	A_{xyA}	A_xy_A	cross sectional area yz of arc	geometry	m^2	57
65	A_{xyN}	A_xy	cross sectional area xy	geometry	m^2	54
67	A_{yzN}	A_yz	cross sectional area yz	geometry	m^2	56
64	$D_{N,A}$	D	difference operator	differenceOperator		
85	$c_{N,S}$	c	molar concentration	secondaryState	$m^{-3} mol$	74
100	$x_{N,S}$	x	concentration mole fraction	secondaryState		84

Continued on next page

	var	symbol	documentation	type	units	eqs
99	n^t_N	nt	total amount	secondaryState	<i>mol</i>	83

7 macroscopic-material

	var	symbol	documentation	type	units	eqs
103	$_x_{N,S}$	$_x$	link variable x to interface macroscopic »> material	get		87

8 reactions–macroscopic

	var	symbol	documentation	type	units	eqs
120	$_K_{N,K}$	$_K$	link variable K to interface reactions »> macroscopic	get	$m^{-3} mol^{-1} s^{-1}$	104
123	$_T_{N,K}$	$_T_K$	link variable T K to interface reactions »> macroscopic	get	K	107
122	$_N_{S,K}$	$_N$	link variable N to interface reactions »> macroscopic	get		106
119	$_E^a_{N,K}$	$_Ea$	link variable Ea to interface reactions »> macroscopic	get	$kg\,m^2\,mol^{-1}\,s^{-2}$	103
121	$_K^o_K$	$_Ko$	link variable Ko to interface reactions »> macroscopic	get	$m^{-3} mol^{-1} s^{-1}$	105

9 macroscopic-reactions

	var	symbol	documentation	type	units	eqs
125	<code>_c_{N,S}</code>	<code>_c</code>	link variable c to interface macroscopic »> reactions	get	$m^{-3} mol$	109

10 material–macroscopic

	var	symbol	documentation	type	units	eqs
73	$_{k_z^c A}$	$_{kc_z_A}$	link variable kc z A to interface material »> macroscopic	get	$m^{-1} s$	62
72	$_{k_y^c A}$	$_{kc_y_A}$	link variable kc y A to interface material »> macroscopic	get	$m^{-1} s$	61
30	$_{\lambda_S}$	$_{Mm}$	link variable Mm to interface material »> macroscopic	get	$kg mol^{-1}$	22
79	$_{k_z^{d,Fick} A,S}$	$_{kd_z_Fick}$	link variable kd z Fick to interface material »> macroscopic	get	ms^{-1}	68
81	$_{k_y^q A}$	$_{kq_y_A}$	link variable kq y A to interface material »> macroscopic	get	$kg K^{-1} s^{-3}$	70
74	$_{k_x^d A,S}$	$_{kd_x_A}$	link variable kd x A to interface material »> macroscopic	get	$kg^{-1} m^{-4} mol^2 s$	63
77	$_{k_y^d A,S}$	$_{kd_y_A}$	link variable kd y A to interface material »> macroscopic	get	$kg^{-1} m^{-4} mol^2 s$	66
106	$_{h_{N,S}}$	$_{h}$	link variable h to interface material »> macroscopic	get	$kg m^2 mol^{-1} s^{-2}$	92
90	$_{\rho_A}$	$_{density_A}$	link variable density A to interface material »> macroscopic	get	$kg m^{-3}$	79
76	$_{k_y^{d,Fick} A,S}$	$_{kd_y_Fick}$	link variable kd y Fick to interface material »> macroscopic	get	ms^{-1}	65
71	$_{k_x^c A}$	$_{kc_x_A}$	link variable kc x A to interface material »> macroscopic	get	$m^{-1} s$	60
75	$_{k_x^{d,Fick} A,S}$	$_{kd_x_Fick}$	link variable kd x Fick to interface material »> macroscopic	get	ms^{-1}	64
78	$_{k_z^d A,S}$	$_{kd_z_A}$	link variable kd z A to interface material »> macroscopic	get	$kg^{-1} m^{-4} mol^2 s$	67
88	$_{\rho_N}$	$_{density}$	link variable density to interface material »> macroscopic	get	$kg m^{-3}$	77

Continued on next page

	var	symbol	documentation	type	units	eqs
80	$_{k_x^q A}$	<code>_kq_x_A</code>	link variable kq x A to interface material »> macroscopic	get	$kg\ K^{-1}\ s^{-3}$	69
82	$_{k_z^q A}$	<code>_kq_z_A</code>	link variable kq z A to interface material »> macroscopic	get	$kg\ K^{-1}\ s^{-3}$	71
108	$_{h_{A,S}}$	<code>_h_A</code>	link variable h A to interface material »> macroscopic	get	$kg\ m^2\ mol^{-1}\ s^{-2}$	94

11 Equations

12 Generic

no	equation	documentation	layer
1	$1 := \text{Instantiate}(\#, \#)$	numerical one	root
2	$0 := \text{Instantiate}(\#, \#)$	numerical value zero	root
3	$t^o := \text{Instantiate}(t, 0)$	time zero	root
4	$t^e := \text{Instantiate}(t, \#)$	time end	root
5	$\Delta t := \text{Instantiate}(t, \#)$	time interval	root
6	$0.5 := \text{Instantiate}(\#, \#)$	numerical one half	root
7	$\Delta := \text{sign}(t - t^o) - \text{sign}(t - (t^o - \Delta t))$	pulse of length time interval	root
8	$r_{xN} := \text{Instantiate}(\ell_N, \#)$	x-direction	physical
9	$r_{yN} := \text{Instantiate}(\ell_N, \#)$	y-direction	physical
10	$r_{zN} := \text{Instantiate}(\ell_N, \#)$	z-direction	physical
11	$V_N := r_{xN} \cdot r_{yN} \cdot r_{zN}$	volume	physical
13	$p_N := \frac{\partial U_N}{\partial V_N}$	pressure	physical
14	$\mu_{N,S} := \frac{\partial U_N}{\partial n_{N,S}}$	chemical potential	physical
15	$H_N := U_N - p_N \cdot V_N$	Enthalpy	physical
16	$T_N := \frac{\partial U_N}{\partial S_N}$	temperature	physical
17	$A_N := U_N - T_N \cdot S_N$	Helmholts energy	physical

Continued on next page

no	equation	documentation	layer
18	$G_N := U_N + p_N \cdot V_N - T_N \cdot S_N$	Gibbs free energy	physical
19	$v_{xN} := (t)^{-1} \cdot r_{xN}$	velocity in x-direction	physical
20	$v_{yN} := (t)^{-1} \cdot r_{yN}$	velocity in y-direction	physical
21	$v_{zN} := (t)^{-1} \cdot r_{zN}$	velocity in z-direction	physical
24	$B_N := \text{Instantiate}(S_N, \#)$	Boltzmann constant	physical
25	$R_N := A^v \cdot B_N$	Gas constant	physical
26	$U_N^e := (C_N)^{-1} \cdot U_N$	electrical potential – voltage	physical
27	$C_{pN} := \frac{\partial H_N}{\partial T_N}$	total heat capacity at constant pressure	material
28	$C_{vN} := \frac{\partial U_N}{\partial T_N}$	total heat capacity at constant volume	material
29	$k_{xN}^q := (V_N)^{-1} \cdot C_{pN} \cdot v_{xN}$	thermal conductivity in x-direction	material
30	$k_{yN}^q := (V_N)^{-1} \cdot C_{pN} \cdot v_{yN}$	thermal conductivity in y-direction	material
31	$k_{zN}^q := (V_N)^{-1} \cdot C_{pN} \cdot v_{zN}$	thermal conductivity in z-direction	material
32	$k_{xN,S}^d := (\mu_{N,S})^{-1} \cdot \left(v_{xN} \cdot \left((V_N)^{-1} \cdot \frac{\partial U_N}{\partial \mu_{N,S}} \right) \right)$	diffusional mass conductivity in x-direction	material
33	$k_{yN,S}^d := (\mu_{N,S})^{-1} \cdot \left(v_{yN} \cdot \left((V_N)^{-1} \cdot \frac{\partial U_N}{\partial \mu_{N,S}} \right) \right)$	diffusional mass conductivity in y-direction	material
34	$k_{zN,S}^d := (\mu_{N,S})^{-1} \cdot \left(v_{zN} \cdot \left((V_N)^{-1} \cdot \frac{\partial U_N}{\partial \mu_{N,S}} \right) \right)$	diffusional mass conductivity in z-direction	material
35	$k_{xN}^c := \left(\lambda_S \star (\mu_{N,S})^{-1} \right) \cdot (V_N)^{-1} \cdot \frac{\partial U_N}{\partial p_N} \cdot v_{xN}$	convective mass conductivity in x-direction	material

Continued on next page

no	equation	documentation	layer
36	$k_{yN}^c := \left(\lambda_S \star (\mu_{N,S})^{-1} \right) \cdot (V_N)^{-1} \cdot \frac{\partial U_N}{\partial p_N} \cdot v_{yN}$	convective mass conductivity in y-direction	material
37	$k_{zN}^c := \left(\lambda_S \star (\mu_{N,S})^{-1} \right) \cdot (V_N)^{-1} \cdot \frac{\partial U_N}{\partial p_N} \cdot v_{zN}$	convective mass conductivity in z-direction	material
38	$h_{N,S} := H_N \cdot (n_{N,S})^{-1}$	partial molar enthalpies	material
39	$k_{xA}^c := I_{N,A} \star k_{xN}^c$	convective mass conductivity in x-direction in arc	material
40	$k_{yA}^c := I_{N,A} \star k_{yN}^c$	convective mass conductivity in y-direction in arc	material
41	$k_{zA}^c := I_{N,A} \star k_{zN}^c$	convective mass conductivity in z-direction in arc	material
42	$k_{xA,S}^d := I_{N,A} \star k_{xN,S}^d$	diffusional mass conductivity in x-direction in arc	material
43	$k_{yA,S}^d := I_{N,A} \star k_{yN,S}^d$	diffusional mass conductivity in z-direction in arc	material
44	$k_{zA,S}^d := I_{N,A} \star k_{zN,S}^d$	diffusional mass conductivity in z-direction in arc	material
45	$k_{xA}^q := I_{N,A} \star k_{xN}^q$	thermal conductivity in x-direction in arc	material
46	$k_{yA}^q := I_{N,A} \star k_{yN}^q$	thermal conductivity in y-direction in arc	material
47	$k_{zA}^q := I_{N,A} \star k_{zN}^q$	thermal conductivity in z-direction in arc	material
48	$m_N := \lambda_S \star n_{N,S}$	mass	material

Continued on next page

no	equation	documentation	layer
49	$\rho_N := (V_N)^{-1} \cdot m_N$	density	material
50	$v_S := V_N \star (n_{N,S})^{-1}$	molar volume of species	material
51	$k_{x,A,S}^{d,Fick} := I_{N,A} \star \left(v_{xN} \cdot \frac{\partial U_N}{\partial \mu_{N,S}} \cdot (n_{N,S})^{-1} \right)$	Fick's diffusivity in arc and x-direction	material
52	$k_{y,A,S}^{d,Fick} := I_{N,A} \star \left(v_{yN} \cdot \frac{\partial U_N}{\partial \mu_{N,S}} \cdot (n_{N,S})^{-1} \right)$	Fick's diffusivity in arc and y-direction	material
53	$k_{z,A,S}^{d,Fick} := I_{N,A} \star \left(v_{zN} \cdot \frac{\partial U_N}{\partial \mu_{N,S}} \cdot (n_{N,S})^{-1} \right)$	Fick's diffusivity in arc and z-direction	material
54	$A_{xyN} := r_{xN} \cdot r_{yN}$	cross sectional area xy	macroscopic
55	$A_{xzN} := r_{xN} \cdot r_{zN}$	cross sectional area xz	macroscopic
56	$A_{yzN} := r_{yN} \cdot r_{zN}$	cross sectional area yz	macroscopic
57	$A_{xyA} := I_{N,A} \star A_{xyN}$	cross sectional area yz of arc	macroscopic
58	$A_{xzA} := I_{N,A} \star A_{xzN}$	cross sectional area xz of arc	macroscopic
59	$A_{yzA} := I_{N,A} \star A_{yzN}$	cross sectional area yz of arc	macroscopic
72	$\hat{q}_{xA} := A_{yzA} \cdot _k_{xA}^q \cdot (D_{N,A} \star T_N)$	heat flow in arc and x-direction	macroscopic
73	$\dot{q}_N := F_{N,A} \star \hat{q}_{xA}$	accumulation due to conductive heat flow	macroscopic
74	$c_{N,S} := (V_N)^{-1} \cdot n_{N,S}$	molar concentration	macroscopic
75	$d_A := \text{sign}(D_{N,A} \star p_N)$	flow direction of convective flow	macroscopic
76	$c_{A,S} := (0.5 \cdot (D_{N,A} - d_A \cdot D_{N,A})) \star c_{N,S}$	concentration in convective mass flow	macroscopic
78	$\rho_A := I_{N,A} \star \rho_N$	density of arc material	material
80	$\dot{V}_A := (_ \rho_A)^{-1} \cdot _k_{xA}^c \cdot A_{yzA} \cdot (D_{N,A} \star p_N)$	volumetric flow	macroscopic

Continued on next page

no	equation	documentation	layer
81	$\hat{n}_{A,S}^c := \dot{V}_A \cdot c_{A,S}$	convective mass flow in an arc	macroscopic
82	$\dot{n}_{N,S}^c := F_{N,A} \star \hat{n}_{A,S}^c$	accumulation due to convective mass flow	macroscopic
83	$n_N^t := I_S \star n_{N,S}$	total amount	macroscopic
84	$x_{N,S} := (n_N^t)^{-1} \cdot n_{N,S}$	concentration mole fraction	macroscopic
85	$\hat{n}_{A,S}^d := A_{yzA} \cdot (-_x k_{A,S}^{d,Fick}) \cdot (D_{N,A} \star c_{N,S})$	diffusional mass flow in arc	macroscopic
86	$\mu_{N,S}^o := \text{Instantiate}(\mu_{N,S}, \#)$	standard chemical potential	material
88	$\mu_{N,S} := \mu_{N,S}^o + R_N \cdot T_N \cdot \ln(_x x_{N,S})$	chemical potential standard model with mole fraction	material
89	$\hat{n}_{A,S}^d := A_{yzA} \cdot (-_x k_{A,S}^d) \cdot (D_{N,A} \star \mu_{N,S})$	diffusional mass flow in arc	macroscopic
90	$\dot{n}_{N,S}^d := F_{N,A} \star \hat{n}_{A,S}^d$	accumulation due to diffusional mass transfer	macroscopic
91	$\dot{H}_N^w := \text{Instantiate}(H_N, \#)$	work flow – instantiate	macroscopic
93	$h_{AA,S} := I_{N,A} \star h_{N,S}$	partial molar enthalpies of transport system	material
95	$\hat{H}_A^c := I_S \star (_h h_{A,S} \cdot \hat{n}_{A,S}^c)$	enthalpy flow due to convective mass flow	macroscopic
96	$\hat{H}_A^d := I_S \star (_h h_{A,S} \cdot \hat{n}_{A,S}^d)$	enthalpy flow due to diffusive mass flow	macroscopic
97	$\dot{H}_N^c := F_{N,A} \star \hat{H}_A^c$	enthalpy accumulation due to convective mass flow	macroscopic
98	$\dot{H}_N^d := F_{N,A} \star \hat{H}_A^d$	enthalpy accumulation due to diffusive mass flow	macroscopic

Continued on next page

no	equation	documentation	layer
99	$T_{N,K} := T_N \cdot P_{N,K}$	temparature of the nodes with reactions	reactions
100	$E_{a_{N,K}} := \text{Instantiate}(R_N \cdot T_{N,K}, \#)$	Arrhenius activation energy	reactions
101	$K^o_K := \text{Instantiate}(I_S \star (P_{N,K} \star ((t)^{-1} \cdot (V_N)^{-1} \cdot (n_{N,S})^{-1})), \#)$	Arrhenius frequency factor – a strange construction	reactions
102	$K_{N,K} := K^o_K \cdot \exp((-E_{a_{N,K}}) \cdot (R_N \cdot T_{N,K})^{-1})$	raction "constant"	reactions
110	$c^n_{N,S} := \text{Instantiate}(_c c_{N,S}, \#)$	norming concentration used in the definition of the species interaction probability	reactions
112	$\bar{n}_{N,S} := (c^n_{N,S})^{-1} \cdot _c c_{N,S}$	normed concentration	reactions
113	$\bar{n}_{N,S,K} := P_{N,K} \cdot \bar{n}_{N,S}$	normed concentration – context node and conversion	reactions
114	$N_{N,S,K} := P_{N,K} \cdot N_{S,K}$	stoichiometric matrix – context nodes	reactions
115	$\phi_{N,K} := \prod_S c n_N K_{N,S,K}$	probability for the species to meet to undergo reaction	reactions

13 Interface Link Equation

no	equation	documentation	layer
22	$_{-}\lambda_S := \lambda_S$	interface equation	material -> macroscopic
60	$_{-}k_{xA}^c := k_{xA}^c$	interface equation	material -> macroscopic
61	$_{-}k_{yA}^c := k_{yA}^c$	interface equation	material -> macroscopic
62	$_{-}k_{zA}^c := k_{zA}^c$	interface equation	material -> macroscopic
63	$_{-}k_{xA,S}^d := k_{xA,S}^d$	interface equation	material -> macroscopic
64	$_{-}k_{x,A,S}^{d,Fick} := k_{x,A,S}^{d,Fick}$	interface equation	material -> macroscopic
65	$_{-}k_{y,A,S}^{d,Fick} := k_{y,A,S}^{d,Fick}$	interface equation	material -> macroscopic
66	$_{-}k_{yA,S}^d := k_{yA,S}^d$	interface equation	material -> macroscopic
67	$_{-}k_{zA,S}^d := k_{zA,S}^d$	interface equation	material -> macroscopic
68	$_{-}k_{z,A,S}^{d,Fick} := k_{z,A,S}^{d,Fick}$	interface equation	material -> macroscopic
69	$_{-}k_{xA}^q := k_{xA}^q$	interface equation	material -> macroscopic

Continued on next page

no	equation	documentation	layer
70	$_k_{yA}^q := k_{yA}^q$	interface equation	material \rightarrow macroscopic
71	$_k_{zA}^q := k_{zA}^q$	interface equation	material \rightarrow macroscopic
77	$_\rho_N := \rho_N$	interface equation	material \rightarrow macroscopic
79	$_\rho_A := \rho_A$	interface equation	material \rightarrow macroscopic
87	$_x_{N,S} := x_{N,S}$	interface equation	macroscopic \rightarrow material
92	$_h_{N,S} := h_{N,S}$	interface equation	material \rightarrow macroscopic
94	$_h_{A,S} := h_{AA,S}$	interface equation	material \rightarrow macroscopic
103	$_E^a_{N,K} := E_{aN,K}$	interface equation	reactions \rightarrow macroscopic
104	$_K_{N,K} := K_{N,K}$	interface equation	reactions \rightarrow macroscopic
105	$_K^o_K := K^o_K$	interface equation	reactions \rightarrow macroscopic
106	$_N_{S,K} := N_{S,K}$	interface equation	reactions \rightarrow macroscopic
107	$_T_{N,K} := T_{N,K}$	interface equation	reactions \rightarrow macroscopic

Continued on next page

no	equation	documentation	layer
109	$_c_{N,S} := c_{N,S}$	interface equation	macroscopic \rightarrow reactions