

水溶维纶纤维

WATER SOLUBLE PVA FIBER

水溶纤维产能为 1.9 万吨/年，S-9、S-8、SS-7、SS-4、SS-2 纤维在水中溶解温度分别为 90℃、80℃、70℃、40℃、20℃。用于棉纺、麻纺、毛纺、绢纺，可纯纺、混纺，生产混纺伴纺纱线、纯水溶纱线、纯水溶无纺布产品。

The capacity of water soluble fiber is 19 ktpa. S-9、S-8、SS-7、SS-4、SS-2 fiber represents our water soluble products with respective dissolving temperature of 90℃、80℃、70℃、40℃、20℃. The products can be used in cotton spinning, linen spinning. Wool spinning and silk spinning in pure or blend. The blended fiber or carrier yarn, pure water soluble yarn and non-woven fabric are well sold in the world.

主要规格

MAIN GRADES

Grade 规格	Specification 指标			
	Linear 线密度	Cut length 长度	Melting temperature 溶断温度	Dry breaking tenacity 干断裂强度
S-9	M	L	90±5℃	≥4.5cN/dtex
S-8			80±5℃	
SS-7			70±5℃	
SS-6			60±5℃	
SS-4			40±5℃	
SS-2			20±5℃	
M=1.33dtex or 1.56dtex or 1.67dtex L=38 mm or 51 mm or 76 mm				

产品包装

PRODUCT PACKAGING

水溶纤维纤维采用 150kg 复膜袋包装

Water soluble PVA fiber is packaged with plastic laminated bag of 150kg.