



Date :	22-Oct-25	Factory :	122T03
HT color :	K2-Boysenberry 134-25-13	Fabric No :	RT2302179_SUB
Reference No :	NBFK24040502	Fabric color :	WHITE PFP 11-0601 TCX PFP/P35586/P35587/P35442/P356 03/P35456/P35452
Quality :	SAM	Application Side :	FACE
Glue :	K		
HT Description :	(SAM-K)NB25-FNB6CM_Flying NB 6cm		

**CONCLUSION :****COMMENTS :**

1.Adherence &amp; Surface Appearance after wash-40°C\*10cycles

M

Obvious glue edge before wash.

Surface appearance slightly worn after wash.

2.Elasticity Test

M

3.Dye Migration

M

4.CF to Rubbing

M

M = Meet buyer's requirement

F = Below buyer's requirement

N/A = Not applicable

\* = No specified requirement or fair

**1.After Wash**

-Washing Temperature(°C) : 40  
 -Washing Cycle : 10  
 -Drying : LOW  
 -Drying Cycle : 10

**GRADING****REQUIREMENT**

-Adherence :	5.0	4.0
-Surface Appearance :	4.0	4.0
-Color Change :	5.0	3.5
-Color Staining :	4.5	3.5

**2.Elasticity Test**

	<b>RESULT</b>	<b>REQUIREMENT</b>
-Before wash :	ACCEPTED	No Cracking
-After wash :	ACCEPTED	No Cracking

**3.Dye Migration**

-Temperature(°C) : 70  
 -Operation Time(hr) : 48

**GRADING****REQUIREMENT**

-Color Change :	5.0	4.0
-Self Staining :	4.5	4.5

**4.CF to Rubbing**

	<b>GRADING</b>	<b>REQUIREMENT</b>
-Color Staining(DRY) :	4.0	4.0
-Color Staining(WET) :	4.5	3.0

**OVERALL COMMENTS FROM LAB :**

☆Press mark appeared after application

After pressing, the appearance of the other side of the fabric has changed from the original.



Date :	22-Oct-25	Factory :	122T03
HT color :	M2-Medusa Green 094-26-10	Fabric No :	RT2302179_SUB
Reference No :	NBFK24040502	Fabric color :	WHITE PFP 11-0601 TCX PFP/P35580/P35583/P35443/P354 51/P35459/P35455
Quality :	SAM	Application Side :	FACE
Glue :	K		
HT Description : (SAM-K)NB25-FNB6CM_Flying NB 6cm			

**CONCLUSION :****COMMENTS :**

1.Adherence &amp; Surface Appearance after wash-40°C\*10cycles

M

Obvious glue edge before wash.

Surface appearance slightly worn after wash.

2.Elasticity Test

M

3.Dye Migration

M

4.CF to Rubbing

M

M = Meet buyer's requirement

F = Below buyer's requirement

N/A = Not applicable

\* = No specified requirement or fair

**1.After Wash**

-Washing Temperature(°C) : 40  
 -Washing Cycle : 10  
 -Drying : LOW  
 -Drying Cycle : 10

**GRADING****REQUIREMENT**

-Adherence :	5.0	4.0
-Surface Appearance :	4.0	4.0
-Color Change :	4.5	3.5
-Color Staining :	5.0	3.5

**2.Elasticity Test**

	<b>RESULT</b>	<b>REQUIREMENT</b>
-Before wash :	ACCEPTED	No Cracking
-After wash :	ACCEPTED	No Cracking

**3.Dye Migration**

-Temperature(°C) : 70  
 -Operation Time(hr) : 48

**GRADING****REQUIREMENT**

-Color Change :	4.5	4.0
-Self Staining :	5.0	4.5

**4.CF to Rubbing**

	<b>GRADING</b>	<b>REQUIREMENT</b>
-Color Staining(DRY) :	4.5	4.0
-Color Staining(WET) :	4.5	3.0

**OVERALL COMMENTS FROM LAB :**

☆Press mark appeared after application

After pressing, the appearance of the other side of the fabric has changed from the original.



Date :	22-Oct-25	Factory :	122T03
HT color :	M1-Inkwell 124-25-23	Fabric No :	RT2302179_SUB
Reference No :	NBFK24040502	Fabric color :	WHITE PFP 11-0601 TCX P35582/P35584/P35450/P35603/P 35458/P35454/P35605
Quality :	SAM	Application Side :	FACE
Glue :	K		
HT Description :	(SAM-K)NB25-FNB6CM_Flying NB 6cm		

**CONCLUSION :**

1.Adherence & Surface Appearance after wash-40°C*10cycles	M
2.Elasticity Test	M
3.Dye Migration	M
4.CF to Rubbing	M

M = Meet buyer's requirement

N/A = Not applicable

**COMMENTS :**

Obvious glue edge before wash.  
Surface appearance slightly worn after wash.

F = Below buyer's requirement

\* = No specified requirement or fair

**1.After Wash**

-Washing Temperature(°C) :	40
-Washing Cycle :	10
-Drying :	LOW
-Drying Cycle :	10

	GRADING	REQUIREMENT
-Adherence :	5.0	4.0
-Surface Appearance :	4.0	4.0
-Color Change :	5.0	3.5
-Color Staining :	4.5	3.5

**2.Elasticity Test**

	RESULT	REQUIREMENT
-Before wash :	ACCEPTED	No Cracking
-After wash :	ACCEPTED	No Cracking

**3.Dye Migration**

-Temperature(°C) :	70
-Operation Time(hr) :	48

	GRADING	REQUIREMENT
-Color Change :	5.0	4.0
-Self Staining :	4.5	4.5

**4.CF to Rubbing**

	GRADING	REQUIREMENT
-Color Staining(DRY) :	4.0	4.0
-Color Staining(WET) :	4.5	3.0

**OVERALL COMMENTS FROM LAB :**

☆Press mark appeared after application

After pressing, the appearance of the other side of the fabric has changed from the original.



Date :	22-Oct-25	Factory :	122T03
HT color :	J1-Alkaline Green 053-89-50	Fabric No :	RT2302179_SUB
Reference No :	NBFK24040502	Fabric color :	WHITE PFP 11-0601 TCX P35581/P35585/P35449/P35602/P 35457/P35453/P35604
Quality :	SAM	Application Side :	FACE
Glue :	K		
HT Description :	(SAM-K)NB25-FNB6CM_Flying NB 6cm		

**CONCLUSION :****COMMENTS :**

1.Adherence &amp; Surface Appearance after wash-40°C\*10cycles

M

Obvious glue edge before wash.

Surface appearance slightly worn after wash.

2.Elasticity Test

M

3.Dye Migration

M

4.CF to Rubbing

M

M = Meet buyer's requirement

F = Below buyer's requirement

N/A = Not applicable

\* = No specified requirement or fair

**1.After Wash**

-Washing Temperature(°C) : 40  
 -Washing Cycle : 10  
 -Drying : LOW  
 -Drying Cycle : 10

**GRADING****REQUIREMENT**

-Adherence :	5.0	4.0
-Surface Appearance :	4.0	4.0
-Color Change :	5.0	3.5
-Color Staining :	4.5	3.5

**2.Elasticity Test**

	<b>RESULT</b>	<b>REQUIREMENT</b>
-Before wash :	ACCEPTED	No Cracking
-After wash :	ACCEPTED	No Cracking

**3.Dye Migration**

-Temperature(°C) : 70  
 -Operation Time(hr) : 48

**GRADING****REQUIREMENT**

-Color Change :	5.0	4.0
-Self Staining :	4.5	4.5

**4.CF to Rubbing**

	<b>GRADING</b>	<b>REQUIREMENT</b>
-Color Staining(DRY) :	4.0	4.0
-Color Staining(WET) :	4.5	3.0

**OVERALL COMMENTS FROM LAB :**

☆Press mark appeared after application

After pressing, the appearance of the other side of the fabric has changed from the original.



## OPERATING INSTRUCTIONS

蓋墊

Report No. : TL11410125-1-1-F

Application surface : FACE

HT No. : NBFK24040502

Code : SAM-K

Item : (SAM-K)NB25-FNB6CM\_Flying NB 6cm

Effect : 超強抗昇華效果 (Super Anti-Migration)/針織布膠 (For Knitted Fabric)

Fabric no : RT2302179\_SUB


Real touch Heat transfer condition: 實際接觸轉印標壓燙條件

## &lt;1st-step application&gt;

## &lt;2nd-step application&gt;

♦Cover with a Teflon, white paper, or release paper on the top to reduce the static electricity. 壓燙時，需覆蓋白紙/鐵氟龍/離型紙以降低靜電。

Temperature :	150 °C	302 °F	Temperature :	°C	°F
Pressure :	40 Psi	2.8 Kg/cm <sup>2</sup>	Pressure :	Psi	Kg/cm <sup>2</sup>
Apply Pressure	Use fabric mat 使用墊布		Apply Pressure		
Time :	15 sec		Time :	sec	
Peeling Time :	Peeling time is instructed by heat transfer package. Cold Peel: wait 2-5 min Warm-Cold Peel: wait 20-60 sec Warm Peel: wait 10-30 sec Hot Peel: wait 5-10 sec				



When peel off the release paper (PET), please peel from arc part of graphic instead of sharp angle to prevent the damage of heat transfer. 撕紙時須從圖形結構為圓弧處撕起，避免從尖角處容易造成損壞。

After pressing the heat transfer, please do not throw the cloth as the glue is not yet completely cooling. 壓燙後，因膠未完全冷卻，請勿甩布。

In-house Heat Transfer Application Machinery Model: Hotronix Air Fusion(Platen 16""X20"", Air Cylinder 6""). Please ensure the application temperature within 2.5°C (5°F) range of suggested temperature. 依田使用的壓燙機型號為Platen 16""X20"", Air Cylinder 6"", 請確保壓台溫差可保持在建議壓燙溫度2.5°C(5°F)以內"


Please review the test specimen by following brand's test manual, and avoid using hard, sharp object such as finger nail to damage the HT. 請依照品牌測試標準文來檢視測試樣，避免使用尖銳硬物像是指甲來破壞轉印標表面

Due to the variety of fabric composition and structure, please follow above suggested conditions to ensure the glue can be completely melted to present the best appearance and quality. 因布的組織與結構多元，為確保膠能充分熱熔，以呈現最好的外觀品質與牢度，請依照指示操作。

Suggestion: Use "fabric-mat" with the thickness of 3mm~4mm to provide a buffer and even pressure to ensure the application durability. 使用3mm~4mm厚度的布墊來平均壓力以確保牢度

Fabric with mesh hole or with obvious texture requires this application method. 網紗布或紋路起伏較大的布種，建議使用此壓燙方式。

## Application Graphic :



Layer ①: Heat-pressing machine platen  
 Layer ②: A full page of silicon pad (10MM)  
 Layer ③: Fabric-Mat  
 Layer ④: Panel  
 Layer ⑤: HT

\* Please see the back page for important remark 請參照背面注意事項說明 \*



## OPERATING INSTRUCTIONS

蓋墊

Report No. : TL11410125-2-2-F

Application surface : FACE

HT No. : NBFK24040502

Code : SAM-K

Item : (SAM-K)NB25-FNB6CM\_Flying NB 6cm

Effect : 超強抗昇華效果 (Super Anti-Migration)/針織布膠 (For Knitted Fabric)

Fabric no : RT2302179\_SUB


Real touch Heat transfer condition: 實際接觸轉印標壓燙條件

## &lt;1st-step application&gt;

## &lt;2nd-step application&gt;

♦Cover with a Teflon, white paper, or release paper on the top to reduce the static electricity. 壓燙時，需覆蓋白紙/鐵氟龍/離型紙以降低靜電。

Temperature :	150 °C	302 °F	Temperature :	°C	°F
Pressure :	40 Psi	2.8 Kg/cm <sup>2</sup>	Pressure :	Psi	Kg/cm <sup>2</sup>
Apply Pressure	Use fabric mat 使用墊布		Apply Pressure		
Time :	15 sec		Time :	sec	
Peeling Time :	Peeling time is instructed by heat transfer package. Cold Peel: wait 2-5 min Warm-Cold Peel: wait 20-60 sec Warm Peel: wait 10-30 sec Hot Peel: wait 5-10 sec				



When peel off the release paper (PET), please peel from arc part of graphic instead of sharp angle to prevent the damage of heat transfer. 撕紙時須從圖形結構為圓弧處撕起，避免從尖角處容易造成損壞。

After pressing the heat transfer, please do not throw the cloth as the glue is not yet completely cooling. 壓燙後，因膠未完全冷卻，請勿甩布。

In-house Heat Transfer Application Machinery Model: Hotronix Air Fusion(Platen 16""X20"" , Air Cylinder 6"" ). Please ensure the application temperature within 2.5°C (5°F) range of suggested temperature. 依田使用的壓燙機型號為Platen 16""X20"" , Air Cylinder 6"" , 請確保壓台溫差可保持在建議壓燙溫度2.5°C(5°F)以內"


Please review the test specimen by following brand's test manual, and avoid using hard, sharp object such as finger nail to damage the HT. 請依照品牌測試標準文來檢視測試樣，避免使用尖銳硬物像是指甲來破壞轉印標表面

Due to the variety of fabric composition and structure, please follow above suggested conditions to ensure the glue can be completely melted to present the best appearance and quality. 因布的組織與結構多元，為確保膠能充分熱熔，以呈現最好的外觀品質與牢度，請依照指示操作。

Suggestion: Use "fabric-mat" with the thickness of 3mm~4mm to provide a buffer and even pressure to ensure the application durability. 使用3mm~4mm厚度的布墊來平均壓力以確保牢度

Fabric with mesh hole or with obvious texture requires this application method. 網紗布或紋路起伏較大的布種，建議使用此壓燙方式。

## Application Graphic :



Layer ①: Heat-pressing machine platen  
 Layer ②: A full page of silicon pad (10MM)  
 Layer ③: Fabric-Mat  
 Layer ④: Panel  
 Layer ⑤: HT

\* Please see the back page for important remark 請參照背面注意事項說明 \*



## OPERATING INSTRUCTIONS

蓋墊

Report No. : TL11410125-3-3-F

Application surface : FACE

HT No. : NBFK24040502

Code : SAM-K

Item : (SAM-K)NB25-FNB6CM\_Flying NB 6cm

Effect : 超強抗昇華效果 (Super Anti-Migration)/針織布膠 (For Knitted Fabric)


Fabric no : RT2302179\_SUB


Real touch Heat transfer condition:實際接觸轉印標壓燙條件

## &lt;1st-step application&gt;

## &lt;2nd-step application&gt;

♦Cover with a Teflon, white paper, or release paper on the top to reduce the static electricity. 壓燙時，需覆蓋白紙/鐵氟龍/離型紙以降低靜電。

◆Cover with a Teflon, white paper, or release paper on the top to reduce the static electricity . 壓燙時，需覆蓋白紙/鐵氟龍/離型紙以降低靜電。					
Temperature :	150 °C	302 °F	Temperature :	°C	°F
Pressure :	40 Psi	2.8 Kg/cm²	Pressure :	Psi	Kg/cm²
Apply Pressure	Use fabric mat 使用墊布		Apply Pressure		
Time :	15	sec	Time :	sec	
Peeling Time :	Peeling time is instructed by heat transfer package. Cold Peel: wait 2-5 min Warm-Cold Peel: wait 20-60 sec Warm Peel: wait 10-30 sec Hot Peel: wait 5-10 sec				



When peel off the release paper (PET), please peel from arc part of graphic instead of sharp angle to prevent the damage of heat transfer. 撕紙時須從圖形結構為圓弧處撕起，避免從尖角處容易造成損壞。

After pressing the heat transfer, please do not throw the cloth as the glue is not yet completely cooling. 壓燙後，因膠未完全冷卻，請勿甩布。

In-house Heat Transfer Application Machinery Model: Hotronix Air Fusion(Platen 16""X20"" , Air Cylinder 6"" ). Please ensure the application temperature within 2.5°C (5°F) range of suggested temperature. 依田使用的壓燙機型號為Platen 16""X20"" , Air Cylinder 6"" , 請確保壓台溫差可保持在建議壓燙溫度2.5°C(5°F)以內"


Please review the test specimen by following brand's test manual, and avoid using hard, sharp object such as finger nail to damage the HT. 請依照品牌測試標準文來檢視測試樣，避免使用尖銳硬物像是指甲來破壞轉印標表面

Due to the variety of fabric composition and structure, please follow above suggested conditions to ensure the glue can be completely melted to present the best appearance and quality. 因布的組織與結構多元，為確保膠能充分熱熔，以呈現最好的外觀品質與牢度，請依照指示操作。

Suggestion: Use "fabric-mat" with the thickness of 3mm~4mm to provide a buffer and even pressure to ensure the application durability. 使用3mm~4mm厚度的布墊來平均壓力以確保牢度

Fabric with mesh hole or with obvious texture requires this application method. 網紗布或紋路起伏較大的布種，建議使用此壓燙方式。

## Application Graphic :



Layer ①: Heat-pressing machine platen  
 Layer ②: A full page of silicon pad (10MM)  
 Layer ③: Fabric-Mat  
 Layer ④: Panel  
 Layer ⑤: HT

\* Please see the back page for important remark 請參照背面注意事項說明 \*





## OPERATING INSTRUCTIONS

蓋墊

Report No. : TL11410125-4-4-F

Application surface : FACE

HT No. : NBFK24040502

Code : SAM-K

Item : (SAM-K)NB25-FNB6CM\_Flying NB 6cm

Effect : 超強抗昇華效果 (Super Anti-Migration)/針織布膠 (For Knitted Fabric)

Fabric no : RT2302179\_SUB


Real touch Heat transfer condition: 實際接觸轉印標壓燙條件

## &lt;1st-step application&gt;

## &lt;2nd-step application&gt;

♦Cover with a Teflon, white paper, or release paper on the top to reduce the static electricity. 壓燙時，需覆蓋白紙/鐵氟龍/離型紙以降低靜電。

Temperature :	150 °C	302 °F	Temperature :	°C	°F
Pressure :	40 Psi	2.8 Kg/cm <sup>2</sup>	Pressure :	Psi	Kg/cm <sup>2</sup>
Apply Pressure	Use fabric mat 使用墊布		Apply Pressure		
Time :	15 sec		Time :	sec	
Peeling Time :	Peeling time is instructed by heat transfer package. Cold Peel: wait 2-5 min Warm-Cold Peel: wait 20-60 sec Warm Peel: wait 10-30 sec Hot Peel: wait 5-10 sec				



When peel off the release paper (PET), please peel from arc part of graphic instead of sharp angle to prevent the damage of heat transfer. 撕紙時須從圖形結構為圓弧處撕起，避免從尖角處容易造成損壞。

After pressing the heat transfer, please do not throw the cloth as the glue is not yet completely cooling. 壓燙後，因膠未完全冷卻，請勿甩布。

In-house Heat Transfer Application Machinery Model: Hotronix Air Fusion(Platen 16""X20"" , Air Cylinder 6"" ). Please ensure the application temperature within 2.5°C (5°F) range of suggested temperature. 依田使用的壓燙機型號為Platen 16""X20"" , Air Cylinder 6"" , 請確保壓台溫差可保持在建議壓燙溫度2.5°C(5°F)以內"


Please review the test specimen by following brand's test manual, and avoid using hard, sharp object such as finger nail to damage the HT. 請依照品牌測試標準文來檢視測試樣，避免使用尖銳硬物像是指甲來破壞轉印標表面

Due to the variety of fabric composition and structure, please follow above suggested conditions to ensure the glue can be completely melted to present the best appearance and quality. 因布的組織與結構多元，為確保膠能充分熱熔，以呈現最好的外觀品質與牢度，請依照指示操作。

Suggestion: Use "fabric-mat" with the thickness of 3mm~4mm to provide a buffer and even pressure to ensure the application durability. 使用3mm~4mm厚度的布墊來平均壓力以確保牢度

Fabric with mesh hole or with obvious texture requires this application method. 網紗布或紋路起伏較大的布種，建議使用此壓燙方式。

## Application Graphic :



Layer ①: Heat-pressing machine platen  
 Layer ②: A full page of silicon pad (10MM)  
 Layer ③: Fabric-Mat  
 Layer ④: Panel  
 Layer ⑤: HT

\* Please see the back page for important remark 請參照背面注意事項說明 \*