



Date :	10-Apr-24	Factory :	122T03
HT color :	A1-White (ET.001)	Fabric No :	TEI80032-6MFX2
Reference No :	NBFK24030015	Fabric color :	NB NAVY 124-23-11
Quality :	SAM	Application Side :	FACE
Glue :	K		
HT Description : (SAM-K)NB25-AO1.6IN_AO logo_4.1cm x 2.03cm			

**CONCLUSION :****COMMENTS :**

1.Adherence &amp; Surface Appearance after wash-40°C\*10cycles

M

Fabric structure visible

2.Elasticity Test

M

3.Dye Migration

M

M = Meet buyer's requirement

F = Below buyer's requirement

N/A = Not applicable

\* = No specified requirement or fair

**1.After Wash**

-Washing Temperature(°C) :	40
-Washing Cycle :	10
-Drying :	LOW
-Drying Cycle :	10

**GRADING****REQUIREMENT**

-Adherence :	5.0	4.0
-Surface Appearance :	4.0	4.0
-Color Change :	5.0	3.5
-Color Staining :	4.5	3.5

**2.Elasticity Test**

	<b>RESULT</b>	<b>REQUIREMENT</b>
-Before wash :	ACCEPTED	No Cracking
-After wash :	ACCEPTED	No Cracking

**3.Dye Migration**

-Temperature(°C) :	70
-Operation Time(hr) :	48

**GRADING****REQUIREMENT**

-Color Change :	5.0	4.0
-Self Staining :	4.5	4.5

**OVERALL COMMENTS FROM LAB :**

☆Press mark appeared after application

The report / application setting of NB25-AO1.6IN, NB24-AO2IN, NB24-AO2.4 can be referred due to the same quality with similar design.



Date :	10-Apr-24	Factory :	122T03
HT color :	A1-White (ET.001)	Fabric No :	TEI80032-6MFX2
Reference No :	NBFK23040076	Fabric color :	NB NAVY 124-23-11
Quality :	SAM	Application Side :	FACE
Glue :	K		
HT Description : (SAM-K)NB24-2.5MATTE_Flying NB 2.5cm			

**CONCLUSION :****COMMENTS :**

1.Adherence &amp; Surface Appearance after wash-40°C\*10cycles

M

Fabric structure visible

2.Elasticity Test

M

3.Dye Migration

M

M = Meet buyer's requirement

F = Below buyer's requirement

N/A = Not applicable

\* = No specified requirement or fair

**1.After Wash**

-Washing Temperature(°C) :	40
-Washing Cycle :	10
-Drying :	LOW
-Drying Cycle :	10

**GRADING****REQUIREMENT**

-Adherence :	5.0	4.0
-Surface Appearance :	4.0	4.0
-Color Change :	5.0	3.5
-Color Staining :	4.5	3.5

**2.Elasticity Test**

	<b>RESULT</b>	<b>REQUIREMENT</b>
-Before wash :	ACCEPTED	No Cracking
-After wash :	ACCEPTED	No Cracking

**3.Dye Migration**

-Temperature(°C) :	70
-Operation Time(hr) :	48

**GRADING****REQUIREMENT**

-Color Change :	5.0	4.0
-Self Staining :	4.5	4.5

**OVERALL COMMENTS FROM LAB :**

☆Press mark appeared after application

The report / application setting of NB24-2.5MATTE, NB19-HF-SAM-FNB1.5 can be referred due to the same quality with similar design.



Date :	10-Apr-24	Factory :	122T03
HT color :	A1-White (ET.001)	Fabric No :	RV2002062
Reference No :	NBFK24030015	Fabric color :	NB NAVY 124-23-11
Quality :	SAM	Application Side :	FACE
Glue :	K		
HT Description :	(SAM-K)NB25-AO1.6IN_AO logo_4.1cm x 2.03cm		

**CONCLUSION :****COMMENTS :**

1.Adherence &amp; Surface Appearance after wash-40°C\*10cycles

M

Fabric structure visible

2.Elasticity Test

M

3.Dye Migration

M

M = Meet buyer's requirement

F = Below buyer's requirement

N/A = Not applicable

\* = No specified requirement or fair

**1.After Wash**

-Washing Temperature(°C) :	40
-Washing Cycle :	10
-Drying :	LOW
-Drying Cycle :	10

**GRADING****REQUIREMENT**

-Adherence :	5.0	4.0
-Surface Appearance :	4.0	4.0
-Color Change :	5.0	3.5
-Color Staining :	4.5	3.5

**2.Elasticity Test**

	<b>RESULT</b>	<b>REQUIREMENT</b>
-Before wash :	ACCEPTED	No Cracking
-After wash :	ACCEPTED	No Cracking

**3.Dye Migration**

-Temperature(°C) :	70
-Operation Time(hr) :	48

**GRADING****REQUIREMENT**

-Color Change :	5.0	4.0
-Self Staining :	4.5	4.5

**OVERALL COMMENTS FROM LAB :**

☆Press mark appeared after application

The report / application setting of NB25-AO1.6IN, NB24-AO2IN、NB24-AO2.4 can be referred due to the same quality with similar design.



Date :	10-Apr-24	Factory :	122T03
HT color :	A1-White (ET.001)	Fabric No :	RV2002062
Reference No :	NBFK23040076	Fabric color :	NB NAVY 124-23-11
Quality :	SAM	Application Side :	FACE
Glue :	K		
HT Description : (SAM-K)NB24-2.5MATTE_Flying NB 2.5cm			

**CONCLUSION :****COMMENTS :**

1.Adherence &amp; Surface Appearance after wash-40°C\*10cycles

M

Fabric structure visible

2.Elasticity Test

M

3.Dye Migration

M

M = Meet buyer's requirement

F = Below buyer's requirement

N/A = Not applicable

\* = No specified requirement or fair

**1.After Wash**

-Washing Temperature(°C) :	40
-Washing Cycle :	10
-Drying :	LOW
-Drying Cycle :	10

**GRADING****REQUIREMENT**

-Adherence :	5.0	4.0
-Surface Appearance :	4.0	4.0
-Color Change :	5.0	3.5
-Color Staining :	4.5	3.5

**2.Elasticity Test**

	<b>RESULT</b>	<b>REQUIREMENT</b>
-Before wash :	ACCEPTED	No Cracking
-After wash :	ACCEPTED	No Cracking

**3.Dye Migration**

-Temperature(°C) :	70
-Operation Time(hr) :	48

**GRADING****REQUIREMENT**

-Color Change :	5.0	4.0
-Self Staining :	4.5	4.5

**OVERALL COMMENTS FROM LAB :**

☆Press mark appeared after application

The report / application setting of NB24-2.5MATTE, NB19-HF-SAM-FNB1.5 can be referred due to the same quality with similar design.



## OPERATING INSTRUCTIONS

蓋宣墊縮

Report No. : TL11303532-1-2-F

Application surface : FACE

HT No. : NBFK24030015

Code : SAM-K

Item : (SAM-K)NB25-AO1.6IN\_AO logo\_4.1cm x 2.03cm

Effect : 超強抗昇華效果 (Super Anti-Migration)/針織布膠 (For Knitted Fabric)

Fabric no : TEI80032-6MFX2

## Real touch Heat transfer condition:實際接觸轉印標壓燙條件

## &lt;1st-step application&gt;


## &lt;2nd-step application&gt;

♦Cover with a teflon or white paper on the top to reduce the static electricity. 壓燙時，需覆蓋白紙/鐵氟龍以降低靜電。  
♦Please pre-heat fabrication 10 secs with below suggested 1st step temp. and pressure condition.請依第一步驟的壓燙溫度及壓力，預先縮布10秒。

Temperature :	302 °F	150 °C
Pressure :	40 Psi	2.81 Kg/cm <sup>2</sup>
Apply Pressure	Use fabric mat 使用墊布	
Time :	20	sec

Temperature :	°F	°C
Pressure :	Psi	Kg/cm <sup>2</sup>
Apply Pressure		
Time :	sec	

Peeling Time : Peeling time is instructed by heat transfer package.  
Cold Peel: wait 2-5 min  
Warm-Cold Peel: wait 20-60 sec  
Warm Peel: wait 10-30 sec



When peel off the release paper (PET), please peel from arc part of graphic instead of sharp angle to prevent the damage of heat transfer. 撕紙時須從圖形結構為圓弧處撕起，避免從尖角處容易造成損壞。

After pressing the heat transfer, please do not throw the cloth as the glue is not yet completely cooling. 壓燙後，因膠未完全冷卻，請勿甩布。

In-house Heat Transfer Application Machinery Model: Hotronix Air Fusion(Platen 16"X20", Air Cylinder 6"). Please ensure the application temperature within 5°F range of suggested temperature. 依田使用的壓燙機型號為Platen 16"X20", Air Cylinder 6"，建議壓台溫差可保持在建議壓燙溫度5°F以內

Please review the test specimen by following brand's test manual, and avoid using hard, sharp object such as finger nail to damage the HT. 請依照品牌測試標準文來檢視測試樣，避免使用尖銳硬物像是指甲來破壞轉印標表面

Due to the variety of fabric composition and structure, please follow above suggested conditions to ensure the glue can be completely melted to present the best appearance and quality. 因布的組織與結構多元，為確保膠能充分熱熔，以呈現最好的外觀品質與牢度，請依照指示操作。

Suggestion: Use "fabric-mat" with the thickness of 3mm~4mm to provide a buffer and even pressure to ensure the application durability. 使用3mm~4mm厚度的布墊來平均壓力以確保牢度

Fabric with mesh hole or with obvious texture requires this application method. 網紗布或紋路起伏較大的布種，建議使用此壓燙方式。

## Application Graphic :

如有任何壓燙或壓痕問題請找我司協助處理。

If there is any further application or press-mark questions, please do not hesitate to contact us. Thank you!

\* Please see the back page for important remark 請參照背面注意事項說明 \*



## OPERATING INSTRUCTIONS

蓋宣墊縮

Report No. : TL11303532-1-3-F

Application surface : FACE

HT No. : NBFK23040076

Code : SAM-K

Item : (SAM-K)NB24-2.5MATTE\_Flying NB 2.5cm

Effect : 超強抗昇華效果 (Super Anti-Migration)/針織布膠 (For Knitted Fabric)

Fabric no : TEI80032-6MFX2

## Real touch Heat transfer condition: 實際接觸轉印標壓燙條件

## &lt;1st-step application&gt;


## &lt;2nd-step application&gt;

♦Cover with a teflon or white paper on the top to reduce the static electricity. 壓燙時，需覆蓋白紙/鐵氟龍以降低靜電。  
♦Please pre-heat fabrication 10 secs with below suggested 1st step temp. and pressure condition. 請依第一步驟的壓燙溫度及壓力，預先縮布10秒。

Temperature :	302 °F	150 °C
Pressure :	40 Psi	2.81 Kg/cm <sup>2</sup>
Apply Pressure	Use fabric mat 使用墊布	
Time :	20	sec

Temperature :	°F	°C
Pressure :	Psi	Kg/cm <sup>2</sup>
Apply Pressure		
Time :	sec	

Peeling Time : Peeling time is instructed by heat transfer package.  
Cold Peel: wait 2-5 min  
Warm-Cold Peel: wait 20-60 sec  
Warm Peel: wait 10-30 sec



When peel off the release paper (PET), please peel from arc part of graphic instead of sharp angle to prevent the damage of heat transfer. 撕紙時須從圖形結構為圓弧處撕起，避免從尖角處容易造成損壞。

After pressing the heat transfer, please do not throw the cloth as the glue is not yet completely cooling. 壓燙後，因膠未完全冷卻，請勿甩布。

In-house Heat Transfer Application Machinery Model: Hotronix Air Fusion(Platen 16"X20", Air Cylinder 6"). Please ensure the application temperature within 5°F range of suggested temperature. 依田使用的壓燙機型號為Platen 16"X20", Air Cylinder 6"，建議壓台溫差可保持在建議壓燙溫度5°F以內

Please review the test specimen by following brand's test manual, and avoid using hard, sharp object such as finger nail to damage the HT. 請依照品牌測試標準文來檢視測試樣，避免使用尖銳硬物像是指甲來破壞轉印標表面

Due to the variety of fabric composition and structure, please follow above suggested conditions to ensure the glue can be completely melted to present the best appearance and quality. 因布的組織與結構多元，為確保膠能充分熱熔，以呈現最好的外觀品質與牢度，請依照指示操作。

Suggestion: Use "fabric-mat" with the thickness of 3mm~4mm to provide a buffer and even pressure to ensure the application durability. 使用3mm~4mm厚度的布墊來平均壓力以確保牢度

Fabric with mesh hole or with obvious texture requires this application method. 網紗布或紋路起伏較大的布種，建議使用此壓燙方式。

## Application Graphic :

如有任何壓燙或壓痕問題請找我司協助處理。

If there is any further application or press-mark questions, please do not hesitate to contact us. Thank you!

\* Please see the back page for important remark 請參照背面注意事項說明 \*



## OPERATING INSTRUCTIONS

蓋宣墊縮

Report No. : TL11303532-2-2-F

Application surface : FACE

HT No. : NBFK24030015

Code : SAM-K

Item : (SAM-K)NB25-AO1.6IN\_AO logo\_4.1cm x 2.03cm

Effect : 超強抗昇華效果 (Super Anti-Migration)/針織布膠 (For Knitted Fabric)

Fabric no : RV2002062

## Real touch Heat transfer condition:實際接觸轉印標壓燙條件

## &lt;1st-step application&gt;

## &lt;2nd-step application&gt;

♦Cover with a teflon or white paper on the top to reduce the static electricity. 壓燙時，需覆蓋白紙/鐵氟龍以降低靜電。  
♦Please pre-heat fabrication 10 secs with below suggested 1st step temp. and pressure condition.請依第一步驟的壓燙溫度及壓力，預先縮布10秒。

Temperature :	302 °F	150 °C
Pressure :	40 Psi	2.81 Kg/cm <sup>2</sup>
Apply Pressure	Use fabric mat 使用墊布	
Time :	20	sec

Temperature :	°F	°C
Pressure :	Psi	Kg/cm <sup>2</sup>
Apply Pressure		
Time :	sec	

Peeling Time : Peeling time is instructed by heat transfer package.  
Cold Peel: wait 2-5 min  
Warm-Cold Peel: wait 20-60 sec  
Warm Peel: wait 10-30 sec



When peel off the release paper (PET), please peel from arc part of graphic instead of sharp angle to prevent the damage of heat transfer. 撕紙時須從圖形結構為圓弧處撕起，避免從尖角處容易造成損壞。

After pressing the heat transfer, please do not throw the cloth as the glue is not yet completely cooling. 壓燙後，因膠未完全冷卻，請勿甩布。

In-house Heat Transfer Application Machinery Model: Hotronix Air Fusion(Platen 16"X20", Air Cylinder 6"). Please ensure the application temperature within 5°F range of suggested temperature. 依田使用的壓燙機型號為Platen 16"X20", Air Cylinder 6"，建議壓台溫差可保持在建議壓燙溫度5°F以內

Please review the test specimen by following brand's test manual, and avoid using hard, sharp object such as finger nail to damage the HT. 請依照品牌測試標準文來檢視測試樣，避免使用尖銳硬物像是指甲來破壞轉印標表面

Due to the variety of fabric composition and structure, please follow above suggested conditions to ensure the glue can be completely melted to present the best appearance and quality. 因布的組織與結構多元，為確保膠能充分熱熔，以呈現最好的外觀品質與牢度，請依照指示操作。

Suggestion: Use "fabric-mat" with the thickness of 3mm~4mm to provide a buffer and even pressure to ensure the application durability. 使用3mm~4mm厚度的布墊來平均壓力以確保牢度

Fabric with mesh hole or with obvious texture requires this application method. 網紗布或紋路起伏較大的布種，建議使用此壓燙方式。

## Application Graphic :

如有任何壓燙或壓痕問題請找我司協助處理。

If there is any further application or press-mark questions, please do not hesitate to contact us. Thank you!

\* Please see the back page for important remark 請參照背面注意事項說明 \*





## OPERATING INSTRUCTIONS

蓋宣墊縮

Report No. : TL11303532-2-3-F

Application surface : FACE

HT No. : NBFK23040076

Code : SAM-K

Item : (SAM-K)NB24-2.5MATTE\_Flying NB 2.5cm

Effect : 超強抗昇華效果 (Super Anti-Migration)/針織布膠 (For Knitted Fabric)

Fabric no : RV2002062

## Real touch Heat transfer condition:實際接觸轉印標壓燙條件

## &lt;1st-step application&gt;


## &lt;2nd-step application&gt;

♦Cover with a teflon or white paper on the top to reduce the static electricity. 壓燙時，需覆蓋白紙/鐵氟龍以降低靜電。  
♦Please pre-heat fabrication 10 secs with below suggested 1st step temp. and pressure condition.請依第一步驟的壓燙溫度及壓力，預先縮布10秒。

Temperature :	302 °F	150 °C
Pressure :	40 Psi	2.81 Kg/cm <sup>2</sup>
Apply Pressure	Use fabric mat 使用墊布	
Time :	20	sec

Temperature :	°F	°C
Pressure :	Psi	Kg/cm <sup>2</sup>
Apply Pressure		
Time :	sec	

Peeling Time : Peeling time is instructed by heat transfer package.  
Cold Peel: wait 2-5 min  
Warm-Cold Peel: wait 20-60 sec  
Warm Peel: wait 10-30 sec



When peel off the release paper (PET), please peel from arc part of graphic instead of sharp angle to prevent the damage of heat transfer. 撕紙時須從圖形結構為圓弧處撕起，避免從尖角處容易造成損壞。

After pressing the heat transfer, please do not throw the cloth as the glue is not yet completely cooling. 壓燙後，因膠未完全冷卻，請勿甩布。

In-house Heat Transfer Application Machinery Model: Hotronix Air Fusion(Platen 16"X20", Air Cylinder 6"). Please ensure the application temperature within 5°F range of suggested temperature. 依田使用的壓燙機型號為Platen 16"X20", Air Cylinder 6"，建議壓台溫差可保持在建議壓燙溫度5°F以內

Please review the test specimen by following brand's test manual, and avoid using hard, sharp object such as finger nail to damage the HT. 請依照品牌測試標準文來檢視測試樣，避免使用尖銳硬物像是指甲來破壞轉印標表面

Due to the variety of fabric composition and structure, please follow above suggested conditions to ensure the glue can be completely melted to present the best appearance and quality. 因布的組織與結構多元，為確保膠能充分熱熔，以呈現最好的外觀品質與牢度，請依照指示操作。

Suggestion: Use "fabric-mat" with the thickness of 3mm~4mm to provide a buffer and even pressure to ensure the application durability. 使用3mm~4mm厚度的布墊來平均壓力以確保牢度

Fabric with mesh hole or with obvious texture requires this application method. 網紗布或紋路起伏較大的布種，建議使用此壓燙方式。

## Application Graphic :

如有任何壓燙或壓痕問題請找我司協助處理。

If there is any further application or press-mark questions, please do not hesitate to contact us. Thank you!

\* Please see the back page for important remark 請參照背面注意事項說明 \*