

Cont2SAS: A Python package for calculating small angle scattering parameters from continuum nanostructures

Arnab Majumdar^{1,3}, Martin Müller^{1,2,3}, and Sebastian Busch^{1¶}

¹ German Engineering Materials Science Centre (GEMS) at Heinz Maier-Leibnitz Zentrum (MLZ), Helmholtz-Zentrum Hereon GmbH, Lichtenbergstr. 1, 85748 Garching, Germany ² Institute of Materials Physics, Helmholtz-Zentrum Hereon GmbH, Max-Planck-Str. 1, 21502 Geesthacht, Germany ³ Institut für Experimentelle und Angewandte Physik (IEAP), Christian-Albrechts-Universität zu Kiel, Leibnizstr. 19, 24098 Kiel, Germany ¶ Corresponding author

DOI: [10.xxxxxx/draft](https://doi.org/10.xxxxxx/draft)

Software

- [Review](#)
- [Repository](#)
- [Archive](#)

Editor: [Open Journals](#)

Reviewers:

- [@openjournals](#)

Submitted: 01 January 1970

Published: unpublished

License

Authors of papers retain copyright and release the work under a

Creative Commons Attribution 4.0 International License ([CC BY 4.0](#))

Summary

Cont2SAS is a software tool built around the existing software solution Sassena – known for calculating scattering patterns from simulated atomic structures. The goal of Cont2SAS is to provide software similar to Sassena, but for calculating Small Angle Scattering (SAS) data from simulated continuum nanostructures. Cont2SAS can calculate SAS patterns, i.e. SAS intensity (I) vs. scattering vector magnitude (Q) using a numerical method. Cont2SAS can also calculate the effective cross-section (σ_{eff}), i.e. the count rate of scattered radiation per incident unit flux. σ_{eff} is calculated by integrating instrument-agnostic SAS patterns taking the instrument geometry into account. Cont2SAS can be used for different purposes, such as validating simulations, tuning simulation parameters, and analyzing SAS data.

Statement of need

SAS experiments with neutrons (SANS) and X-rays (SAXS) are useful techniques for probing material nanostructures ([Chen et al., 2012](#)). With the Time Resolved (TR) variant of SAS, the time evolution of nanostructures can also be probed ([Hollamby, 2013](#)). However, a direct retrieval of the nanostructure from SAS data is not possible due to the so-called phase problem, i.e. the phase loss in measured intensities ([Billinge & Levin, 2007](#)). Therefore, it is fruitful to combine SAS data with simulations to study nanostructures ([Majumdar et al., 2024](#)). This approach is also useful for validating theories underlying simulations ([Reich et al., 2022](#)).

Simulated real-space structures can be generated using atomistic or continuum simulations. However, atomistic simulations cannot feasibly simulate large structures (e.g. micrometer scale) over long times (e.g. seconds) due to computational limitations ([Ghavanloo et al., 2019](#)). This becomes problematic when nanostructure evolution is influenced by larger length-scale structures or when the TR-SAS data is recorded over long time periods. In such cases, continuum simulation is an appropriate option. Cont2SAS aims to provide a tool that offers fast comparison of continuum simulations and SAS data. The ultimate goal is to study nanomaterials and validate theories using SAS data, particularly when length-scales and time-scales, inaccessible to atomistic simulations, need to be simulated.

State of the field

Different software packages such as nMoldyn (Hinsen, 2023; Róg et al., 2003), MDANSE (Goret et al., 2017; UKRI STFC ISIS Neutron and Muon Facility, 2023), LiquidLib (Walter et al., 2018; Z-laboratory, 2023), and Sassena (Lindner, 2012; Lindner & Smith, 2012; Majumdar et al., 2024; Majumdar & Lindner, 2023) can calculate SAS patterns from atomistic simulations, but they cannot calculate the same from continuum simulations. For continuum simulations, existing software implementations are typically developed for problem-specific applications (Berbenni et al., 2025; Dorrell et al., 2020; Schmidt-Rohr, 2007). The Generic SAS Calculator option in SasView (SasView Developers, 2026) is also a potential alternative, but lacks a clear strategy for converting simulation output into the supported input formats (Liu et al., 2023). Hence, Cont2SAS is built as a general-purpose program that converts simulation output into discretized atoms using a well-defined strategy (Majumdar et al., 2026). For calculating SAS data from the discretized atoms, Cont2SAS uses Sassena as a backend calculator, which provides notable computation speed and robustness (Majumdar et al., 2024).

Software features




Figure 1: Workflow of calculating SAS patterns: [left] SLD assignment for a spherical nanoparticle on generated mesh and [right] numerical calculation of SAS pattern. The numerical calculation is validated against the known analytical formula for spherical nanoparticles (Guinier et al., 1955).

Cont2SAS calculates SAS patterns taking simulated nanostructures as input. The simulated structure must include a Scattering Length Density (SLD) distribution, which is either directly obtained from simulation or calculated from a set of simulated variables (e.g. molar density and molar fraction) before being provided as input to Cont2SAS. Simulating SLD distributions is also possible within Cont2SAS for model structures. The simulated input is processed to data tailor-made for Sassena, which calculates SAS patterns, i.e. I vs Q data, as shown in Figure 1. The Q -dependence of I reveals the average shape and size of the nanoparticles, whereas the magnitude of I is related to the scattering contrast, i.e. the average difference in SLD between particles and their surrounding medium.




Figure 2: [left] TR-SAS data, i.e. SAS patterns at different time steps ranging from 0 to 10 seconds. The SLD of a spherical nanoparticle increases linearly with time. [right] σ_{eff} calculated from the SAS patterns. The calculated σ_{eff} values are proportional to the square of the SLD difference between the particle and its environment, i.e. $(\Delta\text{SLD})^2$, whose shown values are multiplied by an empirical constant.

For simulations with multiple time steps, SAS patterns can be calculated from different time steps generating a TR-SAS dataset, as shown in Figure 2. From TR-SAS data, Cont2SAS can calculate the time evolution of the effective cross-section (σ_{eff}), which is defined as the count rate per incident unit flux (see Figure 2). This feature was not available in previous implementations (Berbenni et al., 2025; Dorrell et al., 2020; Liu et al., 2023; Schmidt-Rohr, 2007) or Sassena (Majumdar & Lindner, 2023). The time evolution of the count rate is useful when the SLD of the nanostructure changes over time without any change in average shape and size, e.g. while storing hydrogen in a ball-milled powder sample (Aslan et al., 2019). The calculated σ_{eff} must be multiplied by an empirical factor before comparing it with the measured count rate.

Conclusion

Cont2SAS provides a software package for calculating SAS patterns from continuum simulations of nanostructures. The addition of the effective cross-section in the software package further enables the analysis of the experimental count rate. Cont2SAS can be used for analyzing SAS data and validating simulations to study nanomaterials.

Acknowledgements

This publication was written in the context of the work of the consortium DAPHNE4NFDI in association with the German National Research Data Infrastructure (NFDI) e.V. NFDI is financed by the Federal Republic of Germany and the 16 federal states and the consortium is funded by the Deutsche Forschungsgemeinschaft (DFG, German Research Foundation) - project number 460248799. The authors would like to thank for the funding and support. Furthermore, thanks go to all institutions and actors who are committed to the association and its goals.

Declaration

During the preparation of this work, the authors used ChatGPT in order to improve the quality of the code and the manuscript. After using this tool, the authors reviewed and edited the content as needed and take full responsibility for the content of the published code and article.

References

- Aslan, N., Horstmann, C., Metz, O., Kotlyar, O., Dornheim, M., Pistidda, C., Busch, S., Lohstroh, W., Müller, M., & Pranzas, K. (2019). High-pressure cell for in situ neutron studies of hydrogen storage materials. *Journal of Neutron Research*, 21(3-4), 125–135. <https://doi.org/10.3233/JNR-190116>
- Berbenni, S., Dingreville, R., & Schenk, T. (2025). Simulation and analysis of small angle scattering (SAS) patterns of ni-based superalloy microstructures generated by a phase-field model. *Computational Materials Science*, 258, 114086. <https://doi.org/10.1016/j.commatsci.2025.114086>
- Billinge, S. J., & Levin, I. (2007). The problem with determining atomic structure at the nanoscale. *Science*, 316(5824), 561–565. <https://doi.org/10.1126/science.1135080>
- Chen, Z. H., Kim, C., Zeng, X., Hwang, S. H., Jang, J., & Ungar, G. (2012). Characterizing size and porosity of hollow nanoparticles: SAXS, SANS, TEM, DLS, and adsorption isotherms compared. *Langmuir*, 28(43), 15350–15361. <https://doi.org/10.1021/la302236u>
- Dorrell, M. W., Beaven, A. H., & Sodt, A. J. (2020). A combined molecular/continuum-modeling approach to predict the small-angle neutron scattering of curved membranes. *Chemistry and Physics of Lipids*, 233, 104983. <https://doi.org/10.1016/j.chemphyslip.2020.104983>
- Ghavanloo, E., Rafii-Tabar, H., & Fazelzadeh, S. A. (2019). *Computational continuum mechanics of nanoscopic structures*. Springer. <https://doi.org/10.1007/978-3-030-11650-7>
- Goret, G., Aoun, B., & Pellegrini, E. (2017). MDANSE: An interactive analysis environment for molecular dynamics simulations. *Journal of Chemical Information and Modeling*, 57(1), 1–5. <https://doi.org/10.1021/acs.jcim.6b00571>
- Guinier, A., Fournet, G., Walker, C. B., & Yudowitch, K. L. (1955). *Small-angle scattering of x-rays*. Wiley New York.
- Hinsen, K. (2023). *nMOLDYN3—version 3.0.12*. <https://github.com/khinsen/nMOLDYN3/>.
- Hollamby, M. J. (2013). Practical applications of small-angle neutron scattering. *Phys. Chem. Chem. Phys.*, 15, 10566–10579. <https://doi.org/10.1039/C3CP50293G>
- Lindner, B. (2012). *Towards a unification of supercomputing, molecular dynamics simulation and experimental neutron and x-ray scattering techniques* [PhD thesis]. University of Tennessee, United States.
- Lindner, B., & Smith, J. C. (2012). Sassena—x-ray and neutron scattering calculated from molecular dynamics trajectories using massively parallel computers. *Computer Physics Communications*, 183(7), 1491–1501. <https://doi.org/10.1016/j.cpc.2012.02.010>
- Liu, Y., Bourne, R., & King, S. (2023). *Generic SAS calculator tool*. https://www.sasview.org/docs/user/qtgui/Calculators/sas_calculator_help.html.
- Majumdar, A., & Lindner, B. (2023). *Sassena*. <https://codebase.helmholtz.cloud/DAPHNE4NFDI/sassena>. <https://doi.org/10.5281/zenodo.10037485>
- Majumdar, A., Müller, M., & Busch, S. (2024). Computation of x-ray and neutron scattering patterns to benchmark atomistic simulations against experiments. *International Journal of*

- 128 *Molecular Sciences*, 25(3), 1547. <https://doi.org/10.3390/ijms25031547>
- 129 Majumdar, A., Müller, M., & Busch, S. (2026). *Characterization of nanomaterials through*
 130 *complementary use of continuum simulations and small angle scattering measurements.*
 131 SSRN working paper. <https://doi.org/10.2139/ssrn.6460568>
- 132 Reich, V., Majumdar, A., Müller, M., & Busch, S. (2022). Comparison of molecular dy-
 133 namics simulations of water with neutron and x-ray scattering experiments. *EPJ Web of*
 134 *Conferences*, 272, 01015. <https://doi.org/10.1051/epjconf/202227201015>
- 135 Róg, T., Murzyn, K., Hinsén, K., & Kneller, G. R. (2003). nMoldyn: A program package
 136 for a neutron scattering oriented analysis of molecular dynamics simulations. *Journal of*
 137 *Computational Chemistry*, 24(5), 657–667. <https://doi.org/10.1002/jcc.10243>
- 138 SasView Developers. (2026). *SasView–version 6.1.3*. <https://www.sasview.org>.
- 139 Schmidt-Rohr, K. (2007). Simulation of small-angle scattering curves by numerical fourier
 140 transformation. *Journal of Applied Crystallography*, 40(1), 16–25. [https://doi.org/10.](https://doi.org/10.1107/S002188980604550X)
 141 [1107/S002188980604550X](https://doi.org/10.1107/S002188980604550X)
- 142 UKRI STFC ISIS Neutron and Muon Facility. (2023). *MDANSE–version 2.0.1*. [https:](https://github.com/ISISNeutronMuon/MDANSE/)
 143 [//github.com/ISISNeutronMuon/MDANSE/](https://github.com/ISISNeutronMuon/MDANSE/).
- 144 Walter, N. P., Jaiswal, A., Cai, Z., & Zhang, Y. (2018). LiquidLib: A comprehensive
 145 toolbox for analyzing classical and ab initio molecular dynamics simulations of liquids and
 146 liquid-like matter with applications to neutron scattering experiments. *Computer Physics*
 147 *Communications*, 228, 209–218. <https://doi.org/10.1016/j.cpc.2018.03.005>
- 148 Z-laboratory. (2023). *Liquidlib–version 1.0*. [https://github.com/Z-Laboratory/LiquidLib/tree/](https://github.com/Z-Laboratory/LiquidLib/tree/master)
 149 [master](https://github.com/Z-Laboratory/LiquidLib/tree/master).