



# O-CAOH2\_SG164\_CALCIUMHYDROXIDE @ 20.00K


## Thermal cross sections




O-CAOH2\_SG164\_CALCIIUMHYDROXIDE @ 20.00K  
Thermal mubar




O-CAOH2\_SG164\_CALCIIUMHYDROXIDE @ 20.00K  
Thermal ebar




O-CAOH2\_SG164\_CALCULATED HYDROXIDE @ 20.00K  
thermal inelastic




O-CAOH2\_SG164\_CALCULATED HYDROXIDE @ 20.00K  
thermal inelastic




O-CAOH2\_SG164\_CALCIUMHYDROXIDE @ 20.00K  
thermal inelastic



O-CAOH2\_SG164\_CALCULATED @ 20.00K  
thermal inelastic




O-CAOH2\_SG164\_CALCIIUMHYDROXIDE @ 20.00K  
thermal inelastic for e= 1.012E-09 MeV







O-CAOH2\_SG164\_CALCIIUMHYDROXIDE @ 20.00K  
thermal inelastic for e= 1.417E-08 MeV



O-CAOH2\_SG164\_CALCIIUMHYDROXIDE @ 20.00K  
thermal inelastic for e= 9.000E-08 MeV



O-CAOH2\_SG164\_CALCIIUMHYDROXIDE @ 20.00K  
thermal inelastic for e= 5.033E-07 MeV



O-CAOH2\_SG164\_CALCIIUMHYDROXIDE @ 20.00K  
thermal inelastic for e= 4.070E-06 MeV

