




O-CAOH2_SG164_CALCIUMHYDROXIDE @ 600.00K
Thermal cross sections




O-CAOH2_SG164_CALCIUMHYDROXIDE @ 600.00K
Thermal mubar




O-CAOH2_SG164_CALCIUMHYDROXIDE @ 600.00K
Thermal ebar




O-CAOH2_SG164_CALCULATED HYDROXIDE @ 600.00K
thermal inelastic




O-CAOH2_SG164_CALCULATED HYDROXIDE @ 600.00K
thermal inelastic




O-CAOH2_SG164_CALCULATED HYDROXIDE @ 600.00K
thermal inelastic




O-CAOH2_SG164_CALCULATED HYDROXIDE @ 600.00K
thermal inelastic




O-CAOH2_SG164_CALCIIUMHYDROXIDE @ 600.00K
thermal inelastic for e= 1.012E-09 MeV




O-CAOH2_SG164_CALCIIUMHYDROXIDE @ 600.00K
thermal inelastic for e= 1.417E-08 MeV



O-CAOH2_SG164_CALCULATED HYDROXIDE @ 600.00K
thermal inelastic for $e = 9.000\text{E-}08$ MeV



O-CAOH2_SG164_CALCULATED HYDROXIDE @ 600.00K
thermal inelastic for $e = 5.033 \times 10^{-7}$ MeV



O-CAOH2_SG164_CALCULUMHYDROXIDE @ 600.00K
thermal inelastic for e= 4.070E-06 MeV

