




O-NAOH\_SG63\_SODIUMHYDROXIDE @ 293.60K  
Thermal cross sections




O-NAOH\_SG63\_SODIUMHYDROXIDE @ 293.60K  
Thermal mubar




O-NAOH\_SG63\_SODIUMHYDROXIDE @ 293.60K  
Thermal ebar




O-NAOH\_SG63\_SODIUMHYDROXIDE @ 293.60K  
thermal inelastic




O-NAOH\_SG63\_SODIUMHYDROXIDE @ 293.60K  
thermal inelastic




O-NAOH\_SG63\_SODIUMHYDROXIDE @ 293.60K  
thermal inelastic



O-NAOH\_SG63\_SODIUMHYDROXIDE @ 293.60K  
thermal inelastic




O-NAOH\_SG63\_SODIUMHYDROXIDE @ 293.60K  
thermal inelastic for e= 1.012E-09 MeV







O-NAOH\_SG63\_SODIUMHYDROXIDE @ 293.60K  
thermal inelastic for  $e = 1.417\text{E-}08$  MeV



O-NAOH\_SG63\_SODIUMHYDROXIDE @ 293.60K  
thermal inelastic for e= 9.000E-08 MeV



O-NAOH\_SG63\_SODIUMHYDROXIDE @ 293.60K  
thermal inelastic for  $e = 5.033\text{E-}07$  MeV



O-NAOH\_SG63\_SODIUMHYDROXIDE @ 293.60K  
thermal inelastic for  $e = 4.070\text{E-}06$  MeV

