




PB-PBO-BETA_SG57_BETALEADMNNOXIDE @ 800.00K
Thermal cross sections




PB-PBO-BETA_SG57_BETALEADMONOXIDE @ 800.00K
Thermal mubar




PB-PBO-BETA_SG57_BETALEADMONOXIDE @ 800.00K
Thermal ebar




PB-PBO-BETA_SG57_BETALEADMONOXIDE @ 800.00K
thermal inelastic




PB-PBO-BETA_SG57_BETALEADMONOXIDE @ 800.00K
thermal inelastic




PB-PBO-BETA_SG57_BETALEADMONOXIDE @ 800.00K
thermal inelastic




PB-PBO-BETA_SG57_BETALEADMONOXIDE @ 800.00K
thermal inelastic




PB-PBO-BETA_SG57_BETALEADMONOXIDE @ 800.00K
thermal inelastic for e= 1.012E-09 MeV




PB-PBO-BETA_SG57_BETALEADMONOXIDE @ 800.00K
thermal inelastic for e= 1.417E-08 MeV



PB-PBO-BETA_SG57_BETALEADMONOXIDE @ 800.00K
thermal inelastic for e= 9.000E-08 MeV



PB-PBO-BETA_SG57_BETALEADMONOXIDE @ 800.00K
thermal inelastic for e= 5.033E-07 MeV



PB-PBO-BETA_SG57_BETALEADMONOXIDE @ 800.00K
thermal inelastic for e= 4.070E-06 MeV

