




O-MGOH2\_SG164\_MAGNESIUMHYDROXIDE @ 293.60K  
Thermal cross sections




O-MGOH2\_SG164\_MAGNESIUMHYDROXIDE @ 293.60K  
Thermal mubar




O-MGOH2\_SG164\_MAGNESIUMHYDROXIDE @ 293.60K  
Thermal ebar




O-MGOH2\_SG164\_MAGNESIUMHYDROXIDE @ 293.60K  
thermal inelastic




O-MGOH2\_SG164\_MAGNESIUMHYDROXIDE @ 293.60K  
thermal inelastic




O-MGOH2\_SG164\_MAGNESIUMHYDROXIDE @ 293.60K  
thermal inelastic



O-MGOH2\_SG164\_MAGNESIUMHYDROXIDE @ 293.60K  
thermal inelastic




O-MGOH2\_SG164\_MAGNESIUMHYDROXIDE @ 293.60K  
thermal inelastic for e= 1.012E-09 MeV







O-MGOH2\_SG164\_MAGNESIUMHYDROXIDE @ 293.60K  
thermal inelastic for e= 1.417E-08 MeV



O-MGOH2\_SG164\_MAGNESIUMHYDROXIDE @ 293.60K  
thermal inelastic for  $e = 9.000\text{E-}08$  MeV



O-MGOH2\_SG164\_MAGNESIUMHYDROXIDE @ 293.60K  
thermal inelastic for e= 5.033E-07 MeV



O-MGOH2\_SG164\_MAGNESIUMHYDROXIDE @ 293.60K  
thermal inelastic for e= 4.070E-06 MeV

