




PB-PBO-ALPHA\_SG129\_ALPHALEADMNNOXIDE @ 300.00K  
Thermal cross sections




PB-PBO-ALPHA\_SG129\_ALPHALEADMNNOXIDE @ 300.00K  
Thermal mubar




PB-PBO-ALPHA\_SG129\_ALPHALEADMNNOXIDE @ 300.00K  
Thermal ebar




PB-PBO-ALPHA\_SG129\_ALPHALEADMONOXIDE @ 300.00K  
thermal inelastic




PB-PBO-ALPHA\_SG129\_ALPHALEADMONOXIDE @ 300.00K  
thermal inelastic




PB-PBO-ALPHA\_SG129\_ALPHALEADMONOXIDE @ 300.00K  
thermal inelastic



PB-PBO-ALPHA\_SG129\_ALPHALEADMONOXIDE @ 300.00K  
thermal inelastic




PB-PBO-ALPHA\_SG129\_ALPHALEADMONOXIDE @ 300.00K  
thermal inelastic for  $e = 1.012 \times 10^{-9}$  MeV







PB-PBO-ALPHA\_SG129\_ALPHALEADMONOXIDE @ 300.00K  
thermal inelastic for  $e = 1.417\text{E-}08$  MeV



PB-PBO-ALPHA\_SG129\_ALPHALEADMONOXIDE @ 300.00K  
thermal inelastic for e= 9.000E-08 MeV



PB-PBO-ALPHA\_SG129\_ALPHALEADMNNOXIDE @ 300.00K  
thermal inelastic for e= 5.033E-07 MeV



PB-PBO-ALPHA\_SG129\_ALPHALEADMONOXIDE @ 300.00K  
thermal inelastic for  $e = 4.070E-06$  MeV

